Int. J. Nano Dimens., 8(1): 31-39, Winter 2017

ORIGINAL ARTICLE

Effect of nano Zinc Oxide on gas permeation through mixed matrix Poly (Amide-6-b-Ethylene Oxide)-based membranes

Mahdi Sheikh¹; Morteza Asghari^{1, 2*}; Morteza Afsari³

¹Department of Chemical Engineering, Shahrood Branch, Islamic Azad University, Shahrood, Iran. ²Separation Processes Research Group (SPRG), Department of Engineering, University of Kashan, Kashan, Iran. ³Energy Research Institute, University of Kashan, Ghotb-e-Ravandi Ave., Kashan, Iran.

Received 29 October 2016; revised 10 January 2017; accepted 31 January 2017; available online 16 February 2017 Abstract

Poly (amide-6-b-ethylene oxide)/zinc oxide (PEBA/ZnO) mixed matrix membranes were fabricated using ethanol/water as solvent by solvent casting method. The concentration of ZnO in membrane was set to 0.1 wt.% and the synthesized membranes were characterized by AFM and FTIR. Effects of ZnO nanoparticle on CO_2 , CH_4 and N_2 permeabilities, and CO_2/N_2 and CO_2/CH_4 selectivities of the membranes were investigated at the ambient temperature and pressure range of 4–12 bar. The results revealed that the CO_2 permeability of the nano-composite membrane increased 158 % with pressure, from 54.08 barrer (at 4 bar) to 139.59 barrer (at 12 bar). Furthermore, CO_2 permeability for the nano-composite membrane was higher than neat polymeric membrane. The PEBA/ZnO nano-composite membranes thus provide a promising potential for CO_2/N_2 and CO_2/CH_4 separation.

Keywords: CO, permeation; Gas separation; Mixed matrix membrane; PEBA; Nano-composite; ZnO.

How to cite this article

Sheikh M, Asghari M, Afsari M. Effect of nano Zinc Oxide on gas permeation through mixed matrix poly (Amide-6-b-Ethylene Oxide)-based membranes. Int. J. Nano Dimens., 2017; 8(1): 31-39, DOI: 10.22034/ijnd.2017.24374

INTRODUCTION

Membrane gas separation, dynamic а and rapidly growing field, showed excellent operational properties such as high selectivity and permeability, low energy requirements, and ease of the operation. Polymeric membranes are generally considered to be an effective tool for the separation of gaseous mixtures, due to their manufacturability, superior environmental friendliness, modularity, low running costs, robust physical characteristics, and good intrinsic transport properties [1–3]the existing membrane materials, membrane structures and formation processes are inadequate to fully exploit these opportunities. The requirements for viability of membranes vary somewhat with each application. Nevertheless, the key requirements of durability, productivity and separation efficiency must be balanced against cost in all cases. The various `contender' technologies for large scale gas

* Corresponding Author Email: asghari@kashanu.ac.ir

separation membrane applications and the gas transport mechanisms are considered. The current spectrum of applications of gas separation membranes include; nitrogen enrichment, oxygen enrichment, hydrogen recovery, acid gas (CO₂, H2S. Although polymeric membranes have been well developed for gas separation processes, but the trade-off between permeability and selectivity limits their application in large industrial scales [4-6]. PEBA have some advantages which made it susceptible for preparation of composite membranes [7–11]. PEBA, a copolymer comprised of hard segments of polyamide (PA) and soft segments of polyether (PE), are known as an excellent material for separation of CO, from light gases (e.g.H, or N,). The polymer structure consists of linear chains of polyamide segments interspaced with polyether segments [12, 13] flexible, or rubbery. The general chemical structure of PEBA is demonstrated in Fig. 1.

HO —
$$\begin{bmatrix} C & -PA & -C & -O & -PE & -O \end{bmatrix}_n - H$$

Fig. 1: Chemical structure of PEBA.

In this segmented block copolymer, two separated micro phase domains are formed: first, the polyamide crystalline domains which provide mechanical strength, and the second the polyether amorphous domains which high chain mobility of its ether linkages offer high gas permeability [14]. Different grades of PEBA polymers are commercially available and they generally have excellent mechanical strength and good chemical resistance [15]. Studies pointed to a hydrophilic grade of PEBA prepared by incorporation of low molecular weight poly ethers, known as PEBA 1657 (60 wt% poly (ethylene oxide) and 40 wt% polyamide) which causes enhancement of permeability without scarifying the selectivity. Higher permeability appears to stem from the increase in poly ether content of the polymer, as well as increase in total free volume [16, 17]. The main purpose for production of mixed matrix membranes (MMMs) is to improve the performance of membranes to exceed the Robeson's upper-bound line [5]. Some recent investigations have been carried out to improve the gas transport properties of polymeric membranes by embedding of nanoparticles. The inorganic fillers which are dispersed in polymeric matrix should be technically capable to improve membrane separation performance. The nanocomposite materials could combine the advantages of both component materials: the flexibility and process-ability of polymers, and the selectivity and thermal stability of the inorganic fillers [18] the existing polymeric membrane materials are inadequate to fully exploit the application opportunities on industrial scale; the improvement in permeability is at the expense of selectivity, and vice versa. A new type of membrane material emerging with the potential for future applications is mixed matrix materials composed of homogeneously interpenetrating polymeric and inorganic particle matrices. Compared to original polymeric membranes, significant improvement in separation properties with trivial loss in membrane flexibility is expected for the resultant mixed matrix membranes (MMMs). There were many inorganic

nanoparticles used to prepare MMMs for gas separation. They are usually organized into two main categories namely porous and nonporous [19]. The inorganic porous filler has got the effect of molecular sieving – separating gases by their size or shape [20, 21]. The resulting membranes revealed higher permeability and selectivity of desired components. Also in the case of pore sizes significantly larger than the size of gaseous molecule, absorption and selective surface flow mechanism is dominated as main mechanism [6].

Nonporous inorganic fillers generally cause decrease in the diffusion of larger molecules and increase in the matrix tortuous pattern. Presence of small size (nanometric) inorganic materials might increase void volume of membranes by disrupting polymer chains, leading to higher gas diffusion [22, 23]. Zinc oxide (ZnO), with its unique physical and chemical properties such as high chemical stability, high electrochemical coupling coefficient, broad range of radiation absorption, and high photostability is a multifunctional material, fit for using as nano filler in MMMs [24, 25]. Nowadays ZnO is broadly used in nanotechnology science fields to enhance operation of materials and devices through different techniques in nanometer scale. Due to its vast areas of application, various synthetic methods have been deployed to grow a variety of ZnO nanostructures including nanoparticles, nanowires, nanorods, nanotubes, nanobelts, and so on [24, 26, 27]. Some studies surveyed the use of ZnO nanoparticles for fabrication of MMMs, but the role of ZnO in MMMs for gas separation has not been reported, yet.

ZnO is more economical than other nanoparticles used for gas separation, like TiO_2 . In addition, the supplementation of ZnO could improve mechanical properties of the polymer matrix [25, 27, 28]. Therefore, employment of ZnO nanoparticles in polymeric membranes could be labeled as an innovative and promising technology which may be a key for the development of low cost and high performance gas separation membranes [29-32].

In this work, preparation of PEBA/nano ZnO MMMs was proposed as a novel gas separation membrane. However, we mainly focused on ZnO nanoparticles synthesized by thermal decomposition [26, 33]. The effect of ZnO incorporation on the membrane characteristics and its separation performance was evaluated. Gas permeation properties of these newly

Int. J. Nano Dimens., 8 (1): 31-39, Winter 2017

fabricated membranes were compared with neat PEBA membrane using CO_2 , CH_4 and N_2 single gas permeation experiments.

EXPERIMENTAL

Materials

The copolymer used in this work was supplied by Arkema under the trade name of PEBAX~ MX1657. Also, CO_2 and N_2 gas cylinders with purity of 99.99% were supplied from Roham Gas Company, Iran. ZnO nanoparticles was previously produced in University of Kashan (Fig. 2) and the procedure of manufacturing was described elsewhere in detail [26, 33]. According to the transmission electron microscope (TEM) and scanning electron microscopy (SEM) images, the average size of the ZnO nanospheres ranged from 12 to 20 nm.

MMMs preparation

ZnO nano crystals were firstly added to a solvent mixture of ethanol-water, stirred for 24 h. Then PEBA copolymers were added to solution to obtain 0.1 wt.% solution. In this step nanoparticles are soaked to enhance its dispersion through solution. Afterwards, an 8 wt.% PEBA dope was prepared by gradually addition of the PEBA to the solution. The solution was then sonicated for 15 minutes to obtain a fairly homogeneous solution. Solution casting and solvent evaporation technique were applied to prepare thin films of the membranes. The obtained body of the MMM was dried in a vacuum oven overnight to remove solvent. The MMM preparation procedure is schematically shown in Fig. 3.

Membrane characterization

In order to characterize the structure and morphology of prepared membranes, Fourier Transform Infrared (FTIR) and Atomic Force Microscopy (AFM) analysis were applied. FT-IR spectra of all the nanocomposite thin layers were recorded on spectrometer Nicolet-550 in KBr pellets at room temperature and in the range of 400-4000 cm⁻¹ by resolution of 4 cm⁻¹ for each spectrum. AFM was conducted with NT-MDT Solver P47 (The Moscow, Russia) to study the surface morphologies of neat PEBA and MMMs. Also SEM images were taken for neat and mixed matrix membranes. The morphology of crosssectional of membranes was observed using a field emission scanning electron microscopy (FESEM; MIRA3\\TESCAN (Czech Republic)) at 15kV.

Gas permeation experiments

Fig 4 (4a, and 4b) show the schematic of experimental system for gas permeability measurements. It consists of an upstream gas source, a membrane cell, and a downstream device for permeate flux measurement. The membrane's effective area in the module was 20.67 cm². The feed pressure varied in a range of 2 to 12 bar and the permeate side was kept at atmospheric pressure during all the experiments. In stable conditions, the pure gas permeability of the membranes was calculated using the following equation:

 $P = \frac{q(STP)l}{S\Delta P}$

Where *P* is the permeability coefficient in terms of the Barrer, 10^{-10} cm³ (STP) cm/ (cm² s cmHg), ΔP is the pressure gradient across the membrane expressed in cmHg, q, I and S are volumetric flow rate (cm³/s), membrane thickness (cm), and effective surface area of membranes (cm²), respectively. The average thickness of the MMMs thin film was about 15-20 µm, estimated by an accurate micrometer.

Ideal separation factor $\alpha_{_{A/B}}$ is defined as the ratio of the permeabilities of the two pure gases: $\alpha_{_{A/B}}=P_{_A}/P_{_B}$



Fig. 2: a and b) SEM image and TEM image of ZnO nanoparticles [27].



Fig. 3: A schematic procedure for preparation of MMMs of this study.



Fig. 4: a and b) Schematic of the experimental setup for gas permeability measurement, and membrane module.

RESULTS AND DISCUSSION

Characterization of the MMMs

FTIR: For better understanding of PEBA and ZnO interaction at the molecular level, FTIR spectroscopy was used in the range of 4000-400 cm⁻¹. Figs (5a, 5b and 5c) show the FTIR spectra of ZnO nanocrystals, PEBA membrane, and PEBA/ZnO MMM, respectively. As presented in Fig. 5a, the strong peak around 434 cm⁻¹ shows a distinct stretching mode of ZnO crystals. In neat PEBA (Fig. 5b), the characteristic peaks at 1732 and 1102 cm⁻¹ represented –C–O and –C–O– stretching vibrations, respectively. The peaks at 1641 and

3300 cm⁻¹ indicated the presence of H–N–C–O and the N–H group, respectively. The stretching vibration at 2940 cm⁻¹ is attributed to the presence of aliphatic –C–H. The C–O stretching in the amide group of PEBA consist of two types: the free amide C–O peak at 1657 cm⁻¹, and the hydrogen bonded amide peak at 1640 cm⁻¹. Fig. 5c shows FTIR spectrum of 0.1 wt.% ZnO MMM, where the peaks mostly synchronized with the ones in the neat PEBA membrane. However, a single peak in the range of 400 cm⁻¹ proved the presence of ZnO nanoparticles in prepared PEBA /ZnO MMM.

AFM: AFM surface images of neat PEBA and

PEBA/ZnO membranes in Figs (6a and 6b) indicated that the neat membrane surface is very smooth, but the surface roughness increased with loading of 0.1 wt% ZnO. This increase in surface roughness provided a membrane with more effective surface area, proper for better contact of gas molecules with membrane surface and more possibility for gas dissolution onto the polymeric surface [15, 34, 35].

SEM: Fig. 7 shows SEM images of neat and MMM. Due to low percentage of nanofillers, addition of ZnO nanoparticle has relatively small effect on structure of membrane matrix. The cross section of both neat and MMM showed a smooth surface and no defect were observed in the images.

Gas permeation results

Fig. 8 shows the effect of ZnO nanoparticles on CO, permeability of PEBA/ZnO membrane, in comparison to neat PEBA membrane. As shown, the presence of the nanoparticles within the polymeric matrix led to an increase in CO₂ permeability. Zinc oxide is an important type of non-porous inorganic fillers which has good affinity to CO₂. Unlike porous inorganic fillers, the non-porous ones could alter the chain packing of glassy polymers causing larger free volumes and leading to a significant enhancement in permeability. Additionally Fig. 6 shows that addition of ZnO nanofillers to PEBA increased the surface roughness of the membrane, and subsequently the effective interface of gasmembrane increased, and as a result the gas permeability increased.

The rubbery characteristic of PEBA provides the quadrapolar nature and cause more permeation of CO₂ relative to N₂ and CH₄. On the other hand, kinetic diameter of CO₂ (3.3 Å) is also smaller than those of N₂ (3.64 Å) and CH₄ (3.8 Å), which may also led to greater diffusivity of CO₂, compare

to N₂ and CH₄. For polymeric membranes the solution-diffusion mechanism has gained widespread acceptance in describing the gas permeation results. After ZnO loading, PEBA/ ZnO membrane showed significant improvement in CO, permeability, from 74.34 barrer for neat membrane to 139.59 barrer for MMM with 88% increase, in 12 bar, while ZnO loading had little effect on N₂ and CH₄ permeabilities and remained almost constant in about 4.2 and 8.9 for N₂ and CH₄, respectively. As a consequence, ideal selectivities of CO₂/N₂ and CO₂/CH₄ increased, from 17.2 to 33.16 for CO₂/N₂ and from 8.2 to 15.77 for CO₂/ CH,.

For neat PEBA, CO_2 permeability increased from 61.18 to 74.34 barrer with pressure, whereas for PEBA/ZnO MMM it enhanced from 58.56 to 139.59 barrer.

CO₂, CH₄ and N₂ permeabilities through PEBA/ZnO MMM at different operating pressures are shown in Fig. 9. As seen, the CO₂ permeability increased from 54.08 to 139.59 barrers in pressure range of 4 to 12 bar, while the CH₄ and N₂ permeations were almost remained constant by pressure. Gradual increase in the permeability with pressure is attributed to increase in the sorption of the polar CO, gas into the polymer membrane, which has a preferential affinity for this gas. These membranes revealed a suitable permeability for CO₂, as a gas by high polarity characteristic, and low permeation for CH₄ and N₂, as gases by lower polarity characteristic. Fig. 10 illustrates the CO_2/N_2 and CO_2/CH_4 ideal selectivities of the synthesized MMM. The ideal selectivity also enhanced by pressure from 6.67 to 15.77 for CO₂/CH₂, and from 10.97 to 33.16 for CO_2/N_2 , respectively. The rise in CO_2/N_2 and CO_2/N_2 CH, ideal selectivities of the membranes could be attributed to the plasticization effect of the PEBA polymer matrix.



Fig. 5: a, b and c) - FTIR of ZnO nanocrystals, neat PEBA, and PEBA/0.1 wt.% ZnO MMM.

M. Sheikh et al.



Fig. 6: a and b) Surface morphology of membranes obtained by AFM for neat PEBA, and PEBA/0.1 wt. % ZnO 0.1 MMM.



Fig. 7: a and b) SEM images of mixed matrix membranes and neat membrane.

Int. J. Nano Dimens., 8 (1): 31-39, Winter 2017





Fig. 8: CO_2 permeation through PEBA and PEBA/ZnO membrane versus pressure.



Fig. 9: \rm{CO}_2, \rm{CH}_4 and \rm{N}_2 permeability versus feed pressure for PEBA/ZnO MMMs.



Fig. 10: Effect of feed pressure on ideal selectivity.

CONCLUSIONS

The nanocomposites membrane, based on PEBA and ZnO were fabricated for CO₂/N₂ and CO₂/CH₄ separation. The effects of incorporation of ZnO nanoparticles into the polymer matrix were investigated. The FTIR of nanocomposite revealed that ZnO nanoparticles induced physical interactions with the polymer matrix. AFM images showed that the neat membrane surface was very smooth and its roughness increased with ZnO loading. The gas permeability experiment showed that the permeation of CO₂ increased with feed pressure for PEBA-ZnO 0.1 wt.%, while the permeation of CH, and N, was fairly independent to pressure. PEBA-ZnO 0.1 wt.% membrane exhibited higher CO, permeability relative to the neat PEBA membrane under the same conditions. Incorporation of ZnO nanoparticles into PEBA-1657 polymer matrix showed high potential for CO₂/N₂ and CO₂/CH₄ separation processes. Therefore, the ZnO filled PEBA membrane has shown enough potential for further research.

ACKNOWLEDGMENTS

The authors are dearly appreciated Research & Technology Directorate at National Iranian Gas Company (NIGC) and Energy Research Institute at University of Kashan for supporting this work.

CONFLICT OF INTEREST

The authors declare that there is no conflict of interests regarding the publication of this manuscript.

REFERENCES

- Koros W. J., Mahajan R., (2001), Pushing the limits on possibilities for large scale gas separation: Which strategies? *J. Memb. Sci.* 181: 141-146.
- [2] Nath K., Maroulis Z. B., George D. S., (2008), Membrane Separation Processes, in: Food Process Design. 34: 336-340.
- [3] Li N. N., Fane A. G., Ho W. S. W., Matsuura T., (2008), Seawater desalinationby ultralowenergy reverse osmosis. *Adv. Memb. Technol. and Applics.* 217-238.
- [4] Robeson L. M., (1991), Correlation of separation factor versus permeability for polymeric membranes. J. Memb. Sci. 62: 165–185.
- [5] Robeson L. M., (2008), The upper bound revisited. J. Memb. Sci. 320: 390–400.
- [6] Bertelle S., Gupta T., Roizard D., Vallières C., (2006), Study of polymer-carbon mixed matrix membranes for CO₂ separation from flue gas. *Desalination*. 199: 401–402.
- [7] Groß A., Heintz A., (2000), Diffusion coefficients of aromatics in nonporous PEBA membranes. J. Memb. Sci. 168: 233–242.
- [8] Cen Y., Staudt-Bickel C., Lichtenthaler R. N., (2002), Sorption properties of organic solvents in PEBA membranes. J. Memb. Sci. 206: 341–349.

- [9] Liu L., Chakma A., Feng X., (2004), A novel method of preparing ultrathin poly(ether block amide) membranes. J. Memb. Sci. 235: 43–52.
- [10] Kujawski W., Warszawski A., Ratajczak W., Porębski T., (2004), Application of pervaporation and adsorption to the phenol removal from wastewater. *Sep. Purif. Technol.* 40: 123–132.
- [11] Wu P., Field R. W., England R., Brisdon B. J., (2001), A fundamental study of organofunctionalised PDMS membranes for the pervaporative recovery of phenolic compounds from aqueous streams. J. Memb. Sci. 190: 147–157.
- [12] Holden G., (2011), 6 Thermoplastic Elastomers. Appl. Plast. Eng. Handb. - Process. Mater. 77-91.
- [13] Deleens G., Foy P., Maréchal E., (1977), Synthese et caracterisation de copolycondensats sequences poly(amide-seq-ether)-II. Poly-condensation d'oligomeres polyamides-11diacides diesters avec des oligomeres polyethers dihydroxy. *Eur. Polym. J.* 13: 343-351.
- [14] Flesher J. R., (1987), Polyether block amide: highperformance TPE. Mod. Plast. 100-110.
- [15] Surya Murali R., Sridhar S., Sankarshana T., Ravikumar Y. V. L., (2010), Gas permeation behavior of pebax-1657 nanocomposite membrane incorporated with multiwalled carbon nanotubes. *Ind. Eng. Chem. Res.* 49: 6530–6538.
- [16] Car A., Stropnik C., Yave W., Peinemann K. V., (2008), PEG modified poly(amide-b-ethylene oxide) membranes for CO₂ separation. J. Memb. Sci. 307: 88-95.
- [17] Yave W., Car A., Peinemann K. V., (2010), Nanostructured membrane material designed for carbon dioxide separation. *J. Memb. Sci.* 350: 124–129.
- [18] Chung T. S., Jiang L. Y., Li Y., Kulprathipanja S., (2007), Mixed matrix membranes (MMMs) comprising organic polymers with dispersed inorganic fillers for gas separation. *Prog. Polym. Sci.* 32: 483–507.
- [19] Vu D. Q., Koros W. J., Miller S. J., (2003), Mixed matrix membranes using carbon molecular sieves: I. Preparation and experimental results. J. Memb. Sci. 211: 311-334.
- [20] Vu D. Q., Koros W. J., Miller S. J., (2003), Mixed matrix membranes using carbon molecular sieves. J. Memb. Sci. 211: 311-334.
- [21] Anson M., Marchese J., Garis E., Ochoa N., (2004), ABS copolymer-activated carbon mixed matrix membranes for CO₂/CH₄ separation. J. Memb. Sci. 243: 19–28.
- [22] Ahn J., Chung W. J., Pinnau I., Guiver M. D., (2008), Polysulfone/silica nanoparticle mixed-matrix membranes for gas separation. J. Memb. Sci. 314: 123-133.
- [23] Kolodziejczak-Radzimska A., Jesionowski T., (2014), Zinc oxide-from synthesis to application: A review. *Materials* (*Basel*). 7: 2833-2881.
- [24] Oxide Z., (2013), Synthesis and enhanced mechanical properties of nano Zinc Oxide in Polyvinyl alcohol and Polyvinyl pyrollidone composite film. *Int. J. Nano Dimens.* 4: 153-159.
- [25] Wang Z. L., (2004), Zinc oxide nanostructures: growth, properties and applications. J. Phys. Condens. Matter. 16: R829-R858.
- [26] Salavati-Niasari M., Davar F., Mazaheri M., (2008), Preparation of ZnO nanoparticles from [bis(Acetylacetonato) Zinc(II)]-Oleylamine complex by thermal decomposition. *Mater. Lett.* 62: 1890–1892.
- [27] Mastali N., Bakhtiari H., (2013), Investigation on the structural, morphological and photochemical properties of spin-coated TiO₂ and ZnO thin films prepared by sol-gel method. *Int. J. Nano Dimens.* 5: 113-121.
- [28] Soroko I., Livingston A., (2009), Impact of TiO, nanoparticles

Int. J. Nano Dimens., 8 (1): 31-39, Winter 2017

M. Sheikh et al.

on morphology and performance of crosslinked polyimide organic solvent nanofiltration (OSN) membranes. *J. Memb. Sci.* 343: 189–198.

- [29] Balta S., Sotto A., Luis P., Benea L., (2012), A new outlook on membrane enhancement with nanoparticles: The alternative of ZnO. J. Memb. Sci. 389: 155-161.
- [30] Leo C. P., Cathie Lee W. P., Ahmad A. L., Mohammad A. W., (2012), Polysulfone membranes blended with ZnO nanoparticles for reducing fouling by oleic acid. *Sep. Purif. Technol.* 89: 51-56.
- [31] Hong J., He Y., (2012), Effects of nano sized zinc oxide on the performance of PVDF microfiltration membranes. *Desalination*. 302: 71-79.

[32] Silane T., Acid O., (2015), Surface modification of ZnO

nano-particles with Trimetoxyvinyl Silane and Oleic Acid and studying their dispersion in organic media. *Int. J.Nano Dimens.* 6: 67-75.

- [33] Salavati-Niasari M., Davar F., Fereshteh Z., (2009), Synthesis and characterization of ZnO nanocrystals from thermolysis of new precursor. *Chem. Eng. J.* 146: 498-502.
- [34] Nejad M. N., Asghari M., Afsari M., (2016), Investigation of Carbon Nanotubes in Mixed Matrix Membranes for Gas Separation: A Review. *Chem. Bio. Eng. Rev.* 55: 12616-12631.
- [35] Mahmoudi A., Asghari M., Zargar V., (2015), CO₂/CH4 separation through a novel commercializable three-phase PEBA/PEG/NaX nanocomposite membrane. J. Ind. Eng. Chem. 23: 238-242.