## REVIEW

### **Open Access**

# Atomic transport and surface properties of some simple liquid metal using one component plasma system

Yogeshkumar A Sonvane<sup>1\*</sup>, Pankajsinh B Thakor<sup>2</sup> and Ashwin R Jani<sup>3</sup>

#### Abstract

In the present paper, we have calculated diffusion coefficient, viscosity coefficient, and surface tension of liquid metals near melting point (Li, Na, K, Rb, Cs, Mg, Al, Pb, and Bi). We have applied our newly constructed model potential to describe electron ion interaction with one component plasma reference system. We have also investigated the effect of different correction functions such as those of Hartree, Hubbard and Sham, Vashista and Singwi, Taylor, Ichimaru and Utsumi, Farid et al., and Sarkar et al. on the above-said properties. It is observed that the present results are found to be in good agreement with those of experimental data as well as with other theoretical results.

Keywords: Diffusion coefficient, Viscosity coefficient, Surface tension, Liquid metal

#### Review

#### Introduction

Transport coefficients such as diffusion and viscosity coefficients of liquids are important quantities both from the scientific and technological points of view. For example, knowledge of liquid-state diffusion coefficient is required to understand important material processing techniques. A binary solidification is controlled by the diffusion of reactant species. Experimental measurement of the self-diffusion coefficient of liquid is a difficult task because of the high sensitivity of the phenomenon to external perturbations such as convention effects. The knowledge of viscosity is required in determining the critical cooling rates for glass formation. On the other hand, it is not fully understood how they depend on the structure and the thermodynamics of liquids as well. Finding a relationship between the transport coefficient and structural properties remains one of the most challenging tasks in the field of condensed matter [1-7]. Some attempts have been made since the late 1970s to find relationships between transport and structural properties. Initially, it has been realized for quite different

Full list of author information is available at the end of the article



interaction potentials that the reduced transport coefficient is linked to the reduced entropy by simple expressions using macroscopic reduction parameters such as temperature and density. A similar scaling law which assumes the proportionality between the reduced diffusion coefficient, viscosity coefficient, and excess entropy has been obtained [8,9] using microscopic reduction parameters. The surface properties of liquids have attracted much more interest from both physicists and metallurgists from the long past to the present day because of either scientific or technological importance [10-28]. During soldering, brazing, sintering, and dying, the knowledge of surface properties of the liquid state is required. Although there are a large number of methods to determine the surface properties of liquids such as surface tension, those suitable for liquid metals are limited by their chemical reactivity and high melting points. On the other hand, it is not fully understood how the surface properties depend on the structure and the thermodynamics of the liquids [10].

The surface properties have been studied using different theories, such as the statistical mechanical theory [11,12], density functional theory [13] and computer simulation [15]. The statistical mechanical theory involving surface tension which goes back to Fowler was analyzed and improved by different

© 2012 Sonvane et al.; licensee Springer. This is an Open Access article distributed under the terms of the Creative Commons Attribution License (http://creativecommons.org/licenses/by/2.0), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

<sup>\*</sup> Correspondence: yogesh126@gmail.com

<sup>&</sup>lt;sup>1</sup>Department of Applied Physics, S. V. National Institute of Technology, Surat, Gujarat 395 007, India

Metal	Ζ	T (K) [51]	Density n (gm/cm <sup>3</sup> ) [51]	r <sub>i</sub> (Å)	r <sub>a</sub> (Å)	Packing fraction $\zeta$ [51]	Plasma parameter Г
Li	1	453	0.504	0.68	1.52	0.46	210.62
Na	1	378	0.928	0.95	1.86	0.46	206.45
К	1	343	0.826	1.33	2.27	0.46	183.55
Rb	1	313	1.47	1.48	2.47	0.43	187.86
Cs	1	303	1.84	1.69	2.65	0.43	180.21
Mg	2	953	1.545	0.65	1.60	0.46	120.00
Al	3	943	2.37	0.50	1.43	0.45	100.00
Pb	4	613	10.66	1.20	1.75	0.46	85.00
Bi	3	300	10.03	0.96	1.54	0.40	100

Table 1 Input parameter used in the present study

authors [12-14]. Very recently, Gosh et al. [16] have checked the reliability of the analytical surface entropy formula derived for liquid alkali metals. Here, we have used the pseudopotential approach to describe interionic interaction and determined pair distribution function g(r) from one component plasma (OCP) [29-31] structure factor S(q).

An important application of pseudopotentials is the calculation of transport properties of disordered materials such as liquid, amorphous materials and their alloys. The problem with model pseudopotentials is that of their transferability because there still is no accurate method to obtain the form factor by which all the properties of liquid metals may be successfully investigated. It is found that a particular pseudopotential may be suitable for some properties of some metals and unsuitable for other properties of other metals. The usefulness of any model potential depends on how many number of parameters it involves. Generally, the potential involving less number of parameters is considered to be, comparatively, a better one than that involving more number of parameters because it avoids more complexities in the calculation. It has been observed that a unique method of determination of the potential parameter has not been pointed out so far. A number of investigators have used a fitting procedure in which the potential parameters are fitted in such a way that a good agreement with experimental findings be obtained. Such a procedure will generally give good results for a certain property, but the same set of parameters will not give good results for other properties. Hence, we thought it worthwhile to construct a parameter free model potential which, by employing, explains the physical as well as chemical properties of condensed matter.

A pseudopotential method employing a simple model of a solid composed of atomic cores and valence electrons can predict the existence and properties of new solids and their properties [32]. By implementing this idea, we construct a new model potential which is split into three regions [31,33-37]:

Metal	Calculated viscosity (η) (mPa/s)									
	H [39]	VS [40]	HS [41,42]	S [43]	IU [44]	T [45]	F [46]	Others [22]	Experiments [48,51]	
Li	0.407	0.379	0.393	0.382	0.373	0.378	0.393	0.51	0.602	
Na	0.761	0.694	0.728	0.702	0.684	0.697	0.728	0.56, 0.256	0.70	
К	0.539	0.495	0.518	0.501	0.488	0.499	0.518	0.46, 0.192	0.54	
Rb	0.769	0.721	0.747	0.727	0.709	0.727	0.747	0.56	0.674	
Cs	0.531	0.486	0.511	0.492	0.473	0.486	0.511	0.59	0.686	
Mg	1.166	1.28	1.231	1.251	1.281	1.275	1.231	1.26	1.25	
Al	1.403	1.382	1.392	1.383	1.378	1.378	1.392	1.62	1.2	
Pb	2.615	2.734	2.213	2.772	2.33	2.487	2.213	2.51	2.61	
Bi	1.663	1.55	1.605	1.556	1.498	1.495	1.605	2.34	1.63	

Table 2 Calculated viscosity ( $\eta$ ) (mPa/s) for simple liquid metals

Table 3 Calculated surface tension ( $\gamma$ ) (N/m) for simple liquid metals

Metal	Calculated surface tension ( $\gamma$ ) (N/m)									
	H [39]	VS [40]	HS [41,42]	S [43]	IU [44]	T [45]	F [46]	Experiment		
								[48]		
Li	0.281	0.261	0.264	0.258	0.262	0.272	0.258	0.398		
Na	0.264	0.242	0.243	0.237	0.241	0.253	0.237	0.191		
К	0.136	0.126	0.127	0.123	0.125	0.131	0.124	0.115		
Rb	0.126	0.119	0.119	0.116	0.118	0.122	0.116	0.085		
Cs	0.068	0.063	0.064	0.061	0.063	0.066	0.061	0.070		
Mg	0.624	0.683	0.680	0.686	0.685	0.659	0.686	0.590		
Al	0.709	0.697	0.699	0.696	0.699	0.703	0.696	0.917		
Pb	0.385	0.366	0.408	0.343	0.402	0.325	0.341	0.458		
Bi	0.170	0.153	0.159	0.153	0.159	0.164	0.153	0.378		

$$\begin{aligned} W_B(r) &= 0; & r < r_i, \\ &= -\left(\frac{Ze^2}{r_a}\right) \left\{ 2 - \exp\left(\frac{r}{r_a} - 1\right) \right\}; r_i \le r \le r_a \\ &= -\left(\frac{Ze^2}{r}\right); & r > r_a \end{aligned}$$
 (1)

Basically, this form of the pseudopotential is the modified version of Ashcroft's empty core model [38]. Here, we have considered the actual core of an ion as an empty core rather than pseudizing it. The whole effective region is split into three parts. The effective weak potential felt by an electron is sandwiched between the empty core and the long-range coulomb potential which is continuous at  $r r_a$  and is considered between the ionic radius  $(r_i)$  and atomic radius  $(r_a)$ . It may be noted that most of the pseudopotentials are represented always by twofold splitting in their influence. In the present potential, we have included both the features of the pseudopotential - cancelation as well as the remaining weak interaction around the ion. Another important part of the model potential is that it is parameter free. Looking at the success of the present approach, we believe that it should be interesting to try out all the local forms of the pseudopotential on the line of the present approach.

In the reciprocal space, the corresponding bare-ion form factor of the present model potential is given by the following [31,33-37]:

Here, Z, e,  $\Omega$ , q,  $r_i$ , and  $r_a$  are the valence, electronic charge, atomic volume, wave vector, ionic radius, and atomic radius, respectively.

The choice of the pseudopotential form factor is certainly an important factor in the study of metallic properties, and its actual form is much more sensitive to the choice of dielectric function of the electron gas. Hence, the purpose of the present paper is not only to calculate surface tension  $(\gamma)$ , diffusion coefficient (D), and viscosity coefficient ( $\eta$ ) of liquid metals near melting point (Li, Na, K, Rb, Cs, Mg, Al, Pb and Bi), but also to see the influence of various local-field correction functions in the screening along with the newly constructed model potential [31,33-37]. Thus, we incorporated seven different forms of the exchange and correlation functions, viz. Hartree (H) [39], Vashista and Singwi (VS) [40], Hubbard and Sham (HS), [41,42], Sarkar et al. (SS) [43], Ichimaru and Utsumi(IU) [44], Taylor (T) [45], and Farid et al. (F) [46]. To the best of our knowledge, only few attempts have been made on y, D, and  $\eta$  from transferable pseudopotential. These properties are important quantities from the scientific as well as technological points of view. However, the accurate measurement of these quantities is exceedingly difficult for high-temperature melts such as liquid metals. Furthermore, theoretical calculations of the surface and atomic transport properties are also difficult to perform convincingly. For surface tension, it is necessary to know the ionic and electronic structures in the inhomogeneous transition zone between liquid metal and gaseous phases, the studies of which are still in their infancy in comparison with those in bulk liquids [22]. As for viscosity coefficient, Born and Green [47] have proposed a simplified expression using their kinetic theory. In spite of oversimplified assumptions involved in the derivation, this Born-Green equation has been shown to predict apparently reasonable values for the viscosity coefficient of liquid metals with the help of pair potentials extracted from experimental structural data. However, it is remarkable that these results are by no means quantitatively reliable since pair potentials deduced from the inversion method have large uncertainties [10-28].

$$W_{B}(q) = \frac{-4\pi Z e^{2}}{q^{3}r_{a\ \Omega}\left(1+q^{2}r_{a}^{2}\right)^{2}} \begin{bmatrix} 2\left(1+2\ q^{2}r_{a}^{2}\right)\sin(qr_{a})-qr_{a}\left(1+3\ q^{2}r_{a}^{2}\right)\cos(qr_{a})+\\ 2\left(1+\ q^{2}r_{a}^{2}\right)^{2}\{qr_{i}\cos(qr_{i})-\sin(qr_{i}))\}-\\ \exp\left(\frac{r_{i}}{r_{a}}-1\right)\left\{ \begin{pmatrix} -2q^{3}r_{a}^{3}+q^{3}r_{a}^{2}r_{i}+q^{5}r_{a}^{4}r_{i}\right)\cos(qr_{i})-\\ \left(-q^{2}r_{a}^{2}+q^{4}r_{a}^{4}+q^{4}r_{a}^{3}r_{i}+q^{2}r_{a}r_{i}\right)\sin(qr_{i}) \right\} \end{bmatrix}$$
(2)

www.SID.ir

#### Theory

There is a correlation between  $\eta$  and  $\gamma$ . Egry et al. examined this correlation [17,18] and derived the formula for the surface tension of a fluid, approximating the smooth density profile by a step function and replacing the gas by vacuum:

$$\gamma = \frac{\pi \rho^2}{8} \int_{0}^{\infty} r^4 \frac{du(r)}{dr} g(r) dr$$
(3)

where g(r) is the pair distribution function and u(r) is the effective pair potential. These pair potential is commonly evaluated by treating the electron-ion coupling through the use of the pseudopotential concept and of linear screening theory. The usual form for the effective ion-ion interaction potential u(r) in pure liquid metal is given by the following:

$$u(r) = \left(\frac{z^2 e^2}{r}\right) + \frac{\Omega}{\pi^2} \int F(q) \left[\frac{\sin(qr)}{qr}\right] q^2 \,\mathrm{d}q \tag{4}$$

where F(q) is the energy wave number characteristic in Equation 4 which is written as follows:

$$F(q) = \frac{-\Omega q^2}{16 \pi} |W(q)|^2 \frac{\varepsilon_H(q) - 1}{1 + [\varepsilon_H(q) - 1][1 - f(q)]}$$
(5)

Here, W(q) is the bare ion potential,  $\varepsilon_H(q)$  is the Hartree dielectric, and f(q) is the local-field correction function to introduce the exchange and correlation effects. Born and Green [47] derived an expression for the viscosity of a fluid using the kinetic theory:

$$\eta = \frac{2\pi\rho^2}{15} \left(\frac{m}{k_B T}\right)^{\frac{1}{2}} \int_{0}^{\infty} r^4 \frac{du}{dr} g(r) dr \tag{6}$$

Using the Stokes-Einstein relation [48-50], the following is obtained:

$$\eta = \frac{k_B T}{2\pi\sigma D} \tag{7}$$

#### **Results and discussion**

The input parameter and constants used for the present study for simple liquid metals are tabulated in Table 1. The viscosity ( $\eta$ ) of liquid metals near melting point (Li, Na, K, Rb, Cs, Mg, Al, Pb and Bi) is shown in Table 2. From Table 2, it is noticeable that the different forms of exchange and correlation functions do not have much sensible effects on the numerical values of  $\eta$ . The present results for  $\eta$  are far better than the others available in the theoretical data [22], except for liquids Li and Cs. An excellent agreement between the present results and experimental data [48,51] has been achieved due to the Hartree [39] local-field correction function for K, Pb, and Bi. The local-field correction function for Na and Mg is due to Sarkar et al. [43], whereas for Rb and Al, it is due to Ichimaru and Utsumi [44].

Table 3 shows that the present results are quite in good agreement with those of experimental data [22] for simple liquid metals. It could also be noticed that the local-field correction function does not affect the numerical values of y. An excellent agreement has been found between the present results and those of the experimental data [48], which have been achieved due to Hartree [39]; for K, Cs, Mg, and Bi, they have been achieved due to local-field correction functions of Sarkar et al. [43], Hartree [39], Hartree [39], and Hubbard [41] and Sham [42], respectively, while for Na and Al, they have been achieved due to local-field correction functions of Sarkar et al. [43] and Hartree [39], which are reasonably in good agreement with those of experimental data [48]. There are results that do not agree well with those of experimental data [41], and they have been found for liquids Li, Rb, and Bi. Table 4 shows the calculated self-diffusion coefficient (D) of simple liquid

Table 4 Calculated self-diffusion coefficient (D) (m<sup>2</sup>/s) for simple liquid metals

Metal	Calculated $D$ (m <sup>2</sup> /s × 10 <sup>-9</sup> )									
	H [39]	VS [40]	HS [41,42]	S [43]	IU [44]	T [45]	F [46]	Others [22]	Experiments [48,51]	
Li	9.00	9.69	9.59	9.81	9.66	9.32	9.81	7.33	6.80	
Na	3.30	3.61	3.58	3.67	3.62	3.45	3.67	6.80, 6.40	4.23, 4.30, 4.19	
К	3.41	3.68	3.67	3.77	3.71	3.55	3.76	6.60, 6.10	3.76, 3.70, 4.01	
Rb	2.08	2.20	2.20	2.26	2.22	2.14	2.25	2.79	2.68	
Cs	2.72	2.97	2.93	3.05	2.97	2.82	3.05	2.37	2.31	
Mg	6.32	5.78	5.80	5.75	5.76	5.99	5.75	5.87	5.63	
Al	5.83	5.94	5.91	5.94	5.92	5.88	5.94	5.00	4.87	
Pb	1.69	1.78	1.59	1.90	1.62	2.00	1.91	1.72	1.68	
Bi	1.33	1.48	1.42	1.48	1.43	1.38	1.48	1.72	-	

www.SID.ir

metals. From Table 4, it is clear that the different forms of exchange and correlation functions do not have much sensible effects on the numerical values of *D*. The present results are quite in good agreement with other available theoretical data results [22], except for liquid Li. A good agreement has been found between the present results and those of experimental data [22,48,49] for Na, K, and Mg due to the local-field correction function of Farid et al. [46], while for liquid Pb, it is due to Hartree [39]. The present results are in poor agreement with those of liquids Li and Al.

In general, it is found in Tables 2, 3, and 4 that the overall present results match very well with the results of other theoretical data [22] as well as other experimental data [48,51] of simple liquid metals, except for Li and Rb. It could also be noticed that the local-field correction functions do not greatly affect the numerical values of atomic transport and surface properties. However, significantly better results could be obtained by the use of other local-field correction functions.

#### Conclusions

Good qualitative and quantitative data of atomic transport and surface properties of some liquid metals near melting point have been obtained; they would be beneficial to other theoreticians as well as experimentalists working in the same field. The present obtained results using our newly constructed parameter free model potential [31,33-37] seem to yield better results than those results obtained by other theoreticians [22]. The structure factor S(q) due to the OCP reference system [29-31] is key in the explanation of atomic transport and surface properties of simple liquid metals near melting point. This shows that sensitivity is required in choosing the reference system and local-field correction function to calculate  $\gamma$ , D, and  $\eta$  of liquid metals. Thus, the application of our newly constructed model potential [31,33-37] in the present study definitely adds a new contribution to understand the atomic transport and surface properties of simple metals in liquid state near melting point.

#### Competing interests

The authors declare that they have no competing interests.

#### Authors' contributions

The three authors, YAS, PBT, and ARJ, contributed equally in all steps of the present paper. All authors read and approved the final manuscript.

#### Authors' information

YAS obtained his PhD in Physics from Veer Narmad South Gujarat University, Surat, Gujarat, India in 2011. Since April 2012, he has been working as assistant professor at SV National Institute of Technology, Surat, Gujarat, 395007, India. He is working in the field of theoretical condensed matter physics. During his research career, he was involved with studying theoretically various physical properties such as thermodynamical, structural, transport, and vibrational properties of liquid metals as well as its alloys and non-crystalline material. PBT obtained his PhD in Physics from Sardar Patel University, Vidhyanagar, Anand, Gujarat, India in 2004. Since 2006, he has been working as associate professor at the Department of Physics, Veer Narmad South Gujarat University, Surat, India. His trusted area of expertise is theoretical condensed matter physics. He is involved in the field of studying physical properties like thermodynamical, structural, transport, surface, magnetic, vibrational properties of liquid metals as well as its alloys and amorphous material using pseudopotential approach. ARJ obtained his PhD in Physics from Gujarat University, Ahmedabad, Gujarat, India in 1979. He did his postdoctoral research at Louisiana State University, USA in 1987. Presently he is working as a professor at the Department of Physics, Sardar Patel University, Vidhyanagar, Anand, Gujarat, India. He is working in the field of experimental and theoretical condensed matter physics.

#### Acknowledgments

The authors (PB Thakor and YA Sonvane) acknowledge the financial support from the University Grants Commission, New Delhi under a Major Research Project (F. no. 33-26/2007 (SR)).

#### Author details

<sup>1</sup>Department of Applied Physics, S. V. National Institute of Technology, Surat, Gujarat 395 007, India. <sup>2</sup>Department of Physics, Veer Narmad South Gujarat University, Surat, Gujarat 395 007, India. <sup>3</sup>Department of Physics, Sardar Patel University, Vallabh Vidyanagar, Gujarat 388 120, India.

#### Received: 18 July 2012 Accepted: 6 November 2012 Published: 4 December 2012

#### References

- Li, GX, Liu, CS, Zhu, ZG: Scaling law for diffusion coefficients in simple melts. Phys. Rev B 71, 094209 (2005)
- Li, GX, Liu, CS, Zhu, ZG: Excess entropy scaling for transport coefficients: diffusion and viscosity in liquid metals. J Non-Cryst Solids 351, 946 (2005)
- Li, GX, Liu, CS, Zhu, ZG: Universal scaling law for atomic diffusion and viscosity in liquid metals. Chin Phys Lett 21, 2489 (2004)
- Korkmaz, SD, Korkmaz, S: Investigation of atomic transport and surface properties of liquid transition metals using scaling laws. J. Mole. Liq 150, 81 (2009)
- Korkmaz, S, Yazar, UUN, Korkmaz, SD: A comparative study of the atomic transport properties of liquid alkaline metals using scaling laws. Fluid Phase Equilib 249, 159 (2006)
- Korkmaz, SD, Korkmaz, Ş: Atomic transport properties of liquid alkaline earth metals: a comparison of scaling laws proposed for diffusion and viscosity. Model Simul Mater Sci Eng 15, 285 (2007)
- Yokoyama, I: A relationship between structural, thermodynamic, transport and surface properties of liquid metals: a hard-sphere description. Physica B 291, 145–151 (2000)
- Dzugutov, M: A universal scaling law for atomic diffusion in condensed matter. Nature 381, 137–139 (1996)
- Hoyt, JJ, Asta, M, Sadigh, B: Test of the universal scaling law for the diffusion coefficient in liquid metals. Phys. Rev. Lett 85, 594–597 (2000)
- Korkmaz, SD, Korkmaz, S: Investigation of surface properties of liquid transition metals: surface tension and surface entropy. App. Sur. Sci 257, 261 (2010)
- 11. Fowler, RH: A tentative statistical theory of Macleod's equation for surface tension and the parachor. Proc. Roy. Soc. A **159**, 229 (1937)
- 12. Kirkwood, JG, Buff, FP: The statistical mechanical theory of surface tension. J. Chem. Phys. 17, 338 (1949)
- 13. Lang, ND, Khon, W: Theory of metal surfaces: charge density and surface energy. Phys. Rev. B 1, 4555 (1970)
- Evans, R: A pseudo-atom theory for the surface tension of liquid metals. J. Phys. C. Solid State Phys 7, 2808 (1974)
- Zykova-Timan, T, Ceresoli, D, Tartaglino, U, Tossati, E: Why are alkali halide surfaces not wetted by their own melt? Phys. Rev. Lett. 94, 176105 (2005)
- 16. Gosh, RC, Ahmed, AZZ, Bhuiyana, GM: Investigation of surface entropy for liquid less simple metals. Eur. Phys. J. B. **56**, 177 (2007)

- 17. Egry, I: On the relation between surface tension and viscosity for liquid metals. Scr. Metall. Mater. 28, 1273 (1993)
- 18. Egry, I, Lohofer, G, Sauerland, S: Surface tension and viscosity of liquid metals. J. Non-Cryst. Solids. **156**, 830 (1993)
- 19. Blairs, S: Correlation between surface tension, density and sound velocity of liquid metals. J. Coll. Inter. Sci. **302**, 312 (2006)
- Belashchenko, DK, Kravchunovskaya, NE, Ostrovski, O: Molecular dynamics calculation of surface tension of liquid metals using the embedded atom model. Calphad 34, 45 (2010)
- Brillo, J, Egry, I: Surface tension of nickel, copper, iron and their binary alloys. J. Mat. Sci 40, 2213 (2005)
- 22. Yokoyama, I: Self-diffusion coefficient and its relation to properties of liquid metals: a hard-sphere description. Physica B **271**, 230 (1999)
- Yao, WJ, Han, XJ, Chen, M, Wei, B, Guo, ZY: Surface tension of undercooled liquid cobalt. J Phys Condens Matter 14, 7479 (2002)
- 24. Schmitz, J, Brillo, J, Egry, I: Surface tension of liquid Cu and anisotropy of its wetting of sapphire. J Mater Sci **45**, 2144 (2010)
- Lu, HM, Li, G, Zhu, YF, Jiang, Q: Temperature dependence of self-diffusion coefficient in several liquid metals. J Non-Cryst Solids 352, 2797 (2006)
- Gaskel, T: Self-diffusion in liquid metals: a generalized Stokes-Einstein equation. J Non-Cryst Solids 61, 913 (1984)
- Ahemed, AZZ, Bhuiyan, GM: Application of the EAM potentials to the study of diffusion coefficients of liquid noble and transition metals. Intl. J. Mod. Phys. B 16, 3837 (2002)
- 28. Bretonnet, JL: Excess entropy scaling for the diffusion coefficient in expanded liquid metals. J Chem Phys **120**, 11100 (2004)
- 29. March, NH, Alonso, JA: Some properties of the structure factor S(q) in twodimensional classical liquids near freezing. Phys Chem Liq **48**, 409 (2010)
- Bretonnet, JL, Khanna, KN: One component plasma structure factor of liquid alkali metals. Phys. Let. A 110, 420 (1985)
- 31. Thakor, PB, Sonvane, YA, Jani, AR: Structural properties of some liquid transition metals. Phys Chem Liq **49**, 530 (2011)
- Cohen, ML: Predicting new solids and superconductors. Science 234, 549 (1986)
- 33. Thakor, PB, Sonvane, YA, Jani, AR: Electronic transport properties of some transition liquid metals. Phys Chem Liq **47**, 653 (2009)
- 34. Thakor, PB, Sonvane, YA, Jani, AR: Thermodynamical properties of 3D transition liquid metals. AIP Conf. Proc. **1249**, 157 (2010)
- Thakor, PB, Sonvane, YA, Jani, AR: Shear viscosity coefficient of 5D liquid transition metals. AIP Conf. Proc. 1349, 937 (2011)
- Thakor, PB, Sonvane, YA, Gajjar, PN, Jani, AR: Theoretical investigation of phonon dispersion relation of 3D liquid transition metals. AIP Conf. Proc. 1393, 163 (2011)
- Thakor, PB, Sonvane, YA, Gajjar, PN, Jani, AR: Electronic transport properties of liquid lanthanides. Adv Mater Lett 2, 303 (2011)
- Ashcroft, NW, Lenker, J: Structure and resistivity of liquid metals. Phys Rev 145, 83 (1966)
- 39. Harrison, WA: Elementary electronic structure. World Scientific, Singapore (1999)
- Vashista, P, Singwi, KS: Electron correlations at metallic densities. Phys Rev B6, 875 (1972)
- Hubbard, J: The description of collective motions in terms of many-body perturbation theory II. The correlation energy of a free-electron gas. Proc. Roy. Soc. London A243, 336 (1958)
- 42. Sham, LJ: A calculation of the phonon frequencies in sodium. Proc. Roy. Soc. London A283, 33 (1965)
- Sarkar, A, Sen, D, Haldar, S, Roy, D: Static local field factor for dielectric screening function of electron gas at metallic and lower densities. Mod. Phys. Lett. B12, 639 (1998)
- Ichimaru, S, Utsumi, K: Analytical expression for the dielectric function of strongly coupled electron liquids at metallic and lower density. Phys Rev B24, 7385 (1981)
- Taylor, R: A simple, useful analytical form of the static electron gas dielectric function. J. Phys. F: Metal Phys 8, 1699 (1978)
- Farid, B, Heine, V, Engel, GE, Robertson, IJ: Extremal properties of the Harris-Foulkes functional and an improved screening calculation for the electron gas. Phys Rev B48, 11602 (1993)
- Born, M, Green, HS: A general kinetic theory of liquids III. Dynamical properties. Proc. Roy. Soc. London A 190, 455 (1947)
- 48. Shimoji, M: Liquid Metals. Academic Press, London (1977)

- 49. lida, T, Guthrie, RIL: The Physical Properties of Liquid Metals. Oxford Science Publications, Oxford (1988)
- Shimoji, M, Itami, T: Atomic Transport in Liquid Metals. Trans Tech Publications, Oxford (1986)
- 51. Waseda, Y: The Structure of Non-crystalline Materials. McGraw-Hill, New York (1980)

#### doi:10.1186/2251-7235-6-43

**Cite this article as:** Sonvane *et al.*: **Atomic transport and surface properties of some simple liquid metal using one component plasma system.** *Journal of Theoretical and Applied Physics* 2012 **6**:43.



# Submit your manuscript to a SpringerOpen<sup>®</sup> journal and benefit from:

- Convenient online submission
- Rigorous peer review
- Immediate publication on acceptance
- Open access: articles freely available online
- High visibility within the field
- Retaining the copyright to your article

#### Submit your next manuscript at > springeropen.com