**ORIGINAL RESEARCH** 



# Free vibration analysis of functionally graded doubly curved shell panels resting on elastic foundation in thermal environment

Quoc Huu Tran<sup>1</sup> · Huan Thanh Duong<sup>2</sup> · Tu Minh Tran<sup>1</sup>

Received: 3 May 2017 / Accepted: 22 August 2018 / Published online: 1 September 2018 © The Author(s) 2018

#### Abstract

The purpose of the paper is to develop an analytical investigation on free vibration of a simply supported functionally graded (FG) doubly curved shell panels resting on elastic foundation in thermal environment. Heat conduction and temperaturedependent material properties are both taken into account. The temperature field considered is assumed to be a uniform distribution over the shell surface and varied in the thickness direction only. Material properties are assumed to be temperature dependent and graded in the thickness direction according to a simple power law distribution in terms of the volume fractions of the constituents. Based on the first-order shear deformation theory and applying the Hamilton's principle, governing equations of motion are derived. The results of the study are compared with the available published literature. The numerical results obtained reveal that the material volume fraction index, geometrical parameters and temperature change have significant effects on natural frequencies of the FG doubly curved shell panels.

**Keywords** Functionally graded materials  $\cdot$  Doubly curved shell panels  $\cdot$  Free vibration analysis  $\cdot$  First-order shear deformation  $\cdot$  Elastic foundation  $\cdot$  Thermal environment

#### Introduction

Functionally graded materials (FGMs) have been used in various engineering applications because of their distinctive material properties, which can be altered to satisfy different working environments. Typically, these materials are made from a mixture of ceramic and metal or a combination of different metals. The ceramic constituent provides the hightemperature resistance due to its low thermal conductivity. The ductile metal constituent, on the other hand, prevents fracture caused by stresses due to high-temperature gradient in a very short period of time. Numerous studies on thermomechanical characteristics of FGM structures have been carried out to date.

Static and dynamic analyses of functionally graded shells in thermal environment are well established in the existing literature. Kadoli and Ganesan (2006) presented linear

Quoc Huu Tran thquoc@gmail.com thermal buckling and free vibration analysis for functionally graded cylindrical shells with clamped-clamped boundary condition with temperature-dependent material properties. First-order shear deformation theory along with Fourier series expansion of the displacement variables in the circumferential direction are used to model the FGM shell. Shen and Wang (2010) investigated thermo-elastic vibration and buckling characteristics of the functionally graded piezoelectric cylindrical shell using Maxwell equation with a quadratic variation of the electric potential along the thickness direction of the cylindrical shells and the first-order shear deformation theory. Based on Love's shell theory and the von Karman-Donnell type of kinematic nonlinearity, free vibration analysis of simply supported functional graded cylindrical shells for four sets of in-plane boundary conditions is performed by Haddadpour et al. (2007) using Galerkin's method. The free vibration analysis of rotating functionally graded (FG) cylindrical shells subjected to thermal environment is investigated based on the first-order shear deformation theory of shells and was reported in the work of Malekzadeh and Heydarpour (2012). Pradyumna and Bandyopadhyay (2010) investigated the free vibration and buckling behavior of functionally graded singly and doubly curved shell panels. A higher-order shear deformation theory



<sup>&</sup>lt;sup>1</sup> National University of Civil Engineering, Hai Ba Trung District, Ha Noi, Vietnam

<sup>&</sup>lt;sup>2</sup> Vietnam National University of Agriculture, Gia Lam District, Ha Noi, Vietnam

is used and the shell panels are subjected to a temperature field. Bhangale et al. (2006) used the first-order shear deformation theory to study the thermal buckling and vibration behavior of truncated functionally graded conical shells in a high-temperature environment by finite element method. Temperature-dependent material properties are considered to carry out a linear thermal buckling and free vibration analysis. Zhao et al. (2009) studied static response and free vibration characteristic of metal and ceramic functionally graded shells using the element-free kp-Ritz method. The displacement field is expressed in terms of a set of mesh-free kernel particle functions according to Sander's first-order shear deformation shell theory. Wattanasakulpong and Chaikittiratana (2015) presented an investigation of free vibration of stiffened functionally graded doubly curved shallow shells under thermal environment. Two types of temperature rise throughout the shell thickness: linear temperature rise and nonlinear temperature rise are considered. Alijani et al. (2011) studied geometrically nonlinear vibrations of functionally graded doubly curved shells subjected to thermal variations and harmonic excitation via multi-modal energy approach.

However, studies on thermal vibration analyses of functionally graded doubly curved shell panels resting on elastic foundation are very rare in the existing literature. Thus, in this paper, the vibration analysis of simply supported functionally graded doubly curved shells resting on Winkler–Pasternak elastic foundation including thermal effects is performed. The material properties are assumed to be temperature dependent and graded in the thickness direction according to a simple power law function. A first-order shear deformation theory is used for the analysis of two FG panels, namely, cylindrical, spherical, and as special case of plate.

#### **Theoretical formulation**

Consider a functionally graded doubly curved panel with length *a*, width *b*, and thickness *h*, referred to an orthogonal curvilinear coordinate system (x, y, z), as shown in Fig. 1.  $R_1$  and  $R_2$  are the radii of principal curvatures of the middle surface in the *x*-direction and the *y*-direction, respectively. The elastic material properties vary through the shell thickness according to a simple power law distribution in terms of the volume fractions of the constituents. The top surface (z = h/2) of the shell is assumed to be ceramic rich, whereas the bottom surface (z = -h/2) is assumed to be metal rich. The effective properties of the functionally graded material at any thickness of coordinate *z* can be expressed by the following power law distribution:

$$P(z,T) = \left(P_{\rm c} - P_{\rm m}\right) \left(\frac{z}{h} + \frac{1}{2}\right)^{p} + P_{\rm m},\tag{1}$$



Fig. 1 Coordinate system and geometry of an in-contact doubly curved FGM panel

where *p* is the volume fraction exponent,  $P_{\rm m}$  and  $P_{\rm c}$  represent the properties of the metal and the ceramic, respectively. The properties of the temperature-dependent constituents of an FGM shell can be expressed as (Bhangale et al. 2006):

$$P(T) = P_0 \left( P_{-1} T^{-1} + 1 + P_1 T + P_2 T^2 + P_3 T^3 \right), \tag{2}$$

where  $P_0$ ,  $P_{-1}$ ,  $P_1$ ,  $P_2$  and  $P_3$  are the coefficients of temperature T(K) and are unique to the constituent materials.

In this study, Poisson ratio  $\nu$  is assumed to be constant, Young's modulus E and thermal expansion coefficient  $\alpha$ are assumed to be temperature dependent, whereas the mass density  $\rho$  and thermal conductivity  $\kappa$  are independent of the temperature (Huang and Shen 2004):

$$E(z,T) = E_{\rm m}(T) + \left[E_{\rm c}(T) - E_{\rm m}(T)\right] \left(\frac{z}{h} + \frac{1}{2}\right)^{p};$$
  

$$\kappa(z) = \kappa_{\rm m} + \left(\kappa_{\rm c} - \kappa_{\rm m}\right) \left(\frac{z}{h} + \frac{1}{2}\right)^{p};$$
(3)

$$\begin{aligned} \alpha(z, T) &= \alpha_{\rm m}(T) + \left[\alpha_{\rm c}(T) - \alpha_{\rm m}(T)\right] \left(\frac{z}{h} + \frac{1}{2}\right)^p; \\ \rho(z) &= \rho_{\rm m} + \left(\rho_{\rm c} - \rho_{\rm m}\right) \left(\frac{z}{h} + \frac{1}{2}\right)^p. \end{aligned}$$

It is assumed that temperature variation occurs in the thickness direction only and one-dimensional temperature field is assumed to be constant in the x-y surface of the shell. In such case, the temperature distribution through the thickness of the functionally graded shell can be obtained by solving a steady-state heat transfer equation as follows (Wattanasakulpong and Chaikittiratana 2015):

$$-\frac{\mathrm{d}}{\mathrm{d}z} \left[ \kappa_{\mathrm{f}} \frac{\mathrm{d}T}{\mathrm{d}z} \right] = 0. \tag{4}$$

This equation is solved by imposing boundary conditions of  $T = T_c$  at z = h/2 and  $T = T_m$  at z = -h/2. The



solution of this equation, by means of polynomial series as (Javaheri and Eslami 2002):

$$T(z) = T_{\rm m} + \left(T_{\rm c} - T_{\rm m}\right)\eta(z),\tag{5}$$

with 
$$\eta(z) = \frac{1}{C} \begin{bmatrix} X - \frac{\kappa_{cm}}{(p+1)\kappa_m} X^{p+1} + \frac{\kappa_{cm}^2}{(2p+1)\kappa_m^2} X^{2p+1} \\ -\frac{\kappa_{cm}^2}{(3p+1)\kappa_m^3} X^{3p+1} + \frac{\kappa_{cm}^4}{(4p+1)\kappa_m^4} X^{4p+1} - \frac{\kappa_{cm}^5}{(5p+1)\kappa_m^5} X^{5p+1} \end{bmatrix},$$
(6a)

$$\begin{cases} X = \left(\frac{z}{h} + \frac{1}{2}\right); & \kappa_{\rm cm} = \kappa_{\rm c} - \kappa_{\rm m} \\ C = 1 - \frac{\kappa_{\rm cm}}{(p+1)\kappa_{\rm m}} + \frac{\kappa_{\rm cm}^2}{(2p+1)\kappa_{\rm m}^2} - \frac{\kappa_{\rm cm}^3}{(3p+1)\kappa_{\rm m}^3} + \frac{\kappa_{\rm cm}^4}{(4p+1)\kappa_{\rm m}^4} - \frac{\kappa_{\rm cm}^5}{(5p+1)\kappa_{\rm m}^5}, \end{cases}$$
(6b)

According to the first-order shear deformation shell theory, the displacement field can be expressed as (Wattanasakulpong and Chaikittiratana 2015):

$$u(x, y, z, t) = u_0(x, y, t) + z\phi_x(x, y, t),$$
  

$$v(x, y, z, t) = v_0(x, y, t) + z\phi_y(x, y, t),$$
  

$$w(x, y, z, t) = w_0(x, y, t).$$
(7)

where  $u_0$ ,  $v_0$  and  $w_0$  are the displacement at the mid-surface of the shell in the x, y and z directions, respectively; and  $\phi_x$ and  $\phi_{y}$  are the rotations of the transverse normal about the y and x axes, respectively.

The linear strains are defined as:

$$\begin{cases} \varepsilon_{x} \\ \varepsilon_{y} \\ \gamma_{xy} \end{cases} = \begin{cases} \varepsilon_{x}^{0} \\ \varepsilon_{y}^{0} \\ \gamma_{xy}^{0} \end{cases} + z \begin{cases} \kappa_{x} \\ \kappa_{y} \\ \kappa_{xy} \end{cases}; \\ \begin{cases} \gamma_{yz} \\ \gamma_{xz} \end{cases} = \begin{cases} \gamma_{yz}^{0} \\ \gamma_{xz}^{0} \end{cases} = \begin{cases} \phi_{y} + \frac{\partial w_{0}}{\partial y} - \frac{w_{0}}{R_{2}} \\ \phi_{x} + \frac{\partial w_{0}}{\partial x} - \frac{w_{0}}{R_{1}} \end{cases},$$
(8)

where

$$\epsilon_x^0 = \frac{\partial u_0}{\partial x} + \frac{w_0}{R_1}; \ \epsilon_y^0 = \frac{\partial v_0}{\partial y} + \frac{w_0}{R_2}; \ \gamma_{xy}^0 = \frac{\partial u_0}{\partial y} + \frac{\partial v_0}{\partial x},$$
  

$$\kappa_x = \frac{\partial \phi_x}{\partial x}; \ \kappa_y = \frac{\partial \phi_y}{\partial y}; \ \kappa_{xy} = \frac{\partial \phi_x}{\partial y} + \frac{\partial \phi_y}{\partial x}.$$
(9)

Then, the linear constitutive relations are expressed as,

$$\begin{cases} \sigma_{xx} \\ \sigma_{yy} \\ \sigma_{xy} \\ \sigma_{yz} \\ \sigma_{xz} \end{cases} = \begin{bmatrix} Q_{11} \ Q_{12} \ 0 \ 0 \ 0 \\ Q_{12} \ Q_{22} \ 0 \ 0 \ 0 \\ 0 \ 0 \ Q_{66} \ 0 \ 0 \\ 0 \ 0 \ 0 \ Q_{44} \ 0 \\ 0 \ 0 \ 0 \ Q_{55} \end{bmatrix} \begin{cases} \varepsilon_x \\ \varepsilon_y \\ \gamma_{xy} \\ \gamma_{xz} \\ \gamma_{xz} \end{cases},$$
(10)

where

$$Q_{11} = Q_{22} = \frac{E(z,T)}{1-v^2}; \quad Q_{12} = \frac{vE(z,T)}{1-v^2};$$

$$Q_{44} = Q_{55} = Q_{66} = \frac{E(z,T)}{2(1+v)}.$$
(11)

The force and moment resultants and are defined by:

$$\begin{cases} N_{xx} \\ N_{yy} \\ N_{xy} \end{cases} = \int_{-h/2}^{h/2} \begin{cases} \sigma_{xx} \\ \sigma_{yy} \\ \tau_{xy} \end{cases} dz; \quad \begin{cases} M_{xx} \\ M_{yy} \\ M_{xy} \end{cases} = \int_{-h/2}^{h/2} \begin{cases} z\sigma_{xx} \\ z\sigma_{yy} \\ z\tau_{xy} \end{cases} dz;$$

$$\begin{cases} Q_{yz} \\ Q_{xz} \end{cases} = k_s \int_{-h/2}^{h/2} \begin{cases} \sigma_{yz} \\ \sigma_{xz} \end{cases} dz,$$

$$(12)$$

$$\begin{cases} N_{xx} \\ N_{yy} \\ N_{xy} \\ M_{xy} \\ \end{pmatrix} = \begin{bmatrix} A_{11} A_{12} & 0 & B_{11} B_{12} & 0 \\ A_{12} A_{22} & 0 & B_{12} B_{22} & 0 \\ 0 & 0 & A_{66} & 0 & 0 & B_{66} \\ B_{11} B_{12} & 0 & D_{11} D_{12} & 0 \\ B_{12} B_{22} & 0 & D_{12} D_{22} & 0 \\ 0 & 0 & B_{66} & 0 & 0 & D_{66} \end{bmatrix} \begin{cases} \varepsilon_{x}^{0} \\ \varepsilon_{y}^{0} \\ \gamma_{xy}^{0} \\ \kappa_{x} \\ \kappa_{y} \\ \kappa_{xy} \\ \kappa_{xy} \\ \end{pmatrix};$$

$$\begin{cases} Q_{yz} \\ Q_{xz} \\ Q_{xz} \\ Q_{xz} \\ \end{pmatrix} = k_{s} \begin{bmatrix} A_{44} & 0 \\ 0 & A_{55} \end{bmatrix} \begin{cases} \gamma_{yz}^{0} \\ \gamma_{xz}^{0} \\ \gamma_{xz}^{0} \\ \end{pmatrix},$$
where

v

$$(A_{ij}, B_{ij}, D_{ij}) = \int_{-h/2}^{h/2} Q_{ij}(1, z, z^2) dz \quad \text{with } (ij) = (11, 12, 21, 22, 66),$$
(13)

and,

$$A_{ij} = \int_{-h/2}^{h/2} Q_{ij} dz \quad \text{with } (ij) = (44, 55),$$

and  $k_s$  is shear correction coefficient ( $k_s = 5/6$ ). The temperature is assumed to only vary along the thickness direction of the shell; thus,  $\tau_{_{XY}} = 0$ . The thermal stresses for the functionally graded shell in the x, y directions are expressed as follows:

$$\sigma_{xx}^{(T)} = \sigma_{yy}^{(T)} = -\frac{E(z, T)\alpha(z, T)}{1 - \nu}\Delta T,$$
(14)

where  $\Delta T = T(z) - T_0$  is temperature rise from the reference temperature  $T_0$  at which there are no thermal strain.

Using the Hamilton's principle, we can obtain the equations of motion as (Wattanasakulpong and Chaikittiratana 2015):



$$\frac{\partial N_{xx}}{\partial x} + \frac{\partial N_{xy}}{\partial y} + \frac{Q_{xz}}{R_{1}} = A_{11}^{T} \frac{\partial^{2} u_{0}}{\partial x^{2}} + A_{22}^{T} \frac{\partial^{2} u_{0}}{\partial y^{2}} + B_{11}^{T} \frac{\partial^{2} \phi_{x}}{\partial x^{2}} + B_{22}^{T} \frac{\partial^{2} \psi_{x}}{\partial y^{2}} + I_{0} \frac{\partial^{2} u_{0}}{\partial t^{2}} + I_{1} \frac{\partial^{2} \phi_{x}}{\partial t^{2}},$$

$$\frac{\partial N_{xy}}{\partial x} + \frac{\partial N_{yy}}{\partial y} + \frac{Q_{yz}}{R_{2}} = A_{11}^{T} \frac{\partial^{2} v_{0}}{\partial x^{2}} + A_{22}^{T} \frac{\partial^{2} v_{0}}{\partial y^{2}} + B_{11}^{T} \frac{\partial^{2} \phi_{y}}{\partial x^{2}} + B_{22}^{T} \frac{\partial^{2} w_{0}}{\partial y^{2}} + I_{0} \frac{\partial^{2} v_{0}}{\partial t^{2}} + I_{1} \frac{\partial^{2} \phi_{y}}{\partial t^{2}},$$

$$\frac{\partial Q_{xz}}{\partial x} + \frac{\partial Q_{yz}}{\partial y} - \frac{N_{xx}}{R_{1}} - \frac{N_{yy}}{R_{2}} + K_{g} \nabla^{2} w_{0} - K_{w} w_{0} = A_{11}^{T} \frac{\partial^{2} w_{0}}{\partial x^{2}} + A_{22}^{T} \frac{\partial^{2} w_{0}}{\partial y^{2}} + I_{0} \frac{\partial^{2} w_{0}}{\partial t^{2}},$$

$$\frac{\partial M_{xx}}{\partial x} + \frac{\partial M_{yy}}{\partial y} - Q_{xz} = B_{11}^{T} \frac{\partial^{2} u_{0}}{\partial x^{2}} + B_{22}^{T} \frac{\partial^{2} u_{0}}{\partial y^{2}} + D_{11}^{T} \frac{\partial^{2} \phi_{x}}{\partial x^{2}} + D_{22}^{T} \frac{\partial^{2} \phi_{y}}{\partial y^{2}} + I_{0} \frac{\partial^{2} w_{0}}{\partial t^{2}},$$

$$\frac{\partial M_{xy}}{\partial x} + \frac{\partial M_{yy}}{\partial y} - Q_{yz} = B_{11}^{T} \frac{\partial^{2} v_{0}}{\partial x^{2}} + B_{22}^{T} \frac{\partial^{2} v_{0}}{\partial y^{2}} + D_{11}^{T} \frac{\partial^{2} \phi_{y}}{\partial x^{2}} + D_{22}^{T} \frac{\partial^{2} \phi_{y}}{\partial y^{2}} + I_{0} \frac{\partial^{2} w_{0}}{\partial t^{2}} + I_{2} \frac{\partial^{2} \phi_{x}}{\partial t^{2}},$$

$$(15)$$

where

$$\begin{pmatrix} A_{11}^{T}, B_{11}^{T}, D_{11}^{T} \end{pmatrix} = \int_{-h/2}^{h/2} \sigma_{xx}^{(T)}(1, z, z^{2}) dz, A_{22}^{T} = A_{11}^{T}; B_{22}^{T} = B_{11}^{T}; D_{22}^{T} = D_{11}^{T}, I_{i} = \int_{h/2}^{h/2} \rho(z) \cdot z^{i} dz \quad i = (0, 1, 2), \nabla^{2} = \frac{\partial^{2}}{\partial x^{2}} + \frac{\partial^{2}}{\partial y^{2}},$$
 (16)

#### **Solution procedures**

~

Based on the Navier's approach, the displacement unknowns satisfying the simply supported boundary conditions for the FG doubly curved shell are assumed in the following forms:

$$\begin{cases} u_0(x, y, t) \\ v_0(x, y, t) \\ w_0(x, y, t) \\ \phi_x(x, y, t) \\ \phi_y(x, y, t) \end{cases} = \sum_{m=1}^{\infty} \sum_{n=1}^{\infty} \begin{cases} u_{mn} e^{i\omega t} \cos(\alpha x) \sin(\beta y) \\ v_{mn} e^{i\omega t} \sin(\alpha x) \cos(\beta y) \\ w_{mn} e^{i\omega t} \sin(\alpha x) \sin(\beta y) \\ \phi_{xmn} e^{i\omega t} \cos(\alpha x) \sin(\beta y) \\ \phi_{ymn} e^{i\omega t} \sin(\alpha x) \cos(\beta y) \end{cases}, \quad (17)$$

and  $K_w$  is the Winkler's elastic foundation coefficient and  $K_g$  is a constant showing the effect of the shear interaction of vertical elements.

The internal moment and force resultants are expressed in displacement terms using Eqs. (7)–(13) and then substituting into Eq. (15), we get the equations of motion expressed to the displacement components  $(u_0, v_0, w_0, \phi_x, \phi_y)$ .

where  $u_{mn}$ ,  $v_{mn}$ ,  $w_{mn}$ ,  $\phi_{xmn}$ ,  $\phi_{ymn}$  are the coefficients; *i* is the imaginary unit ( $i^2 = -1$ );  $\omega$  is the natural frequency;  $\alpha = m\pi/a$ ;  $\beta = n\pi/b$ .

The final form of equations of motion can be obtained by substituting Eq. (17) in the equations of motion expressed to the displacement components of Eq. (15) and conceded as.

$$([K]_{5\times 5} - \omega^2 [M]_{5\times 5}) \{\Delta\}_{5\times 1} = \{0\}_{5\times 1},$$
(18)

where  $[K]_{5\times 5}$  and  $[M]_{5\times 5}$  are the stiffness matrix and the mass matrix, respectively. With  $K_{ij}$ ,  $M_{ij}$  are the elements which can be obtained by Symbolic Toolbox of the MATLAB

Table 1	Temperature-dependent
coefficie	nts of the FGM shell
panel	

Material	Properties	$P_0$	P_1	$P_1$	<i>P</i> <sub>2</sub>	<i>P</i> <sub>3</sub>
Si <sub>3</sub> N <sub>4</sub>	$E_{\rm c}$ (Pa)	3.4843E+11	0	-3.07E+04	2.16E+07	-8.946E-11
	$\alpha_{\rm c} (1/{\rm K})$	5.8723E-06	0	9.095E-04	0	0
	$K_{\rm c}$ (W/m K)	13.723	0	-1.032E-03	5.466E-07	-7.876E-11
	$ u_{\rm c}$	0.24	0	0	0	0
	$\rho_{\rm c}({\rm kg/m^3})$	2370	0	0	0	0
SUS304	$E_{\rm m}$ (Pa)	2.0104E+11	0	3.079E-04	-6.53E-07	0
	$\alpha_{\rm m}$ (1/K)	1.233E-05	0	8.086E-04	0	0
	$K_{\rm m}$ (W/m K)	15.379	0	-1.264E-03	2.09E-06	-7.223E-10
	$\nu_{ m m}$	0.3262	0	-2.002E-04	3.797E-07	0
	$\rho_{\rm m}  ({\rm kg/m^3})$	8166	0	0	0	0



software.  $\{\Delta\}_{5\times 1} = \{u_{mn} v_{mn} w_{mn} \phi_{xmn} \phi_{ymn}\}^T$  is the displacement vector.

The natural frequency  $\omega_{mn}$  can be obtained by solving the above eigenvalue-type equation (Eq. 18). With each pair of *m* and *n*, there is a corresponding unique mode shape of the natural frequency for the FG doubly curved shell panel.

#### **Results and discussion**

#### Validation study

To verify the accuracy of the presented solutions, two examples have been analyzed for free vibration of the simply supported FG shell panels and the values of the fundamental frequencies are compared with those in existing literature. It is noted that the doubly curved shell panels can be flexible and degenerated into the different structures by setting these quantities:

- \$\frac{a}{R\_1} = \frac{b}{R\_2} = 0\$ for the plate structures;
   \$\frac{a}{R\_1} = 0\$ for the cylindrical panel; \$\frac{a}{R\_1} = \frac{b}{R\_2}\$ for the spherical panel.

**Table 2** Comparison of non-dimensional frequencies  $\Omega_1$  for FG square doubly curved shells resting on elastic foundation (under ambient temperature)

$(K_0, J_0)$	$(a/R_1, a/R_2)$	Sources	Difference (%)	
		Kiani et al. (2012)	Present	
(0, 0)	(0.2, 0.2)	5.1783	5.1783	0.00
	(0.2, 0)	4.9551	4.9568	0.03
	(0, 0)	4.8985	4.8985	0.00
(100, 0)	(0.2, 0.2)	5.3517	5.3517	0.00
	(0.2, 0)	5.1365	5.1381	0.03
	(0, 0)	5.0826	5.0826	0.00
(100, 10)	(0.2, 0.2)	5.6787	5.6787	0.00
	(0.2, 0)	5.4768	5.4783	0.03
	(0, 0)	5.4278	5.4278	0.00
(500, 0)	(0.2, 0.2)	5.9957	5.9957	0.00
	(0.2, 0)	5.8053	5.8068	0.03
	(0, 0)	5.7606	5.7606	0.00
(500, 10)	(0.2, 0.2)	6.2892	6.2892	0.00
	(0.2, 0)	6.1085	6.1099	0.02
	(0, 0)	6.0673	6.0673	0.00
(500, 50)	(0.2, 0.2)	7.3468	7.3468	0.00
	(0.2, 0)	7.1943	7.1955	0.02
	(0, 0)	7.164	7.1640	0.00

Values in bold are results by the authors, and values in italic are the differences between the authors' results and the reference results

According to Reddy and Chin (1998), the effective material properties used in the present study are listed in Table 1.

Example 1 We first consider the FG doubly curved shell panels resting on elastic foundation under ambient temperature with geometrical parameters: a/b = 1, a/h = 10, power law index p = 0.5 and various curvatures  $(a/R_1, b/R_2)$ 

The non-dimensional natural frequencies for two types of curved panel (spherical panel and cylindrical panel) and the associated plate are calculated for various values of foundation parameters and displayed in Table 2. A comparison is made by comparing with those given by Kiani et al. (2012). The non-dimensional frequency parameter is defined as:  $\Omega_1 = \frac{a^2}{h} \cdot \omega \cdot \sqrt{\rho_c/E_c}$ . According to Kiani et al. (2012), the non-dimensional Winkler and Pasternak coefficients are  $K_0 = \frac{K_w \cdot a^4}{D_m}$ ;  $J_0 = \frac{K_g \cdot b^2}{D_m}$  with  $(D_{\rm m} = E_{\rm m} h^3 / 12 / (1 - v^2))$ . The material properties of ceramic and metal are as follows:

- Ceramic (Al<sub>2</sub>O<sub>3</sub>):  $E_c = 380$  GPa;  $\rho_c = 3800$  kg/m<sup>3</sup>;  $\nu =$
- Metal (Al):  $E_{\rm m} = 70$  GPa;  $\rho_{\rm m} = 2707$  kg/m<sup>3</sup>;  $\nu = 0.3$ .

As shown in Table 2, a good agreement between the results is accomplished.

**Example 2** In this example, the vibration analysis of FG plates  $(a/R_1 = b/R_2 = 0)$  in the thermal environment not resting on elastic foundation ( $K_0 = J_0 = 0$ ) is investigated.

The FG plate is made of SUS304 and Si<sub>3</sub>N<sub>4</sub> and the material properties are assumed to be dependent of temperature as listed in Table 1. Geometrical parameters of the plate are: h = 0.025 (m); a = b = 0.2 (m); a/h = 8. The non-dimensional frequency parameter is used in the form:  $\Omega_2 = \frac{a^2}{h} \cdot \omega \cdot \sqrt{\rho_{0m} (1 - v^2) / E_{0m}}$  with  $E_{0m}$  and  $\rho_{0m}$  as the reference values of  $E_{\rm m}$  and  $\rho_{\rm m}$  at  $T_0 = 300$  K. Table 3 shows the calculated non-dimensional frequencies parameters in a comparison with those given by Shen and Wang (2012) using higher-order shear deformation plate theory. It can be seen clearly that the results obtained are in very good agreement. The biggest difference are 1.18% for  $T_c = 600$  K,  $T_m$ = 600 K, mode (2, 2) and p = 1 and 1.17% for  $T_c = 400$  K,  $T_{\rm m} = 300$  K, mode (2, 2) and p = 0.5.

These two comparisons show that the presented results match very well with the established ones. It can be seen that the maximum difference of the fundamental frequency between present solution and Shen and Wang's solution is only about 1.20% at  $T_c = T_m = 600$  K and p = 1, mode (2, 2).



Temperature	Р	Sources	Mode (1, 1)	Mode (1, 2)	Mode (2, 2)
$T_{\rm c} = 600 \text{ K}; T_{\rm m} = 600 \text{ K}$	0	Shen and Wang (Shen and Wang 2012)	12.079	28.381	43.016
		Present	12.159	28.437	42.977
		Difference (%)	0.66	0.20	0.09
	1	Shen and Wang (Shen and Wang 2012)	7.337	17.203	26.043
		Present	7.287	17.033	25.734
		Difference (%)	0.69	1.00	1.20
	2	Shen and Wang (Shen and Wang 2012)	6.584	15.397	23.259
		Present	6.532	15.261	23.045
		Difference (%)	0.80	0.89	0.93
	10	Shen and Wang (Shen and Wang 2012)	5.698	13.279	20.000
	10	Present	5.643	13.174	19.882
		Difference (%)	0.97	0.79	0.59
$T_{\rm c} = 400 \text{ K}; T_{\rm m} = 300 \text{ K}$ (tem-	0	Shen and Wang (Shen and Wang 2012)	12.424	29.192	44.245
perature dependence)	0	Present	12.440	29.096	43.974
		Difference (%)	0.13	0.33	0.62
	1	Shen and Wang (Shen and Wang 2012)	7.556	17.726	26.842
		Present	7.520	17.567	26.537
		Difference (%)	0.48	0.91	1.15
	2	Shen and Wang (Shen and Wang 2012)	6.785	15.877	23.994
		Present	6.754	15.77	23.811
		Difference (%)	0.46	0.68	0.77
	10	Shen and Wang (Shen and Wang 2012)	5.878	13.708	20.66
		Present	5.846	13.649	20.602
		Difference (%)	0.54	0.43	0.28

 Table 3
 Comparison of non-dimensional frequencies for the FG plates under thermal environment

Values in bold are results by the authors, and values in italic are the differences between the authors' results and the reference results



Fig.2 Variation of the non-dimensional fundamental frequency of the FG panel with the temperature  $(T_c)$ 

#### **Parametric study**

Next, the following parametric studies are carried out to analyze the free vibration of FG doubly curved shell panels in the case of resting on elastic foundation ( $K_0 = 100$ and  $J_0 = 10$ ) or without contacting with elastic foundation ( $K_0 = J_0 = 0$ ) in thermal environment. The FG material type used is SUS304/Si<sub>3</sub>N<sub>4</sub> in the following investigation with the material properties as in the Table 1. The non-dimensional frequency parameter is defined as  $\Omega_3 = 100 \cdot \omega \cdot h \cdot \sqrt{\rho_{0c}/E_{0c}}$  with  $E_{0c}$  and  $\rho_{0c}$  as the reference values of  $E_c$  and  $\rho_c$  at  $T_0 = 300$  K. The geometrical parameters of the shell panels are: a/b = 1; a/h = 20; for spherical shell ( $a/R_1 = b/R_2 = 0.5$ ) and for cylindrical shell ( $a/R_1 = 0$ ;  $b/R_2 = 0.5$ ). The temperature at the metal-rich surface is  $T_m = 300$  K and the temperature at the ceramicrich surface is  $T_c$ .

For illustration purpose, on the plot graph, the nondimensional frequencies of shell panels resting on elastic foundation are depicted by solid lines whereas the dash lines are for the case of shell panels not resting on elastic foundation.





**Fig. 3** Variation of the non-dimensional fundamental frequency of the FG panel with the power law index (p)



Fig. 4 Variation of the non-dimensional fundamental frequency of the FG panel with *a/h* ratio

## Effect of the temperature on the fundamental natural frequency

The temperature variation refers to the case when the metal temperature is kept constant while the ceramic surface is heated; so there is a temperature difference  $\Delta T$  between the top and bottom shell surfaces. The variation of the non-dimensional fundamental frequencies of the spherical and cylindrical FG shell panels (p = 1) versus the temperature is shown in Fig. 2. It is observed that the trend of the non-dimensional fundamental frequency changes of the cylindrical panel and spherical panel are the same. The non-dimensional fundamental frequencies decrease when the temperature of the ceramic



**Fig. 5** Variation of the non-dimensional fundamental frequency of the FG panel with  $b/R_2$  ratio

**Table 4** Variation of the non-dimensional fundamental frequency of the FG panel with various foundation parameters ( $K_0$  and  $J_0$ )

The non-dimensional fundamental frequency $\varOmega_3$							
$\overline{J_0}$	K_0						
	0	100	300	500			
0	1.7176	1.7632	1.8509	1.9347			
100	2.4657	2.4976	2.5602	2.6214			
300	3.5112	3.5337	3.5781	3.6220			
500	4.3086	4.3269	4.3632	4.3992			

surface  $(T_c)$  increases. The reduction of the non-dimensional fundamental frequencies is due to the decreasing of panel's stiffness when the temperature increases. The non-dimensional fundamental frequency of FG shell panels with the elastic foundation is higher than that without elastic foundation.

#### Effect of the power law index on the fundamental frequency

Figure 3 shows the effect of the power law index (p) on non-dimensional fundamental frequencies of cylindrical and spherical panels. The temperatures are  $T_{\rm m} = 300$  K,  $T_{\rm c} = 400$  K. It can be seen that the non-dimensional natural frequency decreases with increasing value of power law index (p). It is basically due to the fact that Young's modulus of ceramic is higher than metal. Figure 3 also shows that the non-dimensional natural frequency decreases significantly when p is small.





**Fig. 6** Effect of foundation parameters  $K_0$  and  $J_0$  on non-dimensional fundamental frequency  $\Omega_3$  of the FG panel

### Effect of geometrical parameters on the fundamental frequency

Figure 4 and 5 depict the variation for the non-dimensional fundamental frequency of spherical panel and cylindrical panel versus the side-to-thickness (a/h) and side-to-radius ratios  $(b/R_2)$ . Note that: p = 1,  $T_m = 300$  K,  $T_c = 400$  K. It can be seen clearly from Fig. 4 that the dimensionless frequencies of these shell panels decrease dramatically with the increase of the side-to-thickness ratio.

To study the effect of the variation of the fundamental frequency versus side-to-radius ratio of shell panels  $(b/R_2)$ , the geometric and material properties and the temperature used for investigation in Fig. 5 are: a/b = 1, a/h = 20, p = 1,  $T_m = 300$  K,  $T_c = 400$  K and with varying ratio of  $b/R_2$ . For spherical panel,  $a/R_1 = b/R_2$  and for cylindrical panel,  $a/R_1 = 0$ . Figure 5 shows that the non-dimensional fundamental frequency increases with increasing of side-to-radius ratio. This means that the rising of the curvature of the shell causes an increase in the stiffness, which causes a rapid increase of the non-dimensional fundamental frequency of the panel.

Table 4 and Fig. 6 show an observation concerning the effect of foundation parameters  $K_0$ ,  $J_0$  on the variation of non-dimensional fundamental frequency  $\Omega_3$  of FG panel with a/b = 1, p = 1, a/h = 20,  $T_m = 300$  K and  $T_c = 400$  K. These results indicate that the non-dimensional fundamental frequency  $\Omega_3$  increases with increasing of foundation parameters  $K_0$ ,  $J_0$ , and the shear Pasternak parameter  $J_0$  has more significant effect than the Winkler parameter  $K_0$  in causing an increase of the non-dimensional fundamental frequency.

Based on the presented theory, it is clearly shown that the effect of foundation parameters  $K_0$ ,  $J_0$  plays an important role in the increase of the non-dimensional fundamental frequency of the FG panel. The non-dimensional fundamental frequencies of shell panels resting on elastic foundation are always bigger than those without elastic foundation.

#### Conclusion

In this paper, a solution for vibration analysis of simply supported FG doubly curved shell panels based on the first-order shear deformation theory is formulated. The Pasternak-type elastic foundation is in contact with the FG shell panels in thermal environment. The accuracy of numerical solutions has been validated against existing results in available literature. The numerical results show a significant impact of foundation parameters, thermal environment ( $T_c$ ,  $T_m$ ), power law index (p), side-to-thickness ratio (a/h) and side-to-radius ratio ( $b/R_2$ ) on non-dimensional fundamental frequency of the FG shell panels. We hope that the presented analytical solution could be useful references for future researches which relate to the mechanical behaviors of FG doubly curved shell panel structures.

Acknowledgments This work was supported by the Foundation for Science and Technology Development of National University of Civil Engineering—Ha Noi—Vietnam (Project code 212-2018/KHXD-TD).

**Open Access** This article is distributed under the terms of the Creative Commons Attribution 4.0 International License (http://creativecommons.org/licenses/by/4.0/), which permits unrestricted use, distribution, and reproduction in any medium, provided you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons license, and indicate if changes were made.

#### References

- Alijani F, Amabili M, Bakhtiari-Nejad F (2011) Thermal effects on nonlinear vibrations of functionally graded doubly curved shells using higher order shear deformation theory. Compos Struct 93(10):2541–2553
- Bhangale RK, Ganesan N, Padmanabhan C (2006) Linear thermoelastic buckling and free vibration behavior of functionally graded truncated conical shells. J Sound Vib 292(1):341–371
- Haddadpour H, Mahmoudkhani S, Navazi H (2007) Free vibration analysis of functionally graded cylindrical shells including thermal effects. Thin Walled Struct 45(6):591–599
- Huang X-L, Shen H-S (2004) Nonlinear vibration and dynamic response of functionally graded plates in thermal environments. Int J Solids Struct 41(9):2403–2427
- Javaheri R, Eslami M (2002) Thermal buckling of functionally graded plates. AIAA J 40(1):162–169
- Kadoli R, Ganesan N (2006) Buckling and free vibration analysis of functionally graded cylindrical shells subjected to a temperaturespecified boundary condition. J Sound Vib 289(3):450–480
- Kiani Y et al (2012) Static and dynamic analysis of an FGM doubly curved panel resting on the Pasternak-type elastic foundation. Compos Struct 94(8):2474–2484

- Malekzadeh P, Heydarpour Y (2012) Free vibration analysis of rotating functionally graded cylindrical shells in thermal environment. Compos Struct 94(9):2971–2981
- Pradyumna S, Bandyopadhyay J (2010) Free vibration and buckling of functionally graded shell panels in thermal environments. Int J Struct Stab Dyn 10(05):1031–1053
- Reddy J, Chin C (1998) Thermomechanical analysis of functionally graded cylinders and plates. J Therm Stress 21(6):593–626
- Shen H-S, Wang Z-X (2012) Assessment of Voigt and Mori-Tanaka models for vibration analysis of functionally graded plates. Compos Struct 94(7):2197–2208
- Sheng G, Wang X (2010) Thermoelastic vibration and buckling analysis of functionally graded piezoelectric cylindrical shells. Appl Math Model 34(9):2630–2643
- Wattanasakulpong N, Chaikittiratana A (2015) An analytical investigation on free vibration of FGM doubly curved shallow shells with stiffeners under thermal environment. Aerosp Sci Technol 40:181–190
- Zhao X, Lee Y, Liew KM (2009) Thermoelastic and vibration analysis of functionally graded cylindrical shells. Int J Mech Sci 51(9):694–707

**Publisher's Note** Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.