Archive of SID.ir



Polyolefins Journal, Vol. 10, No. 2 (2023) DOI: 10.22063/POJ.2023.3308.1250

MINI REVIEW

Development of half-titanocene catalysts for synthesis of cyclic olefin copolymers

Kotohiro Nomura

Department of Chemistry, Tokyo Metropolitan University, Hachioji, Tokyo, 1920397, Japan

Received: 14 January 2023, Accepted: 27 January 2023

ABSTRACT

Certain cyclic olefin copolymers (COCs) are known as promising amorphous materials with high transparency Cin the UV-vis region, thermal and humidity resistance, low dielectric constant, low water absorption, and dimensional stability. This short review focuses on the synthesis of (new) cyclic olefin copolymers by designed (nonbridged) half-titanocene catalysts, which enabled to proceed synthesis of the amorphous polymers by ethylene/ propylene copolymerization not only with norbornene (NBE), and tetracyclododecene (TCD), but also with so called low strained cyclic olefins (cyclopentene, cyclohexene, cycloheptene, and cyclooctene). Their thermal properties (glass transition temperature, T_g values) are affected by structure of the cyclic olefin employed and the contents, whereas linear relationships between T_g values and the contents were observed in all cases. **Polyolefins** J (2023) 10: 59-70

Keywords: Cyclic olefin copolymers; titanium catalyst; half-titanocene; norbornene; cyclic olefin.

INTRODUCTION

Olefin polymerization by early transition metal catalysts is the core technology for industrial production of polyolefins. Synthesis of the new copolymers that are not able to be prepared by conventional catalysts (Ziegler-Natta, metallocene catalysts, etc.) has been a long-term interest. This is because that (thermal, physical, mechanical, electronic) properties of the resultant copolymers were modified by the individual components. Functional polyolefins with specified properties should be more sustainable than those prepared from rather complicated monomers required several steps from fossil oil, especially in terms of better materials recycling (monomer unifications) and chemical recycling (no or much less additional functional groups, less additive). Design and development of the molecular catalysts for the purpose (highly active, better comonomer incorporations) has thus been a promising subject for successful synthesis [1-15].

It has been known that the ligands (steric and electronic) as well as the basic geometry (structural



^{*}Corresponding Author - E-mail: ktnomura@tmu.ac.jp



features) in the catalysts play an important role in catalysis. As shown in Scheme 1, it has been proposed that ansa (bridged) metallocenes showed better α -olefin incorporation than the unbridged ones in the ethylene/ α -olefin copolymerization, and the ansa (cyclopentadienyl)(amide)titanium catalysts, exemplified as $[Me_2Si(C_5Me_4)(N^tBu)]TiCl_2$ (called CGC, constrained geometry catalyst) [3], exhibited the more efficient α -olefin incorporation [3,16-18]. These facts were explained as due to a concept that the bridge constrains the structure to provide a more open coordination space for the coordination of α -olefins (rather steric bulk compared to ethylene). Indeed, the CGC demonstrated a capability of (rather) efficient styrene incorporation in the ethylene/styrene copolymerization [6,7], but showed invariably of the incorporation (<50 mol%) [2,6,7,19]. Later, the bimetallic catalysts (bimetallic CGC) enabled synthesis of the copolymer with high styrene content (76 mol%) [19-21]; the catalyst also enabled the synthesis of ethylene copolymers with disubstituted α-olefins [20,21].

Half-titanocenes modified with anionic ancillary donor ligands of type, Cp'TiX₂(Y) (Y = phenoxide, ketimide, phosphinimide, iminoimidazolide, amidinate etc., Scheme 2), first were demonstrated by us with phenoxide [22,23], and the synthesis of the new ethylene copolymers by incorporations of various olefins (sterically encumbered olefins, cyclic olefins, aromatic vinyl monomers, the others) was demonstrated [5-7, 16-38]. In particular, both the phenoxide (1) and the ketimide (2) analogues have been known as successful examples. Later, the η^{1} amidinate analogue (3) demonstrated the industrial production of chlorine-free synthetic rubber (EPDM, ethylene propylene diene terpolymer) without deep cooling, which is commonly employed in the conventional (Ziegler type) vanadium catalyst systems in industry [13].

Certain cyclic olefin copolymers (COCs) are promising amorphous materials with high transparency in the UV-vis region, high thermal resistance, low water absorption (humidity resistance), low dielectric constants, and dimensional stability; some of the ethylene-based copolymers have been commercialized (as TOPAS[®], APEL[®]) [39,40] as ultra-pure, crystalclear, and high barrier materials (especially for optical and medical applications). The copolymerization approach enables modification of their compositions (cyclic olefin contents, etc.) and microstructures (including tacticity, etc.). Although we can see many reports for the ethylene copolymerization with highly strained norbornene (NBE) by ordinary metallocene catalysts, half-titanocene catalysts, and the others (Scheme 2) [41-48], however, the successful examples for the efficient synthesis of random, high molecular weight copolymers with high NBE contents (high glass transition temperature (Tg values)) still have been limited by the ketimide analogue (2a) and the modified linked half-titanocenes (shown below) [49-51]. Moreover, the successful examples in the synthesis of amorphous copolymers by incorporation of low strain



poly(ethylene-co- α -olefin) poly(ethylene-co-styrene) poly(ethylene-co-norbornene)

Scheme 1. Selected group 4 transition metal complex catalysts for olefin polymerization (metallocene, *ansa*-half-titanocene called constrained geometry catalyst, CGC).

Polyolefins Journal, Vol. 10, No. 2 (2023)

monomers (cyclopentene, cycloheptene, cyclooctene etc.) still have been limited, as described below.

This short review (perspective) thus introduces successful reports for the synthesis of various COCs that were very difficult to prepare by conventional catalysts. These research efforts could provide important information on the basic design of cyclic olefin copolymers (monomer design) as well as catalysts.

ETHYLENE COPOLYMERIZATION WITH NORBORNENE (NBE), AND TETRA-CYCLODODECENE (TCD)

In the ethylene/NBE copolymerization by ordinary metallocene (exemplified as **SBI-Zr**, Scheme 3) and

CGC, both the activity and the molecular weight (M_n values) in the resultant copolymers decreased with increase in the NBE contents (NBE concentration charged, Table 1) [41,42,47]. In contrast, the fluorenyl analogue (Flu-CGC) enabled to proceed the NBE living polymerization in the presence of appropriate Al cocatalyst (dried MAO prepared by removing AlMe, from the commercially available MAO in toluene solution, or MMAO) [50,52,53]. The catalyst exhibited more efficient NBE incorporation than CGC, which enabled to afford not only the ethylene copolymers with high NBE contents [50], but also synthesis of NBE copolymers with propylene [53], α -olefin (1-hexene, 1-octene, etc.) [54,55], and later the gradient NBE copolymers with 1-alkene (1-octene, 1-decene, and 1-dodecene) [56]. Effect of the fluorenyl substituent plays a role toward the activity [55].

Efficient synthesis of the ethylene/NBE copolymers with efficient NBE incorporation was



Scheme 2. Nonbridged half-titanocenes: Basic concept for the catalysts design and selected examples of catalysts, and copolymers.

Polyolefins Journal, Vol. 10, No. 2 (2023)

Development of half-titanocene catalysts for synthesis of cyclic olefin copolymers





Scheme 3. Ethylene copolymerization with norbornene (NBE).

also demonstrated by the ketimide-modified halftitanocene, CpTiCl₂(N=C'Bu₂) (2a) to afford the high molecular weight random copolymers with high NBE contents (Table 1) [51]. No significant decrease in the activity (the catalyst deactivation) were observed even after 30 min. The activity rather increased by increasing in the initial NBE concentration charged, showing a unique contrast to the ordinary catalysts (metallocene, linked half-titanocenes like CGC) except Flu-CGC. The activities and the NBE incorporation were not strongly affected by the Al cocatalyst employed (MAO, MMAOs), whereas the effect of the Al cocatalyst was apparently observed by Flu-CGC [50,53,54]. The activity by **2a** increased at 60°C, and the significant decrease in the activity was not observed at 80°C [51]. The efficient synthesis of high molecular weight copolymers with high NBE contents (58.8-73.5 mol%) could be achieved and the copolymer compositions were uniform (confirmed by DSC thermograms, GPC traces). As shown in Figure 1, a relationship between the T_g values in the copolymer increased linearly with an increase in the NBE content [45,47,51]. Later, the syntheses of poly(NBE-co- α -olefin)s, and poly(TCD-co- α -olefin)s (TCD = tetracyclododecene, dimethanoocta-hydronaphthaline) with high T_g values (α -olefin = 1-hexene, 1-octene, 1-dodecene) were

Cat. (µmol)	Temp./ºC	E/atm	NBE ^(b) /M	[NBE] ₀ /[E] ₀ ^(c)	Activity ^(d)	M _n ^(e)	$M_w/M_n^{(e)}$	NBE ^(f) /mol%
SBI (0.10)	25	4	0.2	0.41	28860	231,000	2.02	10.8
SBI (0.10)	25	4	1.0	2.04	4860	229,000	2.37	29.5
CGC (0.50)	25	4	0.2	0.41	2460	211,000	1.88	9.6
CGC (0.50)	25	4	1.0	2.04	2000	128,000	2.15	26.5
1e (0.2)	25	4	0.2	0.41	10500	146,000	1.56	14.0
1e (0.5)	25	4	1.0	2.04	2300	58,700	1.82	35.2
2a (0.02)	80	4	1.0	3.94	133000	338,000	2.34	61.7
2a (0.02)	60	4	1.0	3.02	194000	475,000	2.20	51.2
2a (0.02)	40	4	1.0	2.45	48900	620,000	2.37	45.9
2a (0.02)	25	4	1.0	2.04	40200	719,000	2.92	40.7
2a (0.02) ^(g)	25	4	1.0	2.04	59700	613,000	2.18	41.0
2a (0.01) ^(h)	25	2	5.0	20.6	85800	340,000	2.00	65.8
2a (0.01) ^(h)	25	2	10.0	41.2	31500	444,000	2.01	73.5
4 (0.20)	25	4	1.0	2.04	6180	108,0000	2.53	31.4
4 (0.20)	80	4	1.0	3.94	5780	800,000	2.35	36.9

^(a)Conditions: toluene and NBE total 50 mL, ethylene 4 atm, MAO (white solid) 0.5-3.0 mmol, 10 min. ^(b)Initial NBE concentration in mmol/mL. ^(c)Initial NBE/E molar ratio. ^(d)Activity in kg-polymer/mol-M·h (M = Ti, Zr). ^(e)GPC data in *o*-dichlorobenzene *vs* PS stds. ^(f)NBE content (mol %) estimated by ¹³C NMR spectra. ^(g)Time 30 min. ^(h)Toluene+NBE total 10 mL.

Polyolefins Journal, Vol. 10, No. 2 (2023)

Nomura K.

also demonstrated by 2a, and the NBE/1-octene copolymerization in the presence of 1,7-octadiene by the tert-BuC₅H₄ analogue (**2b**) gave the polymer containing terminal olefinic double bond in the side chain [57]. Linear relationships between the T_g values and the NBE or TCD contents were observed [57].

The half-titanocene containing imidazolin-2iminato ligand, $CpTiCl_2[1,3-{}^{t}Bu_2(CHN)_2C=N]$ (4), showed rather high catalytic activities with efficient NBE incorporation in the copolymerization to give ultrahigh molecular weight copolymers [58]. Although the observed activities by 4 were lower than those by 2a, the catalyst could exhibit a promising possibility of the thermally robust, efficient catalyst for synthesis of the ultrahigh molecular weight polymers. Significant effect of the ligand substituents toward both the catalytic activity and the comonomer incorporation could be thus demonstrated.

The ethylene/TCD copolymers are promising materials possessing higher T_g values compared to the ethylene/NBE copolymers with the same cyclic olefin contents. Classical Ziegler-type vanadium catalyst systems [VOCl₃, VO(OEt)Cl₂ – EtAlCl₂•Et₂AlCl etc.] have been employed in industry under deep cooling conditions [59]. In contrast to many reports for the ethylene/NBE copolymerization [1-30], there were reports for the copolymerizations using metallocene catalysts (Scheme 4) [60-64], which generally exhibited low catalytic activities and/ or less efficient TCD incorporation. Recently, the efficient copolymerization to afford high molecular weight polymers with uniform compositions was demonstrated by ('BuC₅H₄)TiCl₂(N=CtBu₂) (**2b**) in the



Figure 1. Plots of glass transition temperature (T_g) vs norbornene (NBE) or tetradecane (TCD) contents in the ethylene (E) copolymers, poly(E-*co*-NBE)s, and poly(E-*co*-TCD)s [49,51].

Polyolefins Journal, Vol. 10, No. 2 (2023)

presence of MAO cocatalyst (Table 2) [65]. The Cp analogue, CpTiCl₂(N=CtBu₂) (2a), which is effective catalyst for efficient α -olefin/TCD and ethylene/NBE copolymerizations [51-57], however showed low catalytic activities. The activity by 2b increased at high temperature with increase in the TCD contents in the copolymers. The resultant polymers possess high molecular weights with unimodal molecular weight distributions, and a linear relationship between the T values and the TCD contents was seen (Figure 1). As described above, the ordinary metallocene catalysts exhibited low catalytic activities with less efficient TCD incorporations, and conventional vanadium catalyst systems are generally conducted under deep cooling conditions, the catalyst (2b) would thus provide a promising possibility of development of thermally robust catalysts in the copolymerization.

SYNTHESIS OF THE OTHER CYCLIC OLEFIN COPOLYMERS

Structure of cyclic olefin should play a role toward the properties (thermal and mechanical properties, transparency, dielectric constant, etc.). For example, ethylene copolymers with exo-1,4,4a,9,9a,10-hexahydro-9,10(1',2')-benzeno-1,4-methanoanthracene showed better mechanical property in film (elongation-at-break, stress-strain behavior) compared to the copolymers with BE with the similar T_a value [66]. As described in the introduction, the reports for the ethylene copolymerization with so called low strained cyclic olefins, especially cyclohexene (CHE) [67], cycloheptene (CHP) [68-70], and cis-cyclooctene (COE) [68-71] were limited until recently, whereas there are reports in the copolymerization with cyclopentene (CPE) [68,72-76]. The copolymerization with CHP, and COE by the linked half-titanocene catalysts afforded low molecular weight oligomers even under the specified conditions [68], and the synthesis of high molecular weight amorphous copolymers thus seemed very difficult until recently [70].

The ethylene/CPE copolymers prepared by ordinary zirconocene (metallocene) catalysts possessed a microstructure with 1,3- (and 1,2-) CPE insertion, and subsequent ethylene was inserted after isomerization of inserted CPE [72,73], whereas the copolymerization by titanium catalysts proceeded via 1,2-CPE insertion [68,74-76]. The copolymerization

Development of half-titanocene catalysts for synthesis of cyclic olefin copolymers

Table 2. Ethylene copolymerization with tetracyclododecene (TCD) by $Cp'TiCl_2(N=C^{*}Bu_2)$ [Cp' = Cp (**2a**), ${}^{*}BuC_5H_4$ (**2b**)], $CpTiCl_2[1,3-{}^{*}Bu_2(CHN)_2C=N]$ (**4**), $Me_2Si(C_5Me_4)(NtBu)$]TiCl₂ (**CGC**)-MAO catalysts (reference 65).^(a)

Ti/µmol	TCD ^(b) /mol/L	Temp./°C	Activity ^(c)	M _n ^(d) ×10 ⁻⁵	$M_w/M_n^{(d)}$	$T_{g}^{(e)}(T_{m}^{(e)})/^{\circ}C$	TCD ^(f) /mol%
CGC (0.05)	1.0	25	13900	14.3	1.58	56	
2a (0.8)	2.0	25	1650	1.92	1.41	150	
2b (0.02)	1.0	25	43700	5.88	1.60	108	25.6
2b (0.02)	2.0	25	23900	6.38	1.50	153	32.8
2b (0.02)	2.0	40	27800	6.43	1.67	170	33.5 ^g
2b (0.02)	2.0	60	33300	6.53	1.72	177	35.3
2b (0.02)	3.0	25	16800	6.43	1.61	171	33.6 ^g
2b (0.02)	4.0	60	22400	6.08	1.61	203	36.7

^(a)Polymerization conditions: toluene and TCD total 30 mL, ethylene 6 atm, 10 min, d-MAO (prepared by removing toluene and AIMe₃ from the ordinary MAO) 3.0 mmol. ^(b)Initial TCD concentration in mmol/mL. ^(c)Activity = kg-polymer/mol-Ti·h. ^(d)GPC data in *o*-dichlorobenzene *vs* polystyrene stads. ^(e)By DSC thermograms. ^(f)Estimated by ¹³C NMR spectra. ^(a)Estimated on the basis of the plots of T_a and TCD content.

with efficient CPE insertion as well as with high activity was demonstrated by the ${}^{BuC_{5}H_{4}}$ -ketimide analogue (**2b**) to afford high molecular weight copolymers (CPE content <43.6 mol%) [76]. A linear relationship between the CPE content and the T_g value was also demonstrated [75]. Cp'TiCl₂(O-2,6- ${}^{Pr_{2}C_{6}H_{3}}$) [Cp' ${}^{BuC_{5}H_{4}}$ (**1c**), 1,2,4-Me₃C₅H₂ (**1d**)] proceeded the copolymerization with CHE with 1,2-insertion, whereas the other catalysts (metallocenes, CGC, **1a**, **2**, **4**) did not incorporate CHE under the similar conditions [67]. The catalysts enabled synthesis of the ethylene copolymers with 4-methyl-1-cyclohexene (with 1,2-insertion) and 1-methylcyclopentene(with 1,2- and 1,3-insertion) [77].

The ethylene/COE copolymerization by **1a** gave high molecular weight amorphous copolymers with efficient 1,2-COE incorporations ($M_n = 1.08-12.6 \times 10^5$),

whereas the ketimide analogue (2a) showed rather less COE incorporations compared to **1a** but showed higher activities to afford ultrahigh molecular weight copolymers [70]. The copolymerization with CHP by 1a gave ultrahigh molecular weight amorphous copolymers $(M_n = 1.32 - 3.08 \times 10^6)$ with exclusive 1,2-CHP insertion. In contrast, CGC and SBI-Zr gave (semi)crystalline copolymers with less COE incorporations (Scheme 5); the resultant polymers by SBI-Zr possessed broad molecular weight distributions with 1,3-insertion [70]. The ketimide analogue (2a) showed notable activities in the copolymerization with tricyclo[6.2.1.0(2,7)]undeca-4-ene (TCUE) to produce high molecular weight copolymers ($M_p = 6.4-22.0 \times 10^5$, TCUE content 9.4-40.7 mol%) [70].

As observed in the ethylene copolymers with NBE,



Scheme 4. Reported catalysts for ethylene/tetracyclododecene copolymerization.

Polyolefins Journal, Vol. 10, No. 2 (2023)

Nomura K.



Scheme 5. Ethylene copolymerization with (low strained) cyclic olefins [67,70,75,76].



Figure 2. Relationships between T_g values and cyclic olefin content in the ethylene-cyclic olefin copolymers: Effect of monomer structure toward their thermal property [70].

TCD (Figure 1), and with CPE, linear relationships between their T_g values and the cyclic olefin contents were demonstrated in all cases (Figure 2). It is clear that their T_g values were affected by the ring size; placing an additional ring into cyclohexene leads to an increase in the T_g value [70].

More recently, synthesis of the amorphous propylene copolymers with CPE, CHE, CHP, COE, TCUE, and with TCD were demonstrated (Scheme 6) [37]. Linear plots of the T_g values versus the cyclic olefin contents were seen in all cases, suggesting that the cyclic structure affects the T_g values (except the copolymers with CPE, COE); the T_g values in the propylene copolymers were higher than those in the ethylene copolymers in the region of low cyclic olefin content (up to 25 mol%) [37].



Scheme 6. Propylene copolymerization with (low strained) cyclic olefins [37].

Development of half-titanocene catalysts for synthesis of cyclic olefin copolymers



CONCLUDING REMARKS AND OUTLOOK

As described in the introduction, olefin polymerization by transition metal catalysis is the core technology for the polyolefins process, and the development of new ethylene copolymers that have not been incorporated by conventional catalysts has been a long-term subject. In this manuscript, recent development for synthesis of cyclic olefin copolymers (COCs) has been reviewed including our recent reports. It is clear that design of the molecular catalysts plays a key role for the success. Additionally, analysis of catalytically active species (the structural and electronic nature) has been the central subject for understanding the catalysis mechanism, and we recently use solution synchrotron XAS (X-ray absorption spectroscopy) analysis such as XANES (XANES = X-ray Absorption Near Edge Structure) for analysis of the oxidation state and the basic geometry and their coordination atoms to the centered metal through EXAFS (EXAFS = Extended X-ray Absorption Fine Structure) [78,79]. The method should provide information of the oxidation state, the geometry, coordinated atom and the distance through the spectra. We hope that we could introduce clear picture for designing new COCs and more efficient molecular catalysis through this paper.

ACKNOWLEDGEMENTS

The projects by KN were partly supported by Grantin-Aid for Scientific Research from the Japan Society for the Promotion of Science (JSPS, No. 15H03812, 18H01982, 21H01942).

CONFLICTS OF INTEREST

The authors declare that they have no conflicts of interest.

REFERENCES

- 1. Kaminsky W (1994) Olefinpolymerisation mittels metallocenkatalysatoren. Angew Makromol Chem 223: 101-120
- Kaminsky W (1996) New polymers by metallocene catalysis. Macromol Chem Phys 197: 3907-3945
- 3. McKnight AL, Waymouth RM (1998) Group 4

ansa-cyclopentadienyl-amido catalysts for olefin polymerization. Chem Rev 98: 2587-2598

- Gibson VC, Spitzmesser SK (2003) Advances in non-metallocene olefin polymerization catalysis. Chem Rev 103: 283–316
- Nomura K, Liu J, Padmanabhan S, Kitiyanan B (2007) Nonbridged half-metallocenes containing anionic ancillary donor ligands: New promising candidates as catalysts for precise olefin polymerization. J Mol Catal-A 267: 1-29
- Nomura K (2009) Half-titanocenes containing anionic ancillary donor ligands as promising new catalysts for precise olefin polymerization. Dalton Trans 2009: 8811-8823
- Nomura K, Liu J (2011) Half-titanocenes for precise olefin polymerisation: Effects of ligand substituents and some mechanistic aspects. Dalton Trans 40: 7666-7682
- Redshaw C, Tang Y (2012) Tridentate ligands and beyond in group IV metal α-olefin homo-/ co-polymerization catalysis. Chem Soc Rev 41: 4484-4510
- 9. Osakada K (2014) Organometallic Reactions and Polymerization, Springer-Verlag
- Hoff R, Mathers RT (2018) Handbook of Transition Metal Polymerization Catalysts, 2nd ed., Wiley.
- Stürzel M, Mihan S, Mülhaupt R (2016) From multisite polymerization catalysis to sustainable materials and all-polyolefin composites. Chem Rev 116: 1398-1433
- Baier MC, Zuideveld MA, Mecking S (2014) Post-metallocenes in the industrial production of polyolefins. Angew Chem Int Ed 53: 9722-9744
- 13. van Doremaele G, van Duin M, Valla M, Berthoud A (2017) On the development of titanium κ^1 amidinate complexes, commercialized as Keltan ACETM technology, enabling the production of an unprecedented large variety of EPDM polymer structures. J Polym Sci Pol Chem 55: 2877-2891
- 14. Yuan S-F, Yan Y, Solan GA, Ma Y, Sun W-H (2020) Recent advancements in N-ligated group 4 molecular catalysts for the (co)polymerization of ethylene. Coord Chem Rev 411: 213254
- 15. Nomura K (2023) Catalysis for a Sustainable Environment: Reactions, Processes and Applied Technologies, Wiley, in press
- 16. Suhm J, Schneider MJ, Mülhaupt R (1998) Influence of metallocene structures on ethene

Polyolefins Journal, Vol. 10, No. 2 (2023)

copolymerization with 1-butene and 1-octene. J Mol Catal-A 128: 215-227

- Suhm J, Schneider MJ, Mülhaupt R (1997) Temperature dependence of copolymerization parameters in ethene/1-octene copolymerization using homogeneous rac-Me₂Si(2-MeBenz[e] Ind)₂ZrCl₂/MAO catalyst. J Polym Sci Pol Chem 35: 735-740
- Kakinuki K, Fujiki M, Nomura K (2009) Copolymerization of ethylene with α-olefins containing various substituents catalyzed by half-titanocenes: Factors affecting the monomer reactivities. Macromolecules 42: 4585-4595
- Li H, Marks TJ (2006) Nuclearity and cooperativity effects in binuclear catalysts and cocatalysts for olefin polymerization. Proc Nat Acad Sci USA 103: 15295-15302
- Delferro M, Marks TJ (2011) Multinuclear olefin polymerization catalysts. Chem Rev 111: 2450-2485
- McInnis JP, Delferro M, Marks TJ (2014) Multinuclear group 4 catalysis: Olefin polymerization pathways modified by strong metal-metal cooperative effects. Acc Chem Res 47: 2545-2557
- 22. Nomura K, Naga N, Miki M, Yanagi K, Imai, A (1998) Synthesis of various non-bridged Cp-aryloxy titanium(IV) complexes of the type CpTi(OAr)X₂, and the catalytic alkene polymerization. – Important role of substituents on both aryloxy and cyclopentadienyl groups. Organometallics 17: 2152-2154
- Nomura K, Naga N, Miki M, Yanagi K (1998) Olefin polymerization by (cyclopentadienyl) (aryloxy)titanium(IV) complexes-cocatalyst systems. Macromolecules 31: 7588-7597
- 24. Nomura K, Oya K, Komatsu T, Imanishi Y (2000) Effect of cyclopentadienyl fragment on monomer reactivities and monomer sequence distributions in ethylene/a-olefin copolymerization by nonbridged (cyclopentadienyl)(aryloxy) titanium(IV) complexes – MAO catalyst systems. Macromolecules 33: 3187-3189
- Nomura K, Okumura H, Komatsu T, Naga N (2002) Ethylene/styrene copolymerization by various (cyclopentadienyl)(aryloxy) titanium(IV) complexes - MAO catalyst systems. Macromolecules 35: 5388-5395
- 26. Nomura K, Itagaki K, Fujiki M (2005) Efficient incorporation of 2-methyl-1-pentene in

copolymerization of ethylene with 2-methyl-1-pentene catalyzed by nonbridged halftitanocenes. Macromolecules 38: 2053-2055

- Nomura K, Itagaki K (2005) Efficient incorporation of vinylcylohexane in ethylene/ vinylcyclohexane copolymerization catalyzed by nonbridged half-titanocenes. Macromolecules 38: 8121-8123
- Nomura K, Liu J, Fujiki M, Takemoto A (2007) Facile, efficient functionalization of polyolefins via controlled incorporation of terminal olefins by repeated 1,7-octadiene insertion. J Am Chem Soc 129: 14170-14171
- 29. Liu J, Nomura K (2008) Efficient functional group introduction into polyolefins by copolymerization of ethylene with allyltrialkylsilane using nonbridged half-titanocenes. Macromolecules 41: 1070-1072
- Itagaki K, Nomura K (2009) Efficient synthesis of functionalized polyolefin by incorporation of 4-vinylcyclohexene in ethylene copolymerization using half-titanocene catalysts. Macromolecules 42: 5097-5103
- 31. Kitphaitun S, Yan Q, Nomura K (2020) Effect of SiMe3, SiEt3 para-substituents for exhibiting high activity, introduction of hydroxy group in ethylene copolymerization catalyzed by phenoxide-modified half-titanocenes. Angew Chem Int Ed 59: 23072-23076
- 32. AokiH, NomuraK (2021) Synthesis of amorphous ethylene copolymers with 2-vinylnaphthalene, 4-vinylbiphenyl and 1-(4-vinylphenyl) naphthalene. Macromolecules 54: 83-93
- Kawamura K, Nomura K (2021) Ethylene copolymerization with limonene, β-pinene: New bio-based polyolefins prepared by coordination polymerization. Macromolecules 54: 4693-4703
- 34. Kitphaitun S, Chaimongkolkunasin S, Manit J, Makino R, Kadota J, Hirano H, Nomura K (2021) Ethylene/myrcene copolymer as new bio-based elastomers prepared by coordination polymerization using titanium catalysts. Macromolecules 54: 10049-10058
- 35. Kitphaitun S, Takeshita H, Nomura K (2022) Analysis of ethylene copolymers with long chain α -olefins (1-dodecene, 1-tetradecene, 1-hexadecene): A transition between main chain crystallization and side chain crystallization. ACS Omega 7: 6900-6910
- 36. Kitphaitun S, Fujimoto T, Ochi Y, Nomura



Development of half-titanocene catalysts for synthesis of cyclic olefin copolymers

K (2022) Effect of borate cocatalysts toward activity and comonomer incorporation in ethylene copolymerization by half-titanocene catalysts in methylcyclohexane. ACS Org Inorg Au 2: 386-391

- Okabe M, Nomura K (2023) Propylene cyclic olefin copolymers with cyclopentene, cyclohexene, cyclooctene, tricyclo[6.2.1.0(2,7)] undeca-4-ene, and with tetracyclododecene: The synthesis and effect of cyclic structure on thermal properties. Macromolecules 56: 81-91
- 38. Guo L, Makino R, Shimoyama D, Kadota J, Hirano H, Nomura K (2023) Synthesis of ethylene/ isoprene copolymers containing cyclopentane/ cyclohexane units as unique elastomers by halftitanocene catalysts. Macromolecules: 10.1021/ acs.macromol.2c02399
- http://www.topas.com/products/topas-cocpolymers (TOPAS®)
- 40. https://jp.mitsuichemicals.com/en/special/apel/ index.htm (APEL®)
- Cherdron H, Brekner M-J, Osan F (1994) Cycloolefin copolymer: A new class of transparent thermoplastics. Angew Makromol Chem 223: 121-133
- Kaminsky W, Beulich I, Arndt-Rosenau M (2001) Copolymerization of ethene with cyclic and other sterically hindered olefins. Macromol Symp 173: 211-226
- 43. Dragutan V, Streck R (2000) Catalytic polymerization of cycloolefins: Ionic, Ziegler-Natta and ring-opening metathesis polymerization, Elsevier
- 44. Tritto I, Boggioni L, Ferro DR (2006) Metallocene catalyzed ethene- and propene conorbornene polymerization: Mechanisms from a detailed microstructural analysis. Coord Chem Rev 250: 212-241
- 45. Nomura K (2008) Nonbridged half-titanocenes containing anionic ancillary donor ligands: promising new catalysts for precise synthesis of cyclic olefin copolymers (COCs). Chin J Polym Sci 26: 513-523
- Li X, Hou Z (2008) Organometallic catalysts for copolymerization of cyclic olefins. Coord Chem Rev 252: 1842-1869
- 47. Zhao W, Nomura K (2016) Design of efficient molecular catalysts for synthesis of cyclic olefin copolymers (COC) by copolymerization of ethylene and α -olefins with norbornene or

tetracyclododecene. Catalysts 6: 175

- 48. Boggioni L, Tritto I (2017) State of the art of cyclic olefin polymers. MRS Bull 38: 245-251
- 49. Nomura K, Tsubota M, Fujiki M (2003) Efficient ethylene/norbornene copolymerization by (aryloxo)(indenyl)titanium(IV) complexes– MAO catalyst system. Macromolecules 36: 3797-3799
- 50. Hasan T, Ikeda T, Shiono (2004)Т Ethene-norbornene copolymer with high norbornene content produced bv ansafluorenylamidodimethyltitanium complex using a suitable activator. Macromolecules 37: 8503-8509
- 51. Nomura K, Wang W, Fujiki M, Liu J (2006) Notable norbornene (NBE) incorporation in ethylene–NBE copolymerization catalysed by nonbridged half-titanocenes: better correlation between NBE incorporation and coordination energy. Chem Commun 2659-2661
- 52. Hasan T, Nishii K, Shiono T, Ikeda T (2002) Living polymerization of norbornene via vinyl addition with *ansa*-fluorenylamidodimethyltitanium complex. Macromolecules 35: 8933-8935
- 53. Cai Z, Nakayama Y, Shiono, T (2006) Living random copolymerization of propylene and norbornene with *ansa*fluorenylamidodimethyltitanium complex: Synthesis of novel syndiotactic polypropyleneb-poly(propylene-ran-norbornene). Macromolecules 39: 2031-2033
- Shiono T, Sugimoto M, Hasan T, Cai Z, Ikeda T (2008) Random copolymerization of norbornene with higher 1-alkene with *ansa*fluorenylamidodimethyltitanium catalyst. Macromolecules 41: 8292-8294
- 55. Cai Z, Harada R, Nakayama Y, Shiono T (2010) Highly active living random copolymerization of norbornene and 1-alkene with *ansa*fluorenylamidodimethyltitanium derivative: Substituent effects on fluorenyl ligand. Macromolecules 43: 4527-4531
- 56. Yuan H, Kida T, Kim H, Tanaka R, Cai Z, Nakayama Y, Shiono T (2020) Synthesis and properties of gradient copolymers composed of norbornene and higher α-olefins using an *ansa*-fluorenylamidodimethyltitanium-[Ph3C] [B(C6F5)4] catalyst system. Macromolecules 53: 4323-4329
- 57. Zhao W, Nomura K (2016) Copolymerizations

Polyolefins Journal, Vol. 10, No. 2 (2023)



of norbornene, tetracyclododecene with α -olefins by half-titanocene catalysts: Efficient synthesis of highly transparent, thermal resistance polymers. Macromolecules 49: 59-70

- Apisuk W, Trambitas A G, Kitiyanan B, Tamm M, Nomura K (2013) Efficient ethylene/norbornene copolymerization by half-titanocenes containing imidazolin-2-iminato ligands and MAO catalyst systems. J Polym Sci Pol Chem 51: 2575-2580
- 59. Mitsui Chemicals Co., Synthesis of ethylene/ TCD copolymers by vanadium catalyst systems [VOCl₃, VO(OEt)Cl₂ – EtAlCl₂•Et₂AlCl etc.] in the presence of halogenated Al alkyl cocatalyst, JP2001-106730; JP2006-22266; JP2008-248171
- Kaminsky W, Bark A (1992) Copolymerization of ethene and dimethanooctahydro-naphthalene with aluminoxane containing catalysts. Polym Int 28: 251-253
- 61. Kaminsky W, Engehausen R, Kopf J (1995) A tailor-made metallocene for the copolymerization of ethene with bulky cycloalkenes. Angew Chem Int Ed Engl 34: 2273-2275
- 62. Goodall BL, McIntosh LH, Rhodes LF (1995) New catalysts for the polymerization of cyclic olefins. Macromol Symp 89: 421-432
- Kaminsky W, Beulich I, Arndt-Rosenau M (2001) Copolymerization of ethene with cyclic and other sterically hindered olefins. Macromol Symp 173: 211-226
- Donner M, Fernandes M, Kaminsky W (2006) Synthesis of copolymers with sterically hindered and polar monomers. Macromol Symp 236: 193-202
- 65. Apisuk W, Ito H, Nomura K (2016) Efficient synthesis of cyclic olefin copolymers with high glass transition temperatures by ethylene copolymerization with tetracyclododecene (TCD) using (tert-BuC₅H₄)TiCl₂(N=CtBu₂) – MAO catalyst. J Polym Sci Pol Chem 54: 2662-2667
- 66. Hong M, Cui L, Liu S, Li Y (2012) Synthesis of novel cyclic olefin copolymer (COC) with high performance via effective copolymerization of ethylene with bulky cyclic olefin. Macromolecules 45: 5397-5402
- 67. Wang W, Fujiki M, Nomura K (2005) Copolymerization of ethylene with cyclohexene (CHE) catalyzed by nonbridged half-titanocenes containing aryloxo ligand: Notable effect of both cyclopentadienyl and anionic donor ligand

for efficient CHE incorporation. J Am Chem Soc 127: 4582-4583

- 68. Lavoie AR, Waymouth RM (2004) Catalytic syntheses of alternating, stereoregular ethylene/ cycloolefin copolymers. Tetrahedron 60: 7147-7155
- Naga N (2005) Copolymerization of ethylene with cycloolefins or cyclodiolefins by a constrained-geometry catalyst. J Polym Sci Pol Chem 43: 1285-1291
- 70. Harakawa H, Okabe M, Nomura K (2020) Synthesis of cyclic olefin copolymers (COCs) by ethylene copolymerisations with cyclooctene, cycloheptene, and with tricyclo[6.2.1.0(2,7)] undeca-4-ene: Effect of cyclic monomer structures on thermal properties. Polym Chem 11: 5590-5600
- 71. Buchmeiser MR, Camadanli S, Wang D, Zou Y, Decker U, Kühnel C, Reinhardt I (2011) A catalyst for the simultaneous ring-opening metathesis polymerization/vinyl insertion polymerization. Angew Chem Int Ed 50: 3566-3571
- 72. Kaminsky W, Spiehl R (1989) Copolymerization of cycloalkenes with ethylene in presence of chiral zirconocene catalysts. Makromol Chem 190: 515-526
- Naga N, Imanishi Y (2002) Copolymerization of ethylene and cyclopentene with zirconocene catalysts: Effect of ligand structure of zirconocenes. Macromol Chem Phys 203: 159-165
- 74. Lavoie AR, Ho MH, Waymouth RM (2003) Alternating stereospecific copolymerization of cyclopentene and ethylene with constrained geometry catalysts. Chem Commun 864-865
- Fujita M, Coates GW (2002) Synthesis and characterization of alternating and multiblock copolymers from ethylene and cyclopentene. Macromolecules 35: 9640-9647
- 76. Liu J, Nomura K (2007) Highly efficient ethylene/cyclopentene copolymerization with exclusive 1,2-cyclopentene incorporation by (cyclopentadienyl)(ketimide)titanium(IV) complex - MAO catalysts. Adv Synth Catal 349 : 2235-2240
- 77. Harakawa H, Patamma S, Boccia AC, Boggioni L, Ferro DR, Losio S, Nomura K, Tritto I (2018) Ethylene copolymerization with 4-methylcyclohexene, 1-methylcyclopentene by half-titanocene catalysts: Effect of ligands

Polyolefins Journal, Vol. 10, No. 2 (2023)

EB IPPI

and microstructural analysis of the copolymers. Macromolecules 51: 853-863

- Nomura K (2019) Solution X-ray absorption spectroscopy (XAS) for analysis of catalytically active species in reactions with ethylene by homogeneous (imido)vanadium(V) complexes – Al cocatalyst systems. Catalysts 9: 1016
- 79. Yi J, Nakatani N, Nomura K (2020) Solution XANES and EXAFS analysis of active species of titanium, vanadium complex catalysts in ethylene polymerisation/dimerisation and syndiospecific styrene polymerization. Dalton Tran 49: 8008-8028

Polyolefins Journal, Vol. 10, No. 2 (2023)

