# **REVIEW PAPER**

# A Review on Green Synthesis of Silver Nanoparticles by Employing Plants of Acanthaceae and its Bioactivities

Sharon Stephen, Toji Thomas\*

Department of Botany, St. Thomas College Palai, Arunapuram PO Pala-686574, Kottayam Dt. Kerala, India.

#### ARTICLE INFO

#### Article History:

Received 01Jun 2020 Accepted 23 Jul 2020 Published 01 Aug 2020

#### Keywords:

green synthesis antimicrobial activity nanotechnology phytochemicals biological activities

#### ABSTRACT

Nanotechnology has immense number of applications in all contemporary fields of science. Silver nanoparticles form an important part of metal nanoparticles, with wider range of applications in diverse areas of science. Plant mediated green synthesized silver nanoparticles are usually preferred due to its advantages over other metal nanoparticles viz. non toxicity, lesser energy consumption, cost effectiveness and lesser pollution. Plants belonging to Acanthaceae family are medicinally as well as pharmacologically relevant. They contain many important phytochemicals, which can reduce, stabilize and act as capping agents in the nanoparticle synthesis. Various mechanisms to synthesize silver nanoparticles are explored here to analyse its formations with the most efficient method. Different phytochemicals with various functional groups assisting the formation of nanoparticles during green synthesis are also summarized here. The synthesized silver nanoparticles show effective antimicrobial properties along with many other potential bioactivities. The mechanisms of antimicrobial properties of silver nanoparticles are also assessed. Various bioactivity studies connected with green synthesized AgNPs comprising of antimicrobial, antifungal, biocompatibility, antiinflammatory, anticancer, antioxidant, larvicidal, effect on Seed germination and growth are briefly outlined in this article.

#### How to cite this article

Stephen S., Thomas T. A Review on Green Synthesis of Silver Nanoparticles by Employing Plants of Acanthaceae and its Bioactivities. Nanomed Res J, 2020; 5(3): 215-224. DOI: 10.22034/nmrj.2020.03.002

## INTRODUCTION

It is a well-known fact that nanotechnology emerges as one of the most important interdisciplinary fields of science with wide range of applications. It involves the synthesis and manipulation of particle structure with a dimension of less than 100 nanometers in diameter [1]. Nanoparticles possess diverse physio-chemical properties such as optical, magnetic, catalytic properties [2], and biological applications in antimicrobial [3, 4], antioxidant, anti-inflammatory, antiviral, cardiac protection, wound dressing and anti-cancerous activities [5]. Nanoparticles (NPs) result in superior chemical reactivity, biological activity, and catalytic behaviour than their own larger particles [2, 6]. They are employed in major industries like food, chemical, feed, health, space,

cosmetics etc. The industries preferably employ green synthesized nanoparticles for manufacturing its products [2, 7]. Even though there are many metal NPs were investigated [8], silver nanoparticles (AgNPs) are considered to be the best due to the fact that the disadvantages of AgNPs are negligible as compared to its advantages [9].

Silver nanoparticles are included in a set of zero dimensional substances that demonstrate natural structure under its dimension extending from 1 to 100 nm [10]. AgNPs manifest peculiar thermal conductivity, chemical stability, and Raman scattering phenomena [11, 12]. AgNPs also possess optical, electronic, chemical photo-electrochemical, magnetic, catalytic and biological properties [13, 14] (Fig.1). This is in continuation with the application of silver metal being employed in preserving food products [15], and manufacturing

This work is licensed under the Creative Commons Attribution 4.0 International License.

To view a copy of this license, visit http://creativecommons.org/licenses/by/4.0/.

<sup>\*</sup> Corresponding Author Email: tojidr@yahoo.com




Fig. 1: Some properties of silver nanoparticles




Fig. 2: Common methods of synthesis of silver nanoparticles

utensils from prehistoric time onwards [16]. Now in the 21<sup>st</sup> century, AgNPs are used in broad range of applications, such as biomedical engineering, drug delivery, food industries, antimicrobial, textile industries, agriculture, water treatment (as an antioxidant), anticancer agent, larvicides, cancer cell therapy, component of ointments etc. [14]. Among the reported antimicrobial properties of different metal NPs, it was found that AgNPs exhibited prominent bactericidal and fungicidal activity [17, 18].

Method of synthesis of silver nanoparticles

Broadly speaking, there are Top-down and Bottom-up approaches for the synthesis of metallic nanoparticles (Fig. 2). Top down method is the method of synthesizing nanoparticles in nanoscale level by plastic deformation from large sized patterns [17]. In bottom-up method nanoparticles are formed by the self-assembly of miniaturized atomic components [19, 20]. Although numerous methods are envisaged for silver nanoparticle synthesis, the most conventional ones are physical



and chemical methods [21]. These procedures provide productive output; that are coupled with constrains such as the utilization of harmful reagents, great running costs, more requirement of energy etc. [17]. Some other disadvantages of these methods include energy consumption, slow synthesis and requirement of high concentration [22-24].

Nowadays green synthesis of nanoparticles is accepted widely because of its simple, non-toxic, rapid, stable nature and also less expensive [18]. Green synthesis utilizes environmentally ecofriendly raw materials like plant extract, algae, bacteria, fungi, and enzymes [17]. The major advantage of using plant extract includes large scale production under non aseptic condition and absence of cell culture for the production of nanoparticles [14]. Although a considerable number of plants as well as plant parts are used for the synthesis, here we summarize the reports on various synthesis protocols and bioactivities of silver nanoparticle using plant extract of Acanthaceae.

Phytochemicals characterized from members of Acanthaceae

Acanthaceae, a family of Agiopserms covers over 4,000 plant species and about 230 genera of plants present across the globe, which largely grow in subtropical and tropical places as primary diversity centres like the South American, Indo-Malay, African (comprising Madagascar), and Mexican-Central American areas [25]. Members of Acanthaceae family are medicinally important due to the presence of various phytochemicals like glycosides, flavonoids, phenolic compounds, naphthoquinone, benzonoids, triterpnoids etc. [42-49]; because of the presence of these phytochemicals, they show antibacterial [26, 27, 28], antifungal [29, 30], cytotoxic [31], antiinflammatory [32], antipyretic [33, 34], antiviral [35, 36], antioxidant [18], hepatoprotective [37], insecticidal [38], immunomodulatory [39], and anti-platelet aggregation properties [40, 41].

Green Synthesis of silver nanoparticles - Acanthaceae family members

There are different methods of AgNPs synthesis protocols which allow interaction between plant extract and metal salt either by mixing, heating, incubating, stirring or shaking. This interaction facilitates the formation of nanoparticles. The

major functional groups present in the Acanthaceae family members play an important role in this synthesis of AgNPs.

AgNPs having a size ranging from 10-20 nm were synthesized using Justicia glauca phytochemicals possessing functional groups like -C-O-C- of carboxylic group, O-H stretching of hydroxyl group, carbonyl group of aldehydes or ketonic group [51]. Moreover, these nanoparticles were formed due to the major contribution from C-O-C of phenolic compounds [50]. Dried leaf extract of Indoneesiella echioides was utilized for the creation of silver nanoparticle with a mean size consisting of ~25 nm. The production was assisted due to various functional groups present in phytochemicals revealed by FTIR analysis like the occurrence of aromatic primary amine (C-N stretch), secondary amine (N-H bend), carbonate ions, organic nitrates and aliphatic fluoro compounds (C-F stretch, C-O and C-O stretching modes), carboxylic group, C-O-C, C-OH vibrations, -C-O and -C=C stretch vibrations and Amide II band [52]. Oxidation of aldehydes to carboxylic acid of enzymes/proteins found in plant distillate resulted in nanoparticle formation. Silver nanoparticles were formed using Nilgirianthus ciliates leaf broth having hydroxyl group, carbonyl group, alpha CH3 methyl group of aldehydes and ketones and are characterized by UV-Vis spectra, ultra high resolution SEM, FTIR, DLS [28].

In another method, the aqueous fresh leaf extract of *Thunbergia grandiflora* with alkine, amine, alkyne, alcohol and aromatic compounds were used in the formation AgNP with an average size of 2.39 nm [26]. Fresh leaves of *Justicia adhatoda* yielded AgNPs of average size 20 nm and characterized by UV–visible spectra analysis as well as TEM analysis [53]. Leaf extract of *Barleria prionitis* containing amine, alkane, alkene and ether groups resulted by FTIR analysis, yielded 10-20 nm sized AgNP [54].

Treating aqueous leaf extract of *Lepidagathis* cristata having functional groups like secondary amide, carbonyl group and amide resulted in the formation of AgNPs of average particle size of 30 nm. The amide group of tryptophan present in the leaves significantly contributed in the reduction of the metal ion to nanoparticle [55]. The mixture of *Justitia adathoda* leaf extract composed of functional group like C-C in alkene ring and C = C of aromatic ring, ether linkage and C-N of amine and O-H of secondary alcohol resulted




Fig. 3: Role of Acanthaceae phytochemicals in AgNP green synthesis

in the formation of nanoparticle of size 18 nm. Furthermore, presence of phenolic and aromatic compounds helped in the stabilization of NPs [56].

Fresh leaf extracts of *Asystasia gangetica* containing functional groups like alkyl halide, aromatic amine, primary amine, OH group of alcohol and phenols, CN bond of nitride, C=O bond of carbonyl group were exploited in the assembly of AgNP having a dimension of 40 – 60 nm. [57]. Using methanolic leaf extract of *Clinacanthus nutans*, AgNPs were synthesized with an average size 46.4 - 53.8 nm here, carbonyl group contributed by different flavonoids involved in the formation of AgNPs [58].

Green synthesis of nanoparticle is the synthesis of nanoparticle using plants. Various plant parts can be used for the synthesis viz. stem, leaves, root, rhizome, flower, seed etc. Plants produce diverse bioactive secondary metabolites with different functional groups. These functional groups metal ions resulting in the generation of nanoparticles. The FTIR analysis revealed that different functional groups were associated with these processes [59]. Phenolic compounds hold carboxyl and hydroxyl groups which can disable iron ions by chelating and further inhibiting the superoxide driven Fenton reaction. This is presumed to be the most crucial supply of reactive oxygen species (ROS). Therefore, plants with a high content of phenolic compounds are one of the best candidates for nanoparticle synthesis [60].

The research by Jha et al revealed that phytochemicals particularly glutathiones, polyphenols, ascorbates and metallothioneins were certainly responsible for the generation of nanoparticles [61]. Shankar et al communicated the biosynthesis of pure metallic silver nanoparticles and they were stabilized by reducing sugars and/or terpenoids contained in the leaf broth of *Azadiracta indica* [62]. Polyols, as for example, terpenoids, flavones and polysaccharides in the

leaves of Cinnamomum camphora were considered as the main agents to reduce of silver as well as chloroaurate ions [63]. Li et al reported that proteins with amine groups and vitamin C present in the extract of Cinnamomum annuum L. were accountable for the Ag nanoparticles formation and rapid precipitation [64]. High density of highly steady silver nanoparticles were quickly synthesized using leaf extract of Datura metel which comprised of biomolecules like alkaloids, polysaccharides, amino acid, proteins/enzymes, and alcoholic compounds which could be employed as scaffolds to accelerate the formation of silver nanoparticles in solution phase [65]. Quinol (alcoholic compound) and chlorophyll pigment resulted in the reduction of silver ions and normalization of nanoparticles [66]. Purely natural constituents and its utilization help in the reduction and stabilization of metal nanoparticles (Fig.3) is still in exploration phase [60].

Some other factors responsible for the nanoparticle formation are reaction and incubation temperature. Rise in temperature boosts the speed of generation of nanoparticles. High temperature along with increased concentration of plant extract helped the formation of small sized NPs [67]. A compacted report of silver nanoparticle synthesis of Acanthaceae is reported in Table 1.

# Bioactivity of AgNPs - Antibacterial

Silver ions and silver salts were utilized for therapeutic application starting from the period of human urbanization. Silver ions and silver salts are now utilized in the form of antibacterial agent especially for wound dressing [68]. Among all other metals, silver shows higher antimicrobial activities [17]. It works against 650 microorganisms, including bacteria, fungi, virus, and eukaryotic microorganisms [58]. A summary of the findings is reported in Table 2.

It was observed such that gram positive bacteria

Table 1: Silver nanoparticles synthesis mediated by members of Acanthaceae

Name of the Plants	Plant part used	Size(nm)	Shape	Applications	References
Adhatoda vasica	Dried leaves	22.1-29.1	Spherical	Antimicrobial effect	[1]
Adhatoda vasica	Fresh leaves	10-15	spherical	Antibacterial	[79]
				Biocompatibility	
Andrographis	Fresh leaves	68.06	Cubic	Anticancer	[77]
echioides				antibacterial	
Andrographis	Fresh Leaves	40-60	Cubic	Antibacterial effect	[14]
paniculata					
Andrographis	Dried lesves	2-20	Cubic	Antimicrobial effect	[18]
serpyllifolia				Anti oxidant effect	
Andrographis	Fresh Leaf	3.4-71.6	Spherical	Antibacterial Effect	[27]
serpyllifolia			•	Larvicidal Activity	
Asystasia gangetica	Fresh leaves	40-60	spherical	Antibacterial effect	[57]
Barleria cristata	Dried leaves	38-41	Circular	Mosquitocidal potential	[75]
				Biotoxicity studies	
Barleria prionitis	Dried leaves	10-20	spherical	-	[54]
Blepharismadera	Dried leaves	-	spherical	Antimicrobial effect	[80]
spatensis			1		
Clinacanthus nutans	Methanolic leaves	46.4-53.8	spherical	Antimicrobial effect	[58]
	extract		•		
Hygrophila	Dried leaves	40.96	spherical	Antioxidant effect	[81]
auriculata			•	Antimicrobial effect	
Hygrophila	Seed extract	10-80	spherical	Anti bacterial	[82]
auriculata			•		
Indoneesiella	Dried leaves	-29	spherical	Antioxidant effect	[52]
echioides			•	Antimicrobial effect	
				Cytotoxicity effect	
Justicia adhatoda	leaves	5-50	Spherical	Antimicrobial effect	[53]
			Agglomerate		
Justicia adhatoda	Fresh leaves	18	spherical	Cytotoxicity studies	[56]
Justicia glauca	Fresh leaves	10-20	Spherical	Anti microbial effect	[51]
Justicia gendarussa	Dried leaf powder	12-30	Irregular spherical	Anti oxidant	[78]
J				Anti bacterial	
Justicia jendaracia	callus	50-65	spherical	Anti bacterial	[76]
				Ecotoxicity studies	
Justicia spicigera	Dried l p	86-100	Spherical	Anti bacterial	[29]
• 0	•		•	Anti fungal	
Lepidagathis cristata	Dried leaves	20-50	spherical	Antimicrobial studies	[55]
Nilgirianthus ciliates	leaves	117	crystalline	Antibacterial effect	[28]
Rhinacanthus	Dried leaves	22-11.5	spherical	Antibacterial effect	[29]
nasutus				Antifungal activity	
Strobilanthes	Fresh leaves	6-54	spherical	Antibacterial studies	[83]
flaccidifolius			_		
Thunbergia	Flower	Nanoscale	Crystalline cubic	Catalytic action on congo	[84]
grandiflora			•	red dye	
Thunbergia	Leaf	2.39	Spherical	Antibacterial effect	[26]
grandiflora			_	Effect on Seed germination	
= *				and growth	

are much immune towards AgNPs compared to gram negative bacteria. Since gram negative bacteria are coated with lipopolysaccharides, they show negative charge and therefore get attached with positively charged silver ions. Grampositive bacteria are enveloped by thick layer of peptidoglycans and linear polysaccharides which offer rigidity to the cell and thus avoid the binding

of NPs to its surface. In case of gram-negative bacteria, AgNPs penetrate into the cell by forming holes in the cell wall of the bacteria [69, 70].

# Bioactivity of AgNPs - Antifungal

A few reports of antifungal activities are reported on green synthesis of AgNPs employing Acanthaceace family members; for example, AgNPs

Table 2: Antimicrobial activity of green synthesized silver nanoparticles using members of Acanthaceae family

Plants	CON. AgNP	METHOD	Microorganisms with zone of inhibition in mm	References
Adhatoda vasica	Not specified	Disk diffusion method	Escherichia coli (19 $\pm$ 10) Bacillus thuringiensis (18.30 $\pm$ 1.50)	[1]
			Klebsiella pneumonia (12 $\pm$ 0.3) Pseudomonas Aeruoginosa (24.3 $\pm$ 1.5)	
			Staphylococcus aureus (19 $\pm$ 0.01)	
Andrographis	75 μg/ml	Well diffusion	Staphylococcus aureus(14.66 ± 0.57)	[27]
serpyllifolia	/ 5 μg/ ιιιι	method	Staphylococcus pneumonia $(21.33 \pm 0.88)$	[27]
			Pseudomonas fluorescens (20.00 ± 1.45)	
			Escherichia coli (19.00 $\pm$ 0.52)	
Andrographis	25 μL	Well diffusion	Pseudomonas aeruoginosa (21.3 $\pm$ 0.4)	[14]
paniculata	,	method	Escherichia coli (16.6 ± 0.3)	[]
			Vibrio cholera (15.4 $\pm$ 0.3)	
			Shingella flexneri (15.2 $\pm$ 0.1)	
			Bacillus subtilis (18.6 $\pm$ 0.4)	
			Staphylococcus aureus (13.7 ± 0.2)	
			Micrococcus luteus (17.6 $\pm$ 0.3)	
Clinacanthus nutans	10 μL	Disk diffusion	Bacillus subtilis (11.50 $\pm$ 1.22)	[58]
		method	Enterococcus faecalis $(8.33 \pm 0.47)$	,
			Staphylococcus aureus $(8.67 \pm 0.82)$	
			Escherichia coli (8.50 $\pm$ 0.50)	
			Pseudomonas eruoginosa (9.00 $\pm$ 0.94)	
			Proteus vulgaris $(8.80 \pm 0.45)$	
Hygrophila auriculata	15 μL(20	Agar well	Staphylococcus aureus (16 $\pm$ 0.25)	[81]
	mg/ml)	diffusion	Bacillus cereus (17 $\pm$ 0.10)	
	0 ,	method	Pseudomonas aeruoginosa (18 $\pm$ 0.15)	
		Kriby disc	Escherichia coli (13 $\pm$ 0.35)	
		diffusion		
		method		
Justicia spicigera	100 mg/ml	disc diffusion	Bacillus cereus $(10.0 \pm 0.2)$	[29]
		method	Klebsiella pneumonia (8.3 $\pm$ 0.6)	
			Enterobacter aerogenes $(7.1 \pm 0.4)$	
Lepidagathis cristata	50 μg/ml	Agar well	Escherichia coli (16 ± 0.5)	[55]
		diffusion	Pseudomonas aeruoginosa (15 ± 0.5)	
		method	Streptococcus pneumonia (16 $\pm$ 0.5)	
Rhinacanthus nasutus	50 μg/mL	Disk diffusion	Staphylococcus aureus (17.66 $\pm$ 0.57)	[30]
		method	Bacillus subtilis (15.66 $\pm$ 1.15)	
			Pseudomonas aeruoginosa	
			$(17.33 \pm 1.52)$	
			Escherichia coli (17.33 ± 1.52)	
			Klebsiella pneumonia (17.66 ± 1.52)	
Strobilanthes	5 mg/ml	Agar well	Proteus mirabilis (26 $\pm$ 0.06)	[83]
flaccidifolius		diffusion	Klebsiella pneumonia (26 $\pm$ 0.08)	
		method	Escherichia coli (20 $\pm$ 0.14)	
			Salmonella paratyphi (26 $\pm$ 0.80)	
			Pseudomonas aeruginosa (34 $\pm$ 0.14)	
Thunbergia grandiflora	30 μ <i>l of</i> 25	Disk diffusion	Klebsiella planticola (11.36 $\pm$ 0.3)	
	%	assay		[26]

synthesized using *Rhinacanthus nasutus* barred the growth of *Aspergillus niger* and *Aspergillus flavus* with the zone of inhibition  $18.66 \pm 1.52$ mm and  $17.66 \pm 1.52$ mm respectively [30]. *Justicia spicigera assisted* AgNPs synthesis (using a concentration of 100 mg/ml) showed antifungal activity towards *Macrophomania phaseolina* (ZoI =  $80.95 \pm 1.35$ 

mm), Alternaria alternate (ZoI =  $62.12 \pm 4.50$  mm), Fusarium solani (ZoI =  $35.60 \pm 3.55$  mm) Colletotrichum sp. (ZoI =  $40.16 \pm 2.35$  nm) in PDA medium. AgNPs initiates various changes in the hyphae, cell wall and the germination pattern of fungus [71]. The Ag<sup>+</sup> ions released by AgNPs get attached with thiol group of cystein proteins



of fungus leading to the death of fungus [72]. Antifungal activity decreases with increase in complexity of cellular organization of organisms, which interrupt the movement of the AgNPs into the cells [73, 74].

## Bioactivity of AgNPs - Biocompatibility

AgNPs synthesized from *Barleria cristata* were tested for its safety towards non-target organisms like *Diplonychus indicus*, *Anisops bouvieri*, *and Gambusia affinis*, which are mainly insect predators in ponds. Treatment resulted in negligible toxicity against organisms tested [75]. *Justicia jendaracia* mediated AgNPs study revealed that they did not cause any distinct effect on soil enzyme activity, soil macronutrients, soil microbial population and plant growth parameters of *Vinga mungo* [76]. Thus, the AgNPs are very safe to use; as it is less toxic to useful organisms, as well as it does not alter favourable conditions of plant growth.

## Bioactivity of AgNPs - anti-inflammatory activity

There are limited reports of anti-inflammatory activities on green synthesis of AgNPs by employing Acanthaceace family members. Hemigarphis colorata mediated synthesis of AgNPs, exhibited anti-inflammatory activity or inhibition of protein denaturation through tests namely, inhibiting heat induced albumin denaturation and membrane stabilizing test of RBC. Denaturation of protein causes inflammation. AgNPs synthesized using Hemigarphis colorata plant extract showed higher protein inhibition compared to its original plant extract. Moreover, results of membrane stabilization test also demonstrated that AgNPs could show higher values in the inhibition of hemolysis. Both tests demonstrated that AgNPs could act as an effective anti-inflammatory drug [32].

## Bioactivity of AgNPs - Anticancer

In this case also, a few reports are available, for example, AgNPs formed from *Andrographis echioides* demonstrated anticancer property towards the human breast adenocarcinoma cancer cell line (MCF-7) by creating free radicles like reactive oxygen species or boosting intracellular oxidative stress [77]. AgNPs synthesized by utilizing *Justicia adhatoda* exhibited anticancer property towards HeLa cell lines of cancer cells [56]. Anticancer property of AgNPs was established towards human lung adenocarcinoma cancer cells (A549) based on

AgNPs derived from *Indoneesiella echioides* [52]. *Bioactivity of AgNPs – Antioxidant effect* 

Indoneesiella echioides mediated AgNPs show antioxidant property using tests namely ABTS scavenging assay and DPPH scavenging assay [52]. AgNPs synthesized by employing Justicia gendarussa demonstrated significant antioxidant property. They were tested for ABTS scavenging assay, DPPH scavenging assay and against nitric oxide [78]. AgNPs formed using Andrographis serpyllifolia presented strong antioxidant activity in assays like DPPH, NO and H<sub>2</sub>O<sub>2</sub> [18]. AgNPs act as a natural antioxidant or efficient free radical scavenger against the free radicles which damages cell by means of oxidative stress, which in turn triggers injuries or apoptosis in organisms [52].

#### Bioactivity of AgNPs - larvicidal potential

Andrographis serpyllifolia leaf extract assisted synthesis of AgNPs showed prominent larvicidal effect on Culex quinquefasciatus. It possessed lower LC<sub>50</sub> and LC<sub>90</sub> values and higher mortality rate of larvae [27]. AgNPs synthesized from Barleria cristata displayed strong larvicidal property towards Anopheles subpictus, Aedes albopictus and Culex tritaeniorhynchus [75] AgNPs, synthesized utilizing Nilgirianthus ciliates were experimented on Aedes aegypti, which presented higher efficiency and mortality rate. The suggested mechanism for the effective larvicidal property was due to the penetrating capability of AgNPs, which resulted in molting arrest as well as morphological deformation [28].

Bioactivity of AgNPs – Effect on Seed germination and growth

AgNPs prepared using *Thunbergia grandiflora* resulted in higher rate of germination in seeds of *Vigna radiata wi*th a concentration of 75% AgNPs. AgNPs also exhibited higher rate of shoot and root growth on treating with 25% and 50% AgNPs concentration respectively [26].

## CONCLUSION

Synthesis of silver nanoparticles is effectively established using plants belong to Acanthaceae family. The phytochemicals present in the family members serve as both stabilizing and capping agents of the synthesized nanoparticles. They are best in their biological activities especially antibacterial action against broad spectrum of bacteria. Future

www.SID.ir

studies will revolve the best mechanism of action against bacteria and the occurrence of particular phytochemicals of the family best suitable for the synthesis of nanoparticles.

#### CONFLICT OF INTEREST

There is no conflict of interest among the authors.

## **REFERENCES**

- Bhumi G, Rao ML, Savithramma N. Green synthesis of silver nanoparticles from the leaf extract of Adhatoda vasica Nees. and assessment of its antibacterial activity. Asian Journal of Pharmaceutical and Clinical Research, 2015;8(3):62-7.
- Husen A, Siddiqi KS. Phytosynthesis of nanoparticles: concept, controversy and application. Nanoscale Research Letters. 2014;9(1).
- Nam G, Purushothaman B, Rangasamy S, Song JM. Investigating the versatility of multifunctional silver nanoparticles: preparation and inspection of their potential as wound treatment agents. International Nano Letters. 2015;6(1):51-63.
- Firdhouse MJ, Lalitha P. Biosynthesis of Silver Nanoparticles and Its Applications. Journal of Nanotechnology. 2015;2015:1-18.
- 5. Ahmad S, Munir S, Zeb N, Ullah A, Khan B, Ali J, et al. Green nanotechnology: a review on green synthesis of silver nanoparticles — an ecofriendly approach
- . International Journal of Nanomedicine. 2019; Volume 14:5087-
- Abou El-Nour KMM, Eftaiha Aa, Al-Warthan A, Ammar RAA. Synthesis and applications of silver nanoparticles. Arabian Journal of Chemistry. 2010;3(3):135-40.
- 7. Rana S, Kalaichelvan PT. Antibacterial activities of metal nanoparticles. Advanced Biotechnology, 2011;11(02):21-3.
- Rajeshkumar S, Bharath LV. Mechanism of plant-mediated synthesis of silver nanoparticles – A review on biomolecules involved, characterisation and antibacterial activity. Chemico-Biological Interactions. 2017;273:219-27.
- 9. Jannathul Firdhouse M, Lalitha P. Biocidal potential of biosynthesized silver nanoparticles against fungal threats. Journal of Nanostructure in Chemistry. 2014;5(1):25-33.
- Syafiuddin A, Salmiati, Salim MR, Beng Hong Kueh A, Hadibarata T, Nur H. A Review of Silver Nanoparticles: Research Trends, Global Consumption, Synthesis, Properties, and Future Challenges. Journal of the Chinese Chemical Society. 2017;64(7):732-56.
- Krutyakov YA, Kudrinskiy AA, Olenin AY, Lisichkin GV. Synthesis and properties of silver nanoparticles: advances and prospects. Russian Chemical Reviews. 2008;77(3):233-57.
- Tran QH, Nguyen VQ, Le A-T. Silver nanoparticles: synthesis, properties, toxicology, applications and perspectives. Advances in Natural Sciences: Nanoscience and Nanotechnology. 2013;4(3):033001.
- Sharma VK, Yngard RA, Lin Y. Silver nanoparticles: Green synthesis and their antimicrobial activities. Advances in Colloid and Interface Science. 2009;145(1-2):83-96.
- Sinha SN, Paul D. Phytosynthesis of Silver Nanoparticles UsingAndrographis paniculataLeaf Extract and Evaluation of Their Antibacterial Activities. Spectroscopy Letters.

- 2015;48(8):600-4.
- Fernández A, Soriano E, López-Carballo G, Picouet P, Lloret E, Gavara R, et al. Preservation of aseptic conditions in absorbent pads by using silver nanotechnology. Food Research International. 2009;42(8):1105-12.
- 16. Fromm KM. Give silver a shine. Nature Chemistry. 2011;3(2):178-.
- Beyene HD, Werkneh AA, Bezabh HK, Ambaye TG. Synthesis paradigm and applications of silver nanoparticles (AgNPs), a review. Sustainable Materials and Technologies. 2017;13:18-23.
- 18.Palithya S, Kotakadi VS, Pechalaneni J, Challagundla VN. Biofabrication of silver nanoparticles by leaf extract of Andrographis serpyllifolia and their antimicrobial and antioxidant activity. International Journal of Nano Dimension, 2018;9(4):398-407.
- Prabhu S, Poulose EK. Silver nanoparticles: mechanism of antimicrobial action, synthesis, medical applications, and toxicity effects. International Nano Letters. 2012;2(1).
- Dintinger J, Mühlig S, Rockstuhl C, Scharf T. A bottomup approach to fabricate optical metamaterials by selfassembled metallic nanoparticles. Optical Materials Express. 2012;2(3):269.
- Srikar SK, Giri DD, Pal DB, Mishra PK, Upadhyay SN. Green Synthesis of Silver Nanoparticles: A Review. Green and Sustainable Chemistry. 2016;06(01):34-56.
- Tarasenko NV, Butsen AV, Nevar EA, Savastenko NA. Synthesis of nanosized particles during laser ablation of gold in water. Applied Surface Science. 2006;252(13):4439-44
- Wiley BJ, Im SH, Li Z-Y, McLellan J, Siekkinen A, Xia Y. Maneuvering the Surface Plasmon Resonance of Silver Nanostructures through Shape-Controlled Synthesis. The Journal of Physical Chemistry B. 2006;110(32):15666-75.
- 24.Iravani S, Korbekandi H, Mirmohammadi SV, Zolfaghari B. Synthesis of silver nanoparticles: chemical, physical and biological methods. Research in Pharmaceutical Sciences, 2014;9(6):385-406.
- Burgos-Hernández M, Castillo-Campos G. Taxonomic revision of the Mesoamerican genus Spathacanthus (Justicieae, Acanthoideae, Acanthaceae). PhytoKeys. 2020;144:31-55.
- Mathew A, Thomas S. Green Synthesis, Characterization and Applications of Silver Nanoparticles using Thunbergia grandiflora Roxb. Journal of Nanoscience and Technology. 2019;5(2):669-72.
- Madhankumar R, Sivasankar P, Kalaimurugan D, Murugesan S. Antibacterial and Larvicidal Activity of Silver Nanoparticles Synthesized by the Leaf Extract of Andrographis serpyllifolia Wight. Journal of Cluster Science. 2019;31(4):719-26.
- 28. Meenambigai K, Kokila R, Naresh Kumar A. Nilgirianthus ciliatus mediated Environment friendly extracellular synthesis of AgNps for exacting its potential against the Dengue vector, Aedes aegypti and the Microbial pathogen, Staphylococcus aureus. Journal of Entomological and Acarological Research. 2018;50(1).
- 29. Bernardo-Mazariegos E, Valdez-Salas B, González-Mendoza D, Abdelmoteleb A, Tzintzun Camacho O, Ceceña Duran C, et al. Silver nanoparticles from Justicia spicigera and their antimicrobial potentialities in the biocontrol of foodborne bacteria and phytopathogenic fungi. Revista Argentina de Microbiología. 2019;51(2):103-9.



- Pasupuleti VR, Prasad T, Rayees Ahmad S, Satheesh Krishna B, Ganapathi N, Siew Hua G, et al. Biogenic silver nanoparticles using Rhinacanthus nasutus leaf extract: synthesis, spectral analysis, and antimicrobial studies. International Journal of Nanomedicine. 2013:3355.
- Arullappan S, Rajamanickam P, Thevar N, Kodimani CC. In Vitro Screening of Cytotoxic, Antimicrobial and Antioxidant Activities of Clinacanthus nutans (Acanthaceae) leaf extracts. Tropical Journal of Pharmaceutical Research. 2014;13(9):1455.
- 32.Thomas L, Mathew S. Biosynthesis, characterization, and anti-inflammatory study of *Hemigraphis colorata* loaded silver nanoparticles. Asian Journal of Pharmaceutical and Clinical Research, 2019;12(10):188-92.
- Sawadogo WR, Lompo M, Somé N, Guissou IP, Nacoulma-Ouedraogo OG. Anti-inflammatory, analgesic and antipyretic effects of *Lepidagathis anobrya* Nees (Acanthaceae). African Journal of Traditional, Complementary and Alternative Medicines. 2011;8(4).
- Patra A, Jha S, Murthy PN, Vaibhav AD, Chattopadhyay P, Panigrahi G, et al. Anti-Inflammatory and Antipyretic Activities of Hygrophila spinosa T. Anders Leaves (Acanthaceae). Tropical Journal of Pharmaceutical Research. 2009;8(2).
- Wiart C, Kumar K, Yusof MY, Hamimah H, Fauzi ZM, Sulaiman M. Antiviral properties of ent-labdene diterpenes of Andrographis paniculata nees, inhibitors of herpes simplex virus type 1. Phytotherapy Research. 2005;19(12):1069-70.
- 36. Ngoc TM, Phuong NTT, Khoi NM, Park S, Kwak HJ, Nhiem NX, et al. A new naphthoquinone analogue and antiviral constituents from the root of Rhinacanthus nasutus. Natural Product Research. 2018;33(3):360-6.
- 37.Kshirsagar AD, Ashok P. Hepatoprotective and antioxidant effects of *Hygrophila spinosa* (K. Schum) Heine Acanthaceae stem extract. Biosciences Biotechnology Research Asia, 2016;5(2):657-62.
- 38. Sukkanon C, Karpkird T, Saeung M, Leepasert T, Panthawong A, Suwonkerd W, et al. Excito-repellency Activity of Andrographis paniculata (Lamiales: Acanthaceae) Against Colonized Mosquitoes. Journal of Medical Entomology. 2019;57(1):192-203.
- Ghule BV, Kotagale NR, Patil KS. Inhibition of the proinflammatory mediators in rat neutrophils by shanzhiside methyl ester and its acetyl derivative isolated from Barleria prionitis. Journal of Ethnopharmacology. 2020;249:112374.
- Ali-Seyed M, Vijayaraghavan K. Dengue virus infections and anti-dengue virus activities of Andrographis paniculata. Asian Pacific Journal of Tropical Medicine. 2020;13(2):49.
- 41. Bukke S, Raghu PS, Sailaja G, Kedam TR. The study on morphological, phytochemical and pharmacological aspects of *Rhinacanthus nasutus* (L) Kurz (a review). Journal of Applied Pharmaceutical Science, 2011;1(8):26-32.
- Awan AJ, Ahmed CB, Uzair MU, Aslam MS, Farooq U, Ishfaq K. Family Acanthaceae and genus *Aphelandra*: ethnopharmacological and phytochemical review. International Journal of Pharmacy and Pharmaceutical Sciences, 2014;10(1):44-55.
- 43. Hemalatha K, Hareeka N, Sunitha D. Chemical constituents isolated from leaves of *Barleria cristata* Linn. International Journal of Pharma and Bio Sciences, 2012;3(1):609-15.
- 44. Abd El-Mawla A, Ahmed A, Ibraheim Z, Ernst L. Phenylethanoid Glycosides from Barleria Cristata L. Callus

- Cultures. Bulletin of Pharmaceutical Sciences Assiut. 2005;28(2):199-204.
- Chowdhury N, Hasan AA, Tareq FS, Ahsan M, Azam ATMZ. 4-Hydroxy-trans-cinnamate Derivatives and Triterpene from Barleria cristata. Dhaka University Journal of Pharmaceutical Sciences. 2014;12(2):143-5.
- Ashour MA-G. Isolation, HPLC/UV characterization and antioxidant activity of phenylethanoids from Blepharis edulis (Forssk.) Pers. growing in Egypt. Bulletin of Faculty of Pharmacy, Cairo University. 2012;50(1):67-72.
- 47.Jayapriya G, Shoba FG. GC-MS analysis of bio-active compounds in methanolic leaf extracts of *Justicia adhatoda* (Linn.). Journal of Pharmacognosy and Phytochemistry, 2015;4(1):113-7.
- Khoo LW, Mediani A, Zolkeflee NKZ, Leong SW, Ismail IS, Khatib A, et al. Phytochemical diversity of Clinacanthus nutans extracts and their bioactivity correlations elucidated by NMR based metabolomics. Phytochemistry Letters. 2015;14:123-33.
- Elaiyaraja A, Chandramohan G. Comparative phytochemical profile of *Indonessiella echioides* (L.) Nees leaves using GC-MS. Journal of Pharmacognosy and Phytochemistry, 2016;5(6):158-71.
- Palanisamy S, Thirumalraj B, Chen S-M, Ajmal Ali M, Muthupandi K, Emmanuel R, et al. Fabrication of Silver Nanoparticles Decorated on Activated Screen Printed Carbon Electrode and Its Application for Ultrasensitive Detection of Dopamine. Electroanalysis. 2015;27(8):1998-2006
- Emmanuel R, Palanisamy S, Chen S-M, Chelladurai K, Padmavathy S, Saravanan M, et al. Antimicrobial efficacy of green synthesized drug blended silver nanoparticles against dental caries and periodontal disease causing microorganisms. Materials Science and Engineering: C. 2015;56:374-9.
- 52. Kuppurangan G, Karuppasamy B, Nagarajan K, Krishnasamy Sekar R, Viswaprakash N, Ramasamy T. Biogenic synthesis and spectroscopic characterization of silver nanoparticles using leaf extract of Indonesiella echioides: in vitro assessment on antioxidant, antimicrobial and cytotoxicity potential. Applied Nanoscience. 2015;6(7):973-82.
- Bose D, Chatterjee S. Antibacterial Activity of Green Synthesized Silver Nanoparticles Using Vasaka (Justicia adhatoda L.) Leaf Extract. Indian Journal of Microbiology. 2015;55(2):163-7.
- 54.Ghosh S, Chacko MJ, Harke AN, Gurav SP, Joshi KA, Dhepe A, Kulkarni AS, Shinde VS, Parihar VS, Asok A, Banerjee K, Kamble N, Bellare J, Chopade BA. *Barleria prionitis* leaf mediated synthesis of silver and gold nanocatalysts. Journal of Nanomedicine and Nanotechnology, 2016;7(4):1-7.
- 55.Kumar SH, Prasad C, Deepa K, Sreenivasulu K, Jyothi NVV. Competitive rapid microwave-assisted biogenic synthesis of spherical silver nanoparticles using an aqueous leaf extract of *Lepidagathis cristata*: characterization and antimicrobial studies. Journal of Applied Pharmaceutical Science, 2018:8(6):124-31.
- 56.Kudle KR, Donda MR, Merugu R, Prashanthi Y, Rudra MP. Investigation on the cytotoxicity of green synthesis and characterization of silver nanoparticles using *Justicia adhatoda* leaves on human epitheloid carcinoma cells and evaluation of their antibacterial activity. International Journal of Drug Development and Research, 2014;6(1):113-9.

- 57.Jose A, Abirami T, Kavitha V, Sellakilli R, Karthikeyan J. Green synthesis of silver nanoparticles using Asystasia gangetica leaf extract and its antibacterial activity against gram-positive and gram-negative bacteria. Journal of Pharmacognosy and Phytochemistry, 2018;7(1):2453-7.
- 58. Abd Hamid H, Mutazah R. Synthesis of Silver Nanoparticles by Clinacanthus nutans Extract Supported with Identification of Flavonoids by UPLC-QTOF/MS and Its Antimicrobial Activity. Iranian Journal of Science and Technology, Transactions A: Science. 2018;43(5):2219-25.
- 59. Pirtarighat S, Ghannadnia M, Baghshahi S. Green synthesis of silver nanoparticles using the plant extract of Salvia spinosa grown in vitro and their antibacterial activity assessment. Journal of Nanostructure in Chemistry. 2018;9(1):1-9.
- Green synthesis of metal nanoparticles using plants. Green Chemistry, 2011;13(10):2638-50.
- Jha AK, Prasad K. Green Synthesis of Silver Nanoparticles UsingCycasLeaf. International Journal of Green Nanotechnology: Physics and Chemistry. 2010;1(2):P110-P7.
- 62. Shankar SS, Rai A, Ahmad A, Sastry M. Rapid synthesis of Au, Ag, and bimetallic Au core–Ag shell nanoparticles using Neem (Azadirachta indica) leaf broth. Journal of Colloid and Interface Science. 2004;275(2):496-502.
- Huang J, Li Q, Sun D, Lu Y, Su Y, Yang X, et al. Biosynthesis of silver and gold nanoparticles by novel sundriedCinnamomum camphoraleaf. Nanotechnology. 2007;18(10):105104.
- 64. Li S, Shen Y, Xie A, Yu X, Zhang X, Yang L, et al. Rapid, room-temperature synthesis of amorphous selenium/ protein composites usingCapsicum annuum Lextract. Nanotechnology. 2007;18(40):405101.
- 65.Dubey M, Bhadauria S, Kushwah BS. Green synthesis of nanosilver particles from extract of *Eucalyptus hybrida* (Safeda) leaf. Digest Journal of Nanomaterials and Biostructures, 2009;4(3):537-43.
- 66. Kesharwani J, Yoon KY, Hwang J, Rai M. Phytofabrication of Silver Nanoparticles by Leaf Extract of *Datura metel*: Hypothetical Mechanism Involved in Synthesis. Journal of Bionanoscience. 2009;3(1):39-44.
- Song JY, Jang H-K, Kim BS. Biological synthesis of gold nanoparticles using Magnolia kobus and Diopyros kaki leaf extracts. Process Biochemistry. 2009;44(10):1133-8.
- 68.Singh SP, Bhargava CS, Dubey V, Mishra A. Singh Y. Silver nanoparticles: biomedical applications, toxicity, and safety issues. International Journal of Research in Pharmacy and Pharmaceutical Sciences, 2017;4(2):1-10.
- 69.Ankanna ST, Prasad TN, Elumalai EK, Savithramma N. Production of biogenic silver nanoparticles using *Boswellia ovalifoliolata* stem bark. Digest Journal of Nanomaterials and Biostructures, 2010;5(2):369-72.
- Rai MK, Deshmukh SD, Ingle AP, Gade AK. Silver nanoparticles: the powerful nanoweapon against multidrugresistant bacteria. Journal of Applied Microbiology. 2012;112(5):841-52.
- 71. Harris SD. Morphogenesis in germinating Fusarium graminearum macroconidia. Mycologia. 2005;97(4):880-7.
- 72. Koduru JR, Kailasa SK, Bhamore JR, Kim K-H, Dutta T, Vellingiri K. Phytochemical-assisted synthetic approaches

- for silver nanoparticles antimicrobial applications: A review. Advances in Colloid and Interface Science. 2018;256:326-39
- Villamizar-Gallardo R, Cruz JFO, Ortíz-Rodriguez OO. Fungicidal effect of silver nanoparticles on toxigenic fungi in cocoa. Pesquisa Agropecuária Brasileira. 2016;51(12):1929-36
- 74. Gowramma B, Keerthi U, Rafi M, Muralidhara Rao D. Biogenic silver nanoparticles production and characterization from native stain of Corynebacterium species and its antimicrobial activity. 3 Biotech. 2014;5(2):195-201.
- Govindarajan M, Benelli G. Facile biosynthesis of silver nanoparticles using Barleria cristata: mosquitocidal potential and biotoxicity on three non-target aquatic organisms. Parasitology Research. 2015;115(3):925-35.
- 76.Namasivayam SK, Koilpillai YJ, Bharani RA, Samrat K. Synthesis, characterization, anti bacterial activity and ecotoxicity of silver nanoparticles from callus extract of *Justicia jendaracia* (Burm. f). Asian Journal of Pharmaceutical and Clinical Research, 2014;7(3):212-6.
- 77. Elangovan K, Elumalai D, Anupriya S, Shenbhagaraman R, Kaleena PK, Murugesan K. Phyto mediated biogenic synthesis of silver nanoparticles using leaf extract of Andrographis echioides and its bio-efficacy on anticancer and antibacterial activities. Journal of Photochemistry and Photobiology B: Biology. 2015;151:118-24.
- 78.Vijayakumar AS, Jeyaraj M, Selvakumar M, Abirami E. Pharmacological activity of silver nanoparticles, ethanolic extract from *Justicia gendarussa* (Burm) F plant leaves. Research Journal of Life Sciences Bioinformatics Pharmaceutical and Chemical Sciences, 2019;5(2):462-75.
- Latha M, Priyanka M, Rajasekar P, Manikandan R, Prabhu NM. Biocompatibility and antibacterial activity of the Adathoda vasica Linn extract mediated silver nanoparticles. Microbial Pathogenesis. 2016;93:88-94.
- 80.Parveen K, Prabakar K, Pote-Wembonyama J. Antimicrobial activity and characterization of green synthesized silver nanoparticles from *Blepharis maderaspatensis* (L) Hyne ex. Roth. International Journal of Current Research, 2016;8(9):38482-88.
- 81. S B, Kumaran S, Suresh G, Ramesh B, Sundari MsN. Phytosynthesis of Silver Nanoparticles Using Hygrophila Auriculata Leaf Extract and Assessment of Their Antibacterial and Antioxidant Properties. International Journal of Applied Pharmaceutics. 2018;10(6):112.
- 82. Priya DD, Prakash JT. Green synthesis of silver nanoparticles using *Hygrophila auriculata* seed extract with antibacterial activities. Journal of Pharmacognosy and Phytochemistry, 2018;7(5):2028-32.
- Wangkheirakpam SD, Devi WR, Singh CB, Laitonjam WS. Green Synthesis of Silver Nanoparticles using Strobilanthes flaccidifolius Nees. Leaf Extract and its Antibacterial Activity. JOURNAL OF ADVANCES IN CHEMISTRY. 2016;8(1):1523-32.
- 84. Varadavenkatesan T, Selvaraj R, Vinayagam R. Green synthesis of silver nanoparticles using Thunbergia grandiflora flower extract and its catalytic action in reduction of Congo red dye. Materials Today: Proceedings. 2020;23:39-42.