

Polymerization of Ethylene Using Cp_2ZrCl_2 Metallocene and Methylaluminoxane Homogeneous Catalyst System

Gholamhossein Zohuri^{*1}, Roghieh Jamjah², Saeed Ahmadjo²

(1) Chemistry Group, Department of Science, Ferdowsi University, 91775- Mashhad, I.R. Iran

(2) Department of Catalyst, Iran Polymer and Petrochemical Institute, P.O. Box: 14965/115
Tehran, I.R. Iran

Received 15 December 2003; accepted 19 July 2004

ABSTRACT

Bis(cyclopentadienyl) zirconium dichloride (Cp_2ZrCl_2) as a homogeneous metallocene catalyst was manufactured in laboratory scale under highly controlled conditions. Ethylene polymerization was carried out using this catalyst while, methylaluminoxane (MAO) was used as a cocatalyst. Activity of 5759 gPE/mmol Zr.h at $[Al]/[Zr]$ molar ratio of 770/1 was obtained. Polymer yield was increased with increasing in $[Al]/[Zr]$ ratio to a limiting value. Addition of hydrogen as a chain transfer agent up to 120 cm³/L solvent, increased the activity of the catalyst. Polymerization was carried out at monomer pressure of 1 to 5 atm, and temperature of 40°C to 80°C. Polymerization activity was increased with increasing temperature to 60°C and slightly decreased with more increase in temperature. Upon the addition of catalyst a sudden increase of 10°C in temperature was observed, particularly when polymerization temperature was higher than 50°C. This increase could be due to high rate of polymerization which at high temperature could affect catalyst activity. Monomer pressure up to 2 atm increased productivity of catalyst. Increase in $[Al]/[Zr]$ ratio, polymerization temperature and H_2 concentration decreased \bar{M}_v of polymer obtained. Melting point of polymer also decreased with increasing $[Al]/[Zr]$ ratio. Density of obtained polyethylene was 0.940-0.950 g/cm³. T_g of one of the polymer samples was determined which was 99.9°C.

Key Words:

metallocene;
methylaluminoxane;
homogeneous catalyst;
ethylene polymerization.

INTRODUCTION

Polymerization of olefins to polymers with different microstructures and properties is one of the most investigated areas in both industrial and academic laboratories in polymer science [1,2]. The use of polyolefins as polymer is rapidly grow-

ing and reaches a production level of million tones a year [3]. In this filed, metallocene catalysts have become increasingly important as part of potentially new generation of Ziegler-Natta (ZN) catalyst. As an advantage over the conventional ZN

(*)To whom correspondence should be addressed.
E-mail: G.Zohuri@ippi.ac.ir

catalyst, metallocene or single site catalyst have the capability of better control of polymer tacticity, molecular weight, and molecular weight distribution [4-6].

Metallocene catalysts consist mainly of compounds of group IV of transition metals (Ti, Zr, Hf) and a cocatalyst of aluminium compounds. Among them, zirconium compounds are the most active and common catalyst which are studied [1-3,7-10]. At higher temperature zirconium catalysts are more stable and active than titanium or hafnium systems [4].

While development of highly active metallocene polymerization catalyst systems has been one of the major achievements in polymerization catalysis, success in this area has been achieved mostly by discoveries of suitable cocatalyst activation systems. The activation system is AlMe₃-H₂O (alkylaluminumoxane) instead of the traditional one (Al(C₂H₅)₃ or Al(C₂H₅)₂Cl) that was used before.

The most active cocatalyst is methylaluminumoxane (MAO), which is obtained by controlled hydrolysis of trimethylaluminum. The cocatalyst is oligomeric compounds of general formula of [-Al(Me)O-]_n. The structure of MAO is complicated, which is supposed to be a cage with formula of Al₁₆O₁₂(CH₃)₂₄ [11]. There is at least one bridging oxo group between two aluminum atoms. Unfortunately homogeneous metallocene catalysts require a large excess of MAO to reach this maximum catalytic activity, which to some extent may impair this value in commercial application [12]. To overcome this problem it should be:

- 1) Use of cationic metallocene compounds that do not need any cocatalyst for polymerization [5, 13,14].
- 2) Use of supporting catalysts or co-catalysts by using either inorganic compounds such as Al₂O₃, SiO₂, MgCl₂ [5,10,15-17], or polymeric materials which may get great attention in industry and academic research [7,10,17]. The amount of MAO that is needed to reach to the maximum activity of supported catalysts is reduced [7,10, 16,17].

Ethylene polymerization behavior is heavily influenced by size and electronic properties of substituents groups on ligands. Electron-releasing groups favor higher activity, but bulky substituents and withdrawing groups reduce the activity of the catalyst. Aging of the catalyst, type of solvent, and additives also affect ethylene homopolymerization [10]. In ethylene polymeriza-

tion also much work has been done to minimize the [Al]/[Zr] ratio. So Cp₂ZrCl₂ is one of the most active catalyst [2,18], which is studied in this work.

EXPERIMENTAL

Cp₂ZrCl₂ catalyst was prepared according to method obtained from literature and developed in Polymer and Petrochemical Institute of IRAN [11]. The starting material was ZrCl₄ (anhydrous 98% Merck). MAO was prepared from Aldrich, (10% solution in toluene).

Polymerization runs were carried out in a 1L stainless steel reactor of Buchi (bmd 300) in dry toluene (500 mL). The toluene was refluxed inside the reactor (under vacuum) for about 60 min before the start of each run. The catalyst components were introduced under nitrogen [19-21].

Viscosity average molecular weight (\bar{M}_v) was determined [22,23]. Ubbelohde viscometer with a heating jacket, designed and constructed in Iran Polymer and Petrochemical Institute (IPPI) used for determining the \bar{M}_v of polyethylene. The viscometer jacket was heated with boiling chlorobenzene (b.p=131.6°C). Viscosity average molecular weights of samples were obtained with Mark Houwink equation:

$$\eta = KM^\alpha$$

Where $K=6.77 \times 10^4$ and $\alpha = 0.64$ are constants related to polymer and measuring condition. Decaline is used as solvent. The data for \bar{M}_v determination have been the average of three data.

Melting point of the polymer was determined using DSC PL Model STA 780. T_g of polymer was determined using DMTA PL model. Density of polymer was determined using pycnometer balance with densitometer facility.

RESULTS AND DISCUSSION

Cp₂ZrCl₂ catalyst was prepared using ZrCl₄ as starting compound. FTIR spectroscopy (FTIR, BRUKER model IFS 48) was used for identification of the catalyst structure (Figure 1). Absorption bands at 1439 cm⁻¹ (s), 1018 cm⁻¹ (s) and 806 cm⁻¹ (vs) are belonging to ν (C-




Figure 1. FTIR spectrum of Cp_2ZrCl_2 catalyst using KBr method.

C) asymmetric in a inplane skeletal, δ (C-H) asymmetric inplane deformation, and δ (C-H) symmetric out of plane deformation, respectively, reported for the same compound [24,25].

Ethylene polymerization was studied at constant Zr concentration and various amounts of MAO. Toluene (500 mL) was used as diluent. The effect of $[Al]/[Zr]$ ratio on polymerization activity, melting point, and \bar{M}_v of the obtained polymer were investigated (Table 1). The influence of the MAO concentration on the rate of ethylene polymerization shows the increasing indicate polymerization activity with increase in the $[Al]/[Zr]$ ratio to a constant value (Figure 2). This behaviour is common for metallocene catalysts [18].

Results of temperature's influence on the polymer yield were presented in Table 2. The catalyst system showed polymerization activity over the whole studied temperature range. However, a slight decrease in activity was observed for temperature higher than $60^\circ C$. Upon the addition of the catalyst, a sudden $10^\circ C$ increase in temperature was observed. The increase was higher particularly when polymerization was carried at higher than $50^\circ C$. This behaviour could be the




Figure 2. Plot of average rate of polymerization versus $[Al]/[Zr]$ ratio. Polymerization conditions are as detailed in Table 1.

result of decrease in activity at higher temperature than $60^\circ C$. The decrease in activity could be due to dissociation of π -olefin complex [18, 26].

The effect of H_2 concentration on catalyst activity is shown in Figure 4. Although the object of using H_2 is its chain transfer function, but it affect the catalyst activity by increasing it, with addition of H_2 to 120 ml/L solvent. However, further increase in H_2 concentration, decreased productivity of the catalyst. H_2 was added at $40^\circ C$, so the concentration of both monomer and H_2 were high enough in the solvent.

Influence of increasing monomer pressure from 1 atm to 5 atm was studied which is showed in Figure 5. Productivity of the catalyst increases with increasing monomer pressure up to 2 atm. Higher pressure of monomer at 3 atm decreases activity of the polymer. The activity of the catalyst remains almost constant with monomer pressure higher than 3 atm. Increasing pressure of monomer higher than 2 atm, significantly increases the catalyst activity at the beginning, and as the reaction is exothermic, it could deactivate some of the active sites of the catalyst. As a result, the increasing

Table 1. The influence of the MAO concentrations on polymerization behaviour.

MAO(mmol Al)	$[Al]/[Zr]$	gPE	Rp gPE/mmolZr.h	\bar{M}_v	m.p $^\circ C$
3	385	9.70	1244	284000	133
4.5	577	18.74	2403	259000	134
6	770	22.60	2897	248000	130.44
7.5	962	22.82	2926	138000	132.11
9	1152	22.22	2845	126000	117.81

($P_{Ethylene}$) = 2 atm, (polymerization time) = 1 h, $[Zr]$ = 0.0156 mmol/L solvent, (solvent) = 500 mL toluene, (temperature) = $50^\circ C$, (stirrer speed) = 800 rpm.

Table 2. The influence of temperature on polymerization behaviour.

Temp(°C)	gPE	Rp gPE/mmolZr.h	\bar{M}_v	m.p.°C
40	19.72	2528	300000	138
50	22.69	2897	248000	130.44
60	44.92	5759	237000	-
70	38.26	4905	70000	134
80	41.54	5326	51000	134

(P_{Ethylene}) = 2 atm, (polymerization time) = 1 h, [Zr] = 0.0156 mmol/L solvent, (solvent) = 500 mL toluene, (temperature) = 50°C, ([Al]/[Zr]) = 770/1, (stirrer speed) = 800 rpm.



Table 3. Comparison of polymerization activity of manufactured catalyst and commercial catalyst.

catalyst Cp ₂ ZrCl ₂	gPE	Rp gPE/mmolZr.h	Monomer pressure (atm)
Manufactured	19.72	2528	2
	19.13	2474	3
Commercial(Fluka) 14693	17.34	2223	2
	17.03	2183	3

(temperature) = 40°C, (polymerization time) = 1 h, [Zr] = 0.0156 mmol/L solvent, ([Al]/[Zr]) = 770/1.


temperature could destroy structure of the catalyst particularly at the Cp-Zr bond [18, 26].

Comparison of polymerization activity of manufactured Cp₂ZrCl₂ catalyst and the commercial one purchased from Fluka. shows similar polymerization activity (Table 3).

**Figure 3.** DMTA of polymer obtained at 40°C and monomer pressure = 2 atm.**Figure 4.** Plot of average rate of polymerization versus H₂ concentration. (temperature) = 40°C, (polymerization time) = 1 h, [Zr] = 0.0156 mmol/L solvent, ([Al]/[Zr]) = 770/1.

Polyethylene Characterization

Some characteristics of polyethylene which was obtained with the Cp₂ZrCl₂/MAO catalyst system get at different polymerization conditions are listed in Table 1 and 2. These results indicate certain conclusions. When the [Al]/[Zr] ratio increases, the \bar{M}_v and the melting point of the polymer decrease (Figure 6 and Table 1). Also, chain transfer is facilitated due to increase of methylaluminoxane concentration [2]. As expected, the increasing hydrogen concentration and temperature also decrease \bar{M}_v (Figure 7 and Table 2). Addition of H₂ dramatically decreased \bar{M}_v of the polymer. Addition of H₂, increasing temperature and, then H₂ facilitates chain transfer which causes reduction of \bar{M}_v [20, 21]. Density of some of the polymer measured

**Figure 5.** Plot of gPE obtained versus monomer pressure. (temperature) = 40°C, (polymerization time) = 20 min, [Zr] = 0.0156 mmol/L solvent, (solvent) = 500 mL toluene, (temperature) = 50°C, ([Al]/[Zr]) = 770/1 molar ratio, (stirrer speed) = 800 rpm.




Figure 6. Effect of $[Al]/[Zr]$ ratio on \bar{M}_v of polymer. Polymerization conditions are as detailed in Table 1.




Figure 7. Effect of H_2 concentration on \bar{M}_v . Polymerization conditions are as Figure 4.

which was 0.940-0.956 g/cm³ which is the indication of high density polyethylene.

CONCLUSION

The concluding remarks are as follows:

1. The prepared catalyst was quietly an active catalyst, its activity was comparable with the commercial one.
2. Increasing $[Al]/[Zr]$ ratio increases polymerization activity of the catalyst.
3. Maximum activity of the catalyst was obtained at 60°C.
4. Addition of H_2 up to 120 cm³/L solvent increases the activity of the catalyst, while higher concentration of H_2 decreased its activity.

5. Maximum productivity was obtained at 2 atm of monomer pressure.

6. Increasing temperature, $[Al]/[Zr]$ ratio, and H_2 concentration decreased the \bar{M}_v of the obtained polymer.

REFERENCES

1. Bendikt G.M. and Goodall B. L., *Metallocene Catalyzed Polymer*, Plastic Design Library, Norwich, NY, Ch.1 (1998).
2. Kaminsky W. and Arndt M., *Metallocene for Polymer Catalysis*, *Adv. Polym. Sci.*, **127**, 143, 187 (1997).
3. Bendikt G.M., *Metallocene Technology*, Plastic Design Library, Norwich, NY, Ch.1 (1999).
4. Kaminsky W., and Duch A., *Catalysts In Petroleum Refining and Petrochemical Industries*, in: *New developments in olefin polymerization with metallocene catalysts*, Elsevier, Amsterdam, 91-98 (1995).
5. Tian J., Ko Y.S., Metcalfe R., Feng Y., and Collins S., Synthesis of olefin polymerization using tethered ansa-metallocene complexes, *Macromolecules*, **34**, 3120-3122 (2001).
6. Xu S., Deng X., Wang B., Zhou X., Yang L., Li Y., Hu Y., Zou F., and Li Y., Ethylene polymerization with cycloalkylidene-bridged cyclopentadienyl metallocene Catalyst, *Macromol. Rapid Commun.*, **22**, 708-709 (2001).
7. Meng F., Yn G., and Huang B., Polymer-supported zirconocene catalyst for ethylene polymerization, *J. Polym. Sci. Part A: Polym. Chem.*, **37**, 37-46 (1999).
8. Wang L., Zhang P.Y., Jiang S., and Feng L. X., Study of ethylene polymerization catalyzed by n-Bu-CP₂ZrCl₂ MAO catalytic system and their polymerization kinetics, *J. of Appl. Polym. Sci.*, **81**, 3186-3189 (2001).
9. Zhou J., Li N., Bu N., Lynch D. T., and Wanke S.E, Gas-phase ethylene polymerization over polymer-supported metallocene catalysts, *J. Appl. Polym. Sci.* **90**, 1319-1330 (2003).
10. Salamon J.C., *Polymeric Materials Encyclopedia*, CRC, **6**, 4160, (1996).
11. Togni A., and Halterman R. L., *Metallocenes, Synthesis Reactivity Applications*, Wiley-VCH, Weinheim, **2**, 554 (1998).
12. Liu S., Meng F., Yu G., and Huang B., Preparation of polymer-supported zirconocene catalysts and olefin poly-

- merization, *J. Appl. Polym. Sci.*, **71**, 2253-2258 (1999).
13. Hlatky G.G., Turner H.W., and Echman R.R., Ionic, base-free zirconocene catalysts for ethylene polymerization *J. Am. Chem. Soc.*, **111**, 2728-2729 (1989).
 14. Yang X., Stern C.L., and Marks T.J., Cation-like homogeneous olefin polymerization catalysts based up on zirconocene alkyls and tris (pentafluorophenyl) borane, *J. Am. Chem. Soc.*, **113**, 3623-3625 (1991).
 15. Kaminaka M., and Soga K., Polymerization of propene with the catalyst systems composed of Al₂O₃- or MgCl₂-supported Et[Ind H₄]₂ZrCl₂ and AlR₃(R=CH₃, C₂H₅), *Die Makromol. Chem. Rapid Comm.*, **12**, 367-372(1991).
 16. Soga K., and Kaminaka M., Polymerization of propene with the heterogeneous catalyst system Et[Ind H₄]₂ZrCl₂/MAO/SiO₂ combined with trialkylaluminum, *Die Makromol. Chem. Rapid Comm.*, **13**, 221-24 (1992).
 17. Arai T., Ban H.T., Uozumi H. T., and Soga K., Syntheses of polysiloxane supported zirconocene catalysts and application to ethylene polymerization, *Macromol. Chem. Phys.*, **198**, 229-237 (1997).
 18. Justino J., Romao Dias A., Ascenso J., Marcues M. M., and Tait P.J.T., Polymerization of ethylene using metallocene and aluminoxane systems, *Polym. Int.*, **44**, 407-412 (1997).
 19. Zohuri G. H., Ahmadjo S., Jamjah R., and Nekomanesh M., Structural study of mono-and bi-supported Ziegler-Natta catalysts of MgCl₂/SiO₂/TiCl₄/donor systems, *Iran. Polym. J.*, **10**, 149-155 (2001).
 20. Zohuri G.H., Sadegvandi F., Jamjah R., Ahmadjo S., Nekomanesh M., and Bigdelli E., Copolymerization of ethylene/propylene elastomer using high-activity ziegler-natta catalyst systems of MgCl₂ (ethoxide type)/EB/PDMS/TiCl₄/PMT, *J. Appl. Polym. Sci.*, **84**, 785-790 (2002).
 21. Zohuri G. H., Azimfar F., Jamjah R., and Ahmadjo S., Polymerization of propylene using the high-activity Ziegler-Natta catalyst system SiO₂/MgCl₂/(ethoxide type)/TiCl₄/Di-n-butyl phthalate/ triethylaluminum/ dimethoxy methyl cyclohexyl silane, *J. Appl. Polym. Sci.*, **89**, 1177-1181 (2003).
 22. Zohuri G.H., Nekomanesh M., Bayan M., and Jamjah R., Study on ethylene polymerization by active Ziegler-Natta catalyst based TiCl₄ supported on Mg(OEt)₂, *Iran. Polym. J. (Persian)* **3**, 147-155 (1997).
 23. Brandrup J., and Immergut E. H., *Polymer Handbook*, 3rd ed., Wiley, New York, Sec. VII (1989).
 24. Wilkinson G. and Birmingham J.M., Bis-cyclopentadienyl compound of Ti, Zr, Nb and Ta, *J. Am. Chem. Soc.*, **76**, 4281-4284 (1954).
 25. Druce P.M., Kingston B.M., Lappert M.F., Spading T.R., and Srivastav R.C., Metallocene Halides Part I. Synthesis, spectra and redistribution equilibria of di-π-cyclopentadienyl-dihalogeno-titanium (IV), zirconium-(IV), and hafnium (IV), *J. Chem. Soc. (A)*, 2106-2110 (1969).
 26. Tsai W.M., and Chien J.C.W., Silolene-bridged zirconocenium polymerization catalysts, *J. Polym. Sci. Polym. Chem.*, **32**, 179-158 (1994).