Experimental Examination of Sulfur Dioxide Dry Removal from a Mixture of Gases by Calcium Oxide, Calcium Carbonate and Dolomite

Đurić, Slavko⁺; Brankov, Saša* Faculty of Technical Sciences, 6,Trg Dositeja Obradovića, Novi Sad, SERBIA

Stanojević, Petko

Railways of Republika Srpska, 71, Svetog Save , Doboj, BOSNIA AND HERZEGOVINA

Božičković, Ranko

Faculty of Transport and Technical Sciences, 52, Vojvode Mišića, Doboj, BOSNIA AND HERZEGOVINA

ABSTRACT: This paper refers to an experiment of SO_2 absorption to the three different sorbents: calcium-oxide (CaO), calcium-carbonate (CaCO₃) and dolomite (CaMg(CO₃)₂). In the reactor under the condition of oxidation atmosphere with the mass of sorbent (sample) of 100 g with fractional composition of 500-700µm, the gas temperature varied from 200°C and 400°C. The examinations indicated that the highest degree of sorbent utilization of 14 % was determined for dolomite (CaMg(CO₃)₂) and the binding degree of SO₂ from 65-80% and the lowest for calcium oxide (CaO) of 4% and the binding degree of SO₂ from 34-60% at the reaction temperature of 200°C. When the reaction temperature is 400°C the degree of sorbent utilization is a bit lower. The achieved results indicate the injection capability of powdered sorbents CaMg(CO₃)₂, CaCO₃ and CaO in the areas of lower temperatures as it is the convective part of the boiler or furnace flue of the thermo power plant.

KEY WORDS: Sorbent, Absorption degree of SO₂, Reaction temperature, Particle diameter.

INTRODUCTION

During dry Flue Gas Desulfurisation (FGD) processes the dry particles of the reagent are injected into the stream of gases, which absorb SO₂ through chemical reactions. Most often used reagents are calcium compounds CaCO₃, CaO or Ca(OH)₂. The industrial examinations show that the binding degree of SO₂ from flue gases to the sorbent particles is usually function of stechyometric relation of calcium share in injected sorbent and sulfur share from coal and it is in a wide range of 30-70% utilizing CaCO₃, 35-45% utilizing Ca(OH)₂, 25-60% utilizing CaO, 60-70%, utilizing dolomite (CaMg(CO₃)₂) in stechyometric relations Ca/S= 1-5. [1-3]. Theoretical

^{*} To whom correspondence should be addressed.

⁺ E-mail: djuricnslavko@yahoo.de

^{1021-9986/12/2/ 7/\$/2.70}



Fig. 1: The scheme of experimental facility (and measuring points) for SO_2 separation from the gas mixture (N_2+O_2) via dry processes by sorbent.

and experimental researches of binding of SO_2 to the sorbent particles on the base of calcium compound, confirmed the practical utilization of dry process of flue gases refinement from SO_2 [4-14].

A significant number of theoretical and experimental studies examines indirect and direct sulfatization [4,10,11]. During the indirect sulfatization researchers conclude that the process of formation $CaCO_4$ is enabled by formation of intermediate product $CaSO_3$ which depending on the reaction temperature and O_2 volume ratio in flue gas oxidizes in $CaSO_4$ or CaS. According to some other researchers two mechanisms of $CaSO_4$ synthesis are recommended. The first mechanism includes the formation of intermediate product $CaSO_3$, and the second mechanism the formation of SO_3 . For the both mechanisms the reaction temperatures of around 850 °C are sufficient, but reaction temperatures over 850 °C favor the formation of $CaSO_4$ only for the second mechanism.

The complex interaction of various resistances (diffusion over film gas, diffusion in the product layer and surface reaction of SO_2), is the main cause of inconsistency between mechanisms and results which were given by various researchers.

EXPERIMENTAL SECTION

The scheme and description of experimental facility for SO_2 separation from a mixture of gases

The scheme of laboratory facility for SO_2 separation from a mixture of gases in dry processes with lime (CaO), limestone CaCO₃), dolomite CaMg(CO₃)₂ and the list of Measuring Points (M.P.) are shown in Fig. 1, and in Fig. 2 the schemes of thermal furnace and reactor container for SO₂ separation are shown.

During the experiment of SO₂ absorption process, sorbent mass (sample) in the reactor was 100 g and the sorbent particle size was 500-700 μ m. The heating process of the reactor and sorbent inside the reactor is achieved by electrical heaters. For each experiment the reaction temperature was adjusted to approximately firstly 200 °C, and secondly 400 °C. When the desired temperature was reached (\approx 200 °C i.e. \approx 400 °C), the sorbent is mechanically injected into the reactor using the dispenser. Then the gas mixture N₂+O₂+SO₂ is introduced into a reactor by vacuum pump in order to separate SO₂. A gas analyzer was continually used in measuring the concentration of SO₂ and O₂ in the inlet and gas outlet until the measured concentration



Fig. 2: The scheme of thermal furnace a) and reactor container b).

of SO₂ is stabilized in the gas outlet. The experiments last up to 50 min. The speed of the gas which flows through the reactor for SO₂ separation was between 0.13-0.14 m/s. The gas velocity provides constant sorbent mass in the reactor. The sorbent mass was measured before and after the process of SO₂ separation from the gas mixture. During the experiment the gas value flow rate through the reactor in order to separate SO₂ was between 1.97-2.03 m³/h.

During the experimental process of SO_2 separation from the gas mixture, the following measuring instruments were used:

Measuring the temperature of the sample (sorbent) layer in the reactor

Instrument: Thermo element Ni-Cr-Ni with digital gauges Fluke 54 –N series

Measurement range: -200-300 °C Measuring error: ±0.2%

Measuring the volume share of O_2 and concentration of SO_2 at the entrance and exit of the reactor

Instrument: Gas analyzer Testo 350 XL

Measurement range: 0-25%

0÷5000 ppm SO₂

Measuring error: for SO₂ je $\pm 5\%$ for concentration range 100-2000 ppm and $\pm 10\%$ for concentration range 2001-5000 ppm,

Measuring error: for O_2 is $\pm 0.8\%$ for the range of 0-25%

Measuring the sample (sorbent) mass

Instrument: Platform scale EMB 500-1 Measurement range: 0-500g Measuring error: ±0.001g

Measuring the air volume flow

Instrument: Rotametar RAGK Measurement range: 0.2-6300 l/h



Fig. 3: The change of SO_2 concentration in a mixture of gases which flows through the reactor without sorbent and adding sorbent depending on the reaction time (m(sorbent) = 100 g, t = 200 °C, $d_p = 600 \mu m$).

Measuring error: ±4%

Measuring the SO₂ volume flow

Instrument: Rotametar RAGK Measurment range: 0.2-6300 l/h Measuring error: ±4%

Measuring the gas mixture volume flow

Instrument: Rotametar RAGK Measurement range: 0.2-6300 l/h Measuring error: ±4%

RESULTS AND DISCUSSION

In Fig. 3 and 4 the SO₂ concentration change in the flue gas which flows through the reactor for SO₂ is shown, without the sorbent and adding the sorbent depending on the reaction time (time of flue gas flow through the reactor) and reaction temperature. As it was expected, the concentration of SO₂ in the outlet gas is the lowest for CaMg(CO₃)₂ sorbent particles.

Being at reaction temperature of approximately 200 °C and mean diameter of sorbent particles $\approx 600 \ \mu m$, the degree of SO₂ absorption to the sample particles occurs in the interval of 65-80% with sorbent CaMg(CO₃)₂, 42-66% with sorbent CaCO₃ and 34-60% with sorbent CaO (Fig. 5).

Increasing the reaction temperature from 200 °C to 400 °C the degree of SO_2 absorption to sorbent particles has no greater influence and it is in the interval of



Fig. 4: The change of SO_2 in a mixture of gases which flows through the reactor without sorbent and adding sorbent depending on the reaction time (m(sorbent) = 100 g, t = 400 °C, $d_p = 600 \mu m$).

37-78% by $CaMg(CO_3)_2$ sorbent utilization, 45-78% by $CaCO_3$ sorbent utilization and 19-60% by CaO sorbent utilization (Fig. 6).

During the first 6 min of the process examination of SO_2 absorption to sorbent particles, all sorbent samples quickly absorbed SO_2 at the studied reaction temperatures. After 6 minutes SO_2 absorption decreases, starts to stabilize and takes an approximately constant value (Fig. 5 and 6).

During the research, the value of stechyiometric relation of calcium in sorbent and sulfur in flue gases (Ca/S) varied and it was above 5.

According to the data from the literature [4,8,11] following mechanisms of direct sulfatization can be recommended:

$$CaMg(CO_3)_2 + SO_2 + \frac{1}{2} \cdot O_2 \rightarrow CaSO_4 + MgO + 2 \cdot CO_2 \quad (1)$$

$$CaCO_3 + SO_2 + \frac{1}{2} \cdot O_2 \rightarrow CaSO_4 + CO_2$$
(2)

$$CaCO_3 + SO_2 + \frac{1}{2} \cdot O_2 \rightarrow CaSO_4 + CO_2$$
(3)

During the direct sulfatization of $CaMg(CO_3)_2$), $CaCO_3$ and CaO (reactions (1) - (3)) the degree of sorbent utilization can be determined with the expression:

$$\eta_{\text{sorbent}} = \frac{M_{\text{sorbent}}}{M_{\text{SO}_2}} \cdot \frac{m_{\text{SO}_2}}{m(\text{sorbent})} \cdot \eta_{\text{SO}_2}, \ (\%)$$
(4)

where:



Fig. 5: The degree of SO₂ absorption to sorbent particles $(m(sorbent) = 100 \text{ g}, t = 200 \text{ }^{\circ}C, dp = 600 \mu m)$.

$$M_{sorbent}$$
 - sorbent molar mass, $\left(\frac{g}{mol}\right)$,
 M_{SO_2} - SO₂ molar mass $\left(\frac{g}{mol}\right)$,

 m_{SO_2} - sulfur dioxide mass in flue gases at the entrance of the reactor (g),

M(sorbent) - sorbent mass (sample), (g),

$$\eta_{SO_2} = \frac{\phi_{SO_2,in} - \phi_{SO_2,out}}{\phi_{SO_2,in}} \cdot 100, \ (\%), - \text{ the degree of}$$

SO₂ absorption to sorbent particles

 $\phi_{SO_2,in}$ – SO₂ volume ratio in flue gas at the entrance of the reactor, (ppm),

 $\varphi_{SO_2,out} - SO_2 - SO_2$ volume ratio in flue gas at the exiting of the reactor, (ppm).

Using the numerical data gained by measurements (Fig. 3-6) and using the Eq. (4), the achieved values of the degree of sorbent utilization at the reaction temperature of 200 °C are low and are up to 14 % for sorbent dolomite, 6 % for sorbent CaCO₃ and 4 % for sorbent CaO. At the reaction temperature of 400 °C the degree of sorbent utilization is slightly lower. The low degree of sorbent utilization is a consequence of consumption of greater mass of sorbent than the mass of SO₂ in flue gases entering the reactor. (Fig. 7 and 8).

CONCLUSIONS

The aim of the SO_2 separation experiment from a mixture of flue gases, which is demonstrated in this paper, was to determine the dependability of SO_2



Fig. 6: The degree of SO_2 absorption to sorbent particles $(m(sorbent) = 100 \text{ g}, t = 400 \text{ °C}, dp = 600 \mu m).$

separation degree from flue gas using different sorbents: dolomite (CaMg(CO₃)₂), calcium carbonate (CaCO₃) and calcium oxide (CaO), the influence of reaction temperature in the reactor and degree determination of sorbent utilization. Because of the previously said the temperatures varied from 200 and 400 °C. The sample mass within the reactor was 100 g and the mean diameter of sorbent particles was $\approx 600 \ \mu\text{m}$. During the examination the following conclusions were made:

(1) It was acknowledged that the increase of the reaction temperature from 200 to 400 °C has no greater impact on SO₂ absorption to CaMg(CO₃)₂ and CaO sorbent particles. When the reaction temperature is somewhere around 200 °C and the mean diameter of sorbent particles is $\approx 600 \ \mu\text{m}$, the degree of SO₂ absorption is in the interval of 65-80% by CaMg(CO₃)₂ sorbent utilization, 42-66% by CaCO₃ sorbent utilization and 34-60% by CaO sorbent utilization. When the reaction temperature is somewhere around 400 °C and it has the same diameter of sorbent particles, the degree of SO₂ absorption is in the interval of 37-78% by CaMg(CO₃)₂ sorbent utilization and 19-60% by CaO sorbent utilization.

(2) During the first 6 min of examination of SO_2 absorption process to the sorbent particles, all sorbent samples quickly absorbed SO_2 at the studied reaction temperatures. This leads to a conclusion that the first 6 min of the process is completely controlled by the chemical reaction on the solid surface of the sorbent. After 6 min, the SO_2 absorption starts to stabilize and takes an approximate constant value (Fig. 5 and 6) and



Fig. 7: The degree of sorbent (sample) utilization depending on the time of flue gas flow through the reactor for SO_2 separation (m(sorbent) = 100 g, t = 200 °C, dp = 600 µm).

leads to a conclusion that the diffusion resistance becomes significant due the thickness of product layer.

(3) Low degree of sorbent utilization is determined: 14 % by dolomite (CaMg(CO₃)₂) utilization, 6 % by calcium carbonate (CaCO₃) utilization and 4 % by calcium oxide (CaO) utilization at the reaction temperature somewhere around 200 °C. When the reaction temperature is somewhere around 400 °C only higher degree of sorbent utilization for calcium carbonate CaCO₃ is marked and it is of 7 %. Low degree of sorbent utilization is due the utilization of great mass of sorbents (samples) in relation to the SO₂ mass entering the reactor.

The attained results of the experiment described in this paper indicate the capability of injecting powdered sorbents $CaMg(CO_3)_2$, $CaCO_3$ and CaO in the areas with lower temperatures as it is the convective part of the furnace and the flue canal of thermal power plant and which aim was to reduce the SO_2 emission in flue gas. The achieved results can also represent the starting point in the phase of equipment designing for FGD as well as the equipment for separation the solid particle, whose practical utilization would improve the energetic and ecological efficiency of thermal-energetic power plants.

Nomenclature

d _p	Sorbent particle diameter, µm
m	The mass of sorbent, g
t	Reaction temperature, °C
$\phi_{SO_2,in}$	Gas flue SO_2 volume ratio in flue gas at
	the entrance of the reactor, ppm



Fig. 8: The degree of sorbent (sample) utilization depending on the time of flue gas flow through the reactor for SO_2 separation (m(sorbent) = 100 g, t = 400 °C, dp = 600 µm).

$\phi_{SO_2,out}$	Gas flue SO ₂ volume ratio in flue
	gas at the outlet of the reactor, ppm
η_{SO_2}	Retention degree of SO ₂ for particle
X	sorbent, %
$\eta_{sorbent}$	Exploitation degree, %

Received : Aug. 19, 2010 ; Accepted : July 4, 2011

REFERENCES

- LIFAC Sorbent Injection Desulfurization Demonstration Project, U.S. Department of Energy, Assistant Secretary for Fossil Energy, Washington , DC 20585, Project Performance Summary Clean Coal Technology Demonstration Program, 6-7, (2004).
- [2] Sorbent Injection SOx Control Combustion Optimization Generation Optimization, U.S.- China NOx and SO₂ Control Workshops Shenyang, Liaoning Province, P.R. China 3-7 November, (2003).
- [3] Klingspor J., Cope D.R., FDG handbook, "Flue Gas Desulphuriastion Systems", IEACoal Research, London, (1987).
- [4] Hallaj R., Nikazar M., Dabir B., Thermogravimetric Study and Modeling of Direct Sulfation of Limestone by Sulfur Dioxide, *Chem. Eng.*, 12, p. 566 (2004).
- [5] Nikazar M., Hallaj R., Rahmani M., Dabir B., Hajaligol M.R., Direct Sulfation of Limestone by Sulfur Dioxide, *Pakistan J. App. Sci.*, 2, p. 158 (2002).

- [6] Manović V., Anthony J.E., Sequential SO₂/CO₂ Capture Enhanced Bysteam Reactivation of a CaO -Based Sorbent, *Fuel*, **87**, p. 1564 (2008).
- [7] Tambe S., Gauri K.L., Li S., Cobourn G., Kinetic Study of SO₂ Reaction with Dolomite, *Environ. Sci. Technol.*, 25, p. 2071 (1991).
- [8] Mahesh V.I., Himanshu G., Bartev B.S., Liang S.F., Multicyclic Study on the Simultaneous Carbonation and Sulfation of High-Reactivity CaO, *Ind. Eng. Chem.*, 43, p. 3939 (2004).
- [9] Stanmore, B. R., Gilot, P., Review Calcination and Carbonation of Limestone During Thermal Cycling for CO₂ Sequestration, *Fuel Processing Technology*, 86, p. 1707 (2005).
- [10] Sima A., Rouein H., Manouchehr N., Study and Kinetic Modeling of the Direct Sulfation of Iranian Limestones by Sulfur Dioxide at High CO₂ Partial Pressures, *Iranian Journal of Chemistry and Chemical Engineering*, 27, p. 45 (2008).
- [11] Fuertes A.B., Velasco G., Fuente E., Alvarez T., Study of the Direct Sulfation of Limestone Particles at High CO₂ Partial Pressures, *Fuel Processing Technology*, **38**, p. 181 (1994).
- [12] Bruce K.R., Gullett B.K., Beach L.O., Comparative SO₂ Reactivity of CaO Derived From CaCO₃ and Ca(OH)₂, *AIChE J.*, **35**(1), p. 37 (1989).
- [13] Pisani R., Moraes D., Removal SO₂ with Particles of Dolomite Limestone Powder in a Binary Fluidized Bed Reactor with Bubbling Fluidization, *Braz. J. Chem. Eng.* 20(2), (2003).
- [14] Yrjas P., Kristiina Iisa K., Hupa M., Comparison of SO₂ Capture Capacities of Limestones and Dolomites under Pressure, *Fuel*, 4(3), p. 395 (1995).