# Extraction-separation of Eu(III)/Th(IV) Ions with a Phosphorylated Ligand in an Ionic Liquid

Karamzadeh, Zinat; Yaftian, Mohammad Reza\*+

Phase Equilibria Research Laboratory, Department of Chemistry, Faculty of Science, University of Zanjan, Zanjan, I.R. IRAN

### Shiri Yekta, Zahra; Nilchi, Abdolreza

NSTRI, P.O. Box 11365-8486 Tehran, I.R. IRAN

### Dolatyari, Leila•

Phase Equilibria Research Laboratory, Department of Chemistry, Faculty of Science, University of Zanjan, Zanjan, I.R. IRAN

**ABSTRACT:** Extraction-separation of Eu(III) and Th(IV) ions from nitrate media into the ionic liquid 1-hexyl-3-methylimidazolium hexafluorophosphate by a phosphorylated salen extractant, bis(chlorophosphoryle)decahydro-2,4-di(2-hydroxyphenyl)benzo[d][1,3,6]oxadiazepine (DPO), is investigated. It is found that Eu(III) ions are extracted via a solvation mechanism, and the extraction of Th(IV) ions proceeds through an ion exchange mechanism. The analysis of the experimental data reveals that the extraction of Eu(III) and Th(IV) ions is taken place by formation of  $Eu(DPO)(NO_3)_3$  and  $Th(DPO)_2(PF_6)_4$  complexes. A significant selectivity towards thorium ions with respect to trivalent lanthanides (lanthanum, europium, and erbium) was observed. Thorium(IV) can be efficiently extracted from nitric acid solutions into the studied ionic liquid in the presence of DPO.

KEYWORDS: Phosphorylated ligand; Ionic liquid; Europium; Thorium; Extraction; Separation.

### INTRODUCTION

One of the main processes in nuclear wastes management is the intra- and inter-group separation of lanthanides and actinides [1,2]. To fulfill this need, several separation strategies have been studied and developed [3]. Liquid–liquid extraction is among the known efficient techniques for separation and concentration of these metal ions. Selection of the extractant and organic solvent used in such process play a key role for achieving to an efficient separation design. In many cases these technique involves the use of toxic

non-volatile, nonflammable, thermally stable solvents. These

characteristics allow they play important role in green

chemistry [4]. RTILs are widely used as replacements for

traditional organic solvents in separation processes [5].

They have been used for the extraction and separation

of a variety of organic species [6] and metal ions [7-11].

Room-Temperature Ionic Liquids (RTILs) are

and hazardous organic solvents.

<sup>\*</sup> To whom correspondence should be addressed.

<sup>+</sup> E-mail: yaftian@znu.ac.ir

Other Address: Department of Chemistry, Zanjan Branch, Islamic Azad University, Zanjan, I.R. IRAN 1021-9986/16/2/89 7/\$/2.70

Knowing the dissimilarities in the behaviour of ionic liquids with conventional organic solvents [12] and by considering the potential of phosphorus bearing molecules [1-3], few studies have recently been concerned on the extraction of lanthanides and actinides by phosphorylated ligands into ionic liquids. For example, Visser et al. [13] have studied the extraction of uranyl ions with n-octyl(phenyl)-N,Ndiisobutylcarbamoylmethylphosphine oxide (CMPO) tri-*n*-butylphosphate (TBP) and into 1-butyl-3methylimidazolium hexafluorophosphate and 1-octyl-3methylimidazolium bis(trifluoromethanesulfonyl)imide from aqueous acidic media. This study showed an enhancement of UO22+ extraction when RTILs are used in comparison with the results obtained by using conventional diluents. The analysis of the extraction data reveals that, the extraction of uranyl ions into ionic liquids are occurred via the formation of cationic species  $UO_2(NO_3)(CMPO)^+$ , while the extracted species in dodecane were neutral complexes UO2(NO3)2(CMPO)2. The employment of ionic liquids has also been reported for the extraction of Am(III), Pu(IV), U(VI) and Th(IV) ions from nitric acid [14]. A cation exchange mechanism for the extraction of trivalent lanthanides by dissolving CMPO in 1-butyl-3-methylimidazolium hexafluorophosphate is reported by Nakashima et al.[15]. Srinivasan et al. [16] have studied the extraction of Am(III) ions from nitric acid medium by the extractants applied in TRUEX process into 1-butyl-3methylimidazolium bis(trifluoromethanesulfonyl)imide ([C<sub>4</sub>mim][NTf<sub>2</sub>]). The stoichiometry of the extracted complexes was determined CMPO-TBP/[C4mim][NTf2] which was similar with that found in conventional TRUEX process. Recently, Srinivasan et al. [17] have also shown the extraction behavior of a mixture of CMPO and TBP in the room temperature ionic liquid  $[C_4 mim][NTf_2]$  for the extraction of europium(III) ions from nitric acid medium. The distribution ratio of Eu(III) in CMPO-TBP/[C4mim][NTf2] was measured as a function of various parameters such as the concentration of nitric acid, europium ions, CMPO, and TBP, as well as temperature.

In continuation of our studies concerning on the extraction-separation of europium(III) and thorium(IV) ions by a variety of ionophores including phosphorylated extractants [18-24], we have recently reported the application of a room-temperature ionic liquid for such



Bis(chlorophosphoryle)decahydro -2,4- di(2-hydroxyphenyl) benzo[d][1,3,6]oxadiazepine (DPO)



1-Hexyl-3-methylimidazolium hexafluorophosphate (IL, n=4)

goal [10]. It is noteworthy that in many investigations Eu(III) and Th(IV) ions have been selected because they are used as models for trivalent and tetravalent actinides, respectively [25]. In the present paper, the extraction of Eu(III) and Th(IV) ions by using a new phosphorylated ligand, bis(chlorophosphoryle)decahydro-2,4-di(2hydroxyphenyl)benzo[d][1,3,6]oxadiazepine (DPO), dissolved in an ionic liquid (**IL**) named 1-hexyl-3methylimidazolium hexafluoro phosphate is reported.

# **EXPERIMENTAL SECTION**

# Chemicals

1-Hexyl-3-methylimidazolium hexafluorophosphate  $([C_6 mim^+][PF_6^-]),$ abbreviated as IL was from Kimia Exir Chemical (Iran). Company Bis(chlorophosphoryle)decahydro -2,4di(2hydroxyphenyl)benzo[d][1,3,6]oxadiazepine (DPO) has been prepared and characterized according to the procedure reported by Hosseini Monfared et al. [26]. Nitric acid and sodium nitrate (Merck) were the highest purity available grade. Stock solution of thorium (0.01 mol/L) was prepared by dissolving a proper quantity of tetrahydrated thorium nitrate (Fluka) in distilled water. For preparing the stock solution of lanthanides (0.01 mol/L), a weighed quantity of the corresponding oxide (Fluka) was dissolved in nitric acid and then diluted appropriately with distilled water. As the nitrate salts

Solvent	Eu(III) %		Th(IV) %	
	Without DPO	With DPO <sup>a</sup>	Without DPO	With DPO <sup>b</sup>
IL	С	25	37	100
Carbon tetrachloride	С	7	8	71
Chloroform	С	4	8	54
Dichloromethane	С	С	9	60
1,2-Dichloroethane	С	5	7	63

Table 1: Extraction percentage of Eu(III) and Th(IV) ions from sodium nitrate aqueous solution (1 mol / L) adjusted at pH 2.5, into the studied ionic liquid (IL) and some conventional solvents, after 60 min magnetically stirring at 20°C.

a) 0.01 mol/L; b) 0.001 mol/L; c) non-detectable

used for preparation of thorium and lanthanides solutions were not primary standard materials, the stock solutions were standardized. The standardization of the stock solutions was performed by complex formation titration using EDTA (Merck) at pH 2 in the presence of Pyrocathecol violet (Fluka) for thorium and at pH 7 in the presence of Eriochrome black T (Merck) for lanthanides [27]. A  $6.4 \times 10^{-4}$  mol/L solution of ArsenazoIII (Fluka) was used for spectrophotometric determination of thorium and europium ions [28].

### Apparatus

A HACH spectrophotometer (DR 5000, Canada) was used for uv-vis spectrometric measurements. The pH adjustments were performed by a Metrohm digital pH meter (model 780, Switzerland) equipped with a combined glass electrode. Temperature of the extraction vessels was controlled using a Julabo MP5 thermostate water circulator. An inductively coupled plasma optical emission spectrometry (ICP-OES, Spectro-Genesis, Germany) was used for the determination of Th(IV), La(III), Eu(III) and Er(III) ions in their mixtures in competitive extraction experiment.

### Extraction procedure

The solvent extraction experiments were carried out in stoppered glass tubes immersed in a thermostated water bath  $(20\pm1^{\circ}C)$  using 5 mL aqueous phase in contact with 1 mL of organic phase including **IL**. It is confirmed that the extraction equilibrium was reached after 35 min magnetically stirring. After separation of the two phases, by centrifugation, the concentration of cation remaining in the aqueous phase was measured spectrophotometrically using ArsenazoIII as indicator. In the selectivity investigation the concentration of Th(IV), La(III), Eu(III) and Er(III) ions in their mixture was determined by ICP.

# **RESULTS AND DISCUSSION**

# Extraction of Eu(III) and Th(IV) ions by DPO in IL and conventional solvents

Extraction of europium and thorium ions in the presence of DPO into the Ionic Liquid IL, and into the conventional organic solvents including carbon tetrachloride. dichloromethane chloroform. and 1,2-dichloroethane has been investigated (Table 1). Because of the lower efficiency of DPO towards europium ions with respect to thorium ions, the concentration of DPO used for the europium ions was higher that used for thorium ions.

The results demonstrate the importance of the studied ionic liquid in the extraction of both ions. In addition the presence of DPO enhances markedly the extraction percentage of thorium ions in all solvents, and increases the extraction of europium ions in **IL**. It is also seen that the extraction process into the studied solvents shows a significant selectivity towards thorium ions.

### Effect of aqueous phase pH

The possible protonation of DPO has enforced to study the effect of aqueous phase pH on the extraction efficiency. To this end, the extraction of Eu(III) and Th(IV) ions from aqueous nitrate media as a function of aqueous phase pH into the studied ionic liquid



Fig. 1: Variation of extraction percentage vs. pH for extraction of Eu(III) and Th(IV) ions  $(1 \times 10^{-4} \text{ mol/L})$  from sodium nitrate solution (1 mol/L) into IL in the presence DPO (0.01 and 0.001 mol/L for the extraction of Eu(III) and Th(IV) ions, respectively) after 60 min magnetically stirring, at 20°C.



Fig. 2: Variation of extraction percentage versus pH for the the extraction of Eu(III) (A) and Th(IV) (B) ions  $(1 \times 10^4 \text{ mol/L})$  at different sodium nitrate concentration into IL, stirring time 60 min, at 20°C.

in the presence of DPO has been investigated (Fig. 1). A significant pH dependency at pH values <2 was observed for the extraction of europium and thorium ions into the studied ionic liquid. This behavior can be attributed to the protonation of DPO molecules at the lower pH values inferior to 2. This pH was used for continuing the experiments. This selection was done because the maximum extraction percentage of both thorium and europium ions can be achieved at this pH. In addition nuclear wastes, as many other industrial effluents, are usually acidic and it is important to examine an extraction procedure in acidic conditions.

### Effect of nitrate concentration

Extraction via solvation is the mechanism assumed for the extraction of Eu(III) and Th(IV) ions by the neutral ligand DPO in **IL**. In this case the anion accompanying the compelexed cation plays a decisive role for enhancing the extraction efficiency. In order to verify this effect, the extraction of the studied ions from sodium nitrate solution with different concentrations into DPO in **IL** has been performed. The results (Fig. 2) show that, although the extraction of europium ions is influenced by the nitrate concentration, the extraction of thorium ions does not depend on this parameter. As the nuclear waste solutions contain nitrate ion, a concentration of 1 mol/L was selected for performing the experiments.

#### Characterization of the extracted species

The results in previous section allow considering a mechanism via solvation for the extraction of europium ions by DPO dissolved in **IL**. In fact, in this case the ionic liquid plays a role as a polar diluent and it is not participated in the extracted species of europium ions. In contrast, the independency on the nitrate ion concentration permits to propose an ion exchange process for the extraction of thorium ions. These conclusions conduct to suggest the following extraction reactions for the extraction of the studied ions:

$$\operatorname{Eu}_{\mathrm{aq}}^{3+} + 3\operatorname{NO}_{3,\mathrm{aq}}^{-} + \operatorname{nDPO}_{\mathrm{IL}} \rightleftharpoons \operatorname{Eu}(\operatorname{DPO})_{\mathrm{n}}(\operatorname{NO}_{3})_{3,\mathrm{IL}}$$
(1)

$$Th_{aq}^{4+} + mDPO_{IL} + 4C_6 mim^+ PF_{6,IL}^- \rightleftharpoons T$$
(2)

$$h(DPO)_m(PF_6)_{4,IL} + 4C_6mim_{aq}^+$$

where the subscribers " $_{aq}$ " and " $_{IL}$ " denote the phase, aqueous or ionic liquid, in which the species are presented.



Fig. 3: Variation of logD vs. log[DPO] for the extraction of Eu(III) and Th(IV) ions  $(1 \times 10^{-4} \text{ mol/L})$  from sodium nitrate aqueous phase (1 mol/L), at pH 1.5, stirring time 60 min, at 20°C.



Fig. 4: Variation of the extraction percentage of Th(IV) ions from aqueous sodium nitrate solutions (1 mol/L) into IL containing DPO (0.001 mol/L) at pH 2, at 20°C.



Fig. 5: Effect of nitric acid concentration on the extraction of Th(IV) ions into IL containing DPO (0.01 mol/L), stirring time 35 min, at 20°C.

In order to determine the number of molecules of DPO in the extracted Eu(III) and Th(IV) complexes the conventional log-log analysis was used [10]. Based on these results (Fig. 3) the values of "n" and "m" in the above mentioned equations was found to be 1 and 2, respectively.

### Time dependency of the process

Time dependency of the extraction of thorium ions into ionic liquid **IL** in the presence of DPO from sodium nitrate solution (1 mol/L) was verified (Fig. 4). It is found that the extraction equilibrium of thorium ions is achieved after 35 minutes. This relatively long time requirement for the extraction into **IL** is already encountered for the extraction of metal ions into the ionic liquids [10]. Thus 35 min was selected as the time required for achieving to an equilibrium condition.

# Extraction<sup>2</sup> of Eu(III) and Th(IV) ions from nitric acid solutions

One requirement for an extraction process employed in waste management is its ability in acidic media. In order to investigate this potential of the proposed processes, the extraction of Th(IV) and Eu(III) ions from nitric acid solutions was performed. The obtained results (Fig. 5) show, although the extraction percentage of Th(IV) ions by the studied ionic liquids was not altered by the presence of NaNO<sub>3</sub>, the extraction of these ions from nitric acid solutions decreases by the acid concentration. This is a consequence of the enhancement of the competition between hydrogen and thorium ions. These results present the ability of the proposed extraction procedure for extraction thorium ions from high nitric acid concentration. Due to the very week extraction of Eu(III) ions into IL, the results do not reported.

#### Selectivity

Although individual single ion extraction experiments allow estimating the extraction performance of an extractant, a real evaluation of the extraction efficiency and selectivity of a ligand can be provided by performing competitive extraction experiments. The results of the extraction of lanthanum, europium, erbium and thorium ions (each  $1 \times 10^{-4}$  mol/L) from sodium nitrate solution (1 mol L<sup>-1</sup>) into **IL** solution of DPO (0.01 mol/L)



Fig. 6: Results of a competitive extraction of lanthanium, europium, erbium and thorium ions  $(1 \times 10^{-4} \text{ mol/L})$  from sodium nitrate solution (1 mol/L) by DPO (0.01 mol/L) in IL, stirring time 35 minutes.

adjusted at pH 2 are presented in Fig. 6. The order of the extraction selectivity was found to be Th(IV) >> Er(III) > Eu(III)  $\approx$  La(III). A significant selectivity towards thorium ions with respect to the investigated lanthanides was demonstrated by the solution of DPO dissolved in **IL**.

### CONCLUSIONS

A solution formed by dissolving bis(chlorophosphoryle) decahydro-2,4-di(2-hydroxyphenyl) benzo[d] [1,3,6] oxadiazepine (DPO) into ionic liquid 1-hexyl-3-methylimidazolium hexafluorophosphate can be used for extraction-separation of thorium and europium ions from nitrate media. A neutral extraction (extraction via solvation) was suggested for the europium ions, whereas thorium ions have been extracted with an ion exchange mechanism. An excellent selectivity for the extraction of thorium with respect to some lanthanides has been found. The extraction of thorium and europium ions from nitric acid solutions shows the ability of DPO/IL mixture for removal of thorium ions from such solutions.

Received : Apr. 25, 2015 ; Accepted : Dec. 7, 2015

# REFERENCES

- Marinsky, J. A., Marcus, Y. (Eds), "Ion Exchange and Solvent Extraction", Marcel Dekker, New York (1974).
- [2] Dam, H. H., Reinhoudt, D. N., Verboom, W., Multicoordinate Ligands for Actinide/Lanthanide Separations, Chem. Soc. Rev., 36: 367-377 (2007).

- [3] Chipmen, N. A., Wai, C. M. (Eds), "Separation Techniques in Nuclear Waste Management", CRC, Florida (1996).
- [4] Rogers, R. D., Seddon, K. R., Volko, S. "Green Industrial Applications of Ionic Liquids", Springer, Dordrecht (2012).
- [5] Billard I., Ouadi A. Gillard C., Liquid-Liquid Extraction of Actinides, Lanthanides, and Fission Products by Use of Ionic Liquids: from Discovery to Understanding, Anal. Bioanal. Chem., 400: 1555-1566 (2012).
- [6] Poole C.F., Poole S.K., Extraction of Organic Compounds with Room Temperature Ionic Liquids, J. Chromatogr. A, 1217: 2268-2286 (2010).
- [7] Rout A., Venkatesan K.A., Srinivasan T.G., Vasudeva Rao P.R., Liquid-Liquid Extraction of Pu(IV), U(VI) and Am(III) Using Malonamide in Room Temperature Ionic Liquid as Diluent, J. Hazard. Mater., 221-222: 62-67 (2012).
- [8] Wellens S., Goovaerts R., Möller C., Luyten J., Thijs B., Binnemans K., A Continuous Ionic Liquid Extraction Process for the Separation of Cobalt from Nickel, Green Chem., 15: 3160-3164 (2013).
- [9] Hoogerstraete T.V., Onghena B., Binnemans K., Homogeneous Liquid–Liquid Extraction of Metal Ions with a Functionalized Ionic Liquid, J. Phys. Chem. Lett. 4: 1659-1663 (2013).
- [10] Shiri-Yekta Z., Yaftian M.R., Nilchi A., Extraction-Separation of Eu(III) and Th(IV) Ions from Nitrate Media Into A Room-Temperature Ionic Liquid, *J. Iran. Chem. Soc.*, **10**: 221-227 (2013).
- [11] Bahar S., Zakerian R., Ionic Liquid Based Dispersive Liquid Liquid Microextraction and Enhanced Determination of the Palladium in Water, soil and Vegetable samples by FAAS, *Iran. J. Chem. Chem. Eng. (IJCCE)*, **33**(4): 51-58 (2014).
- [12] Dai S., Ju Y.H., Barnes C.E., Solvent Extraction of Strontium Nitrate by a Crown Ether Using Room-Temperature Ionic Liquids, J. Chem. Soc. Dalton Trans, 8: 1201-1201 (1999).
- [13] Visser, A. E., Jensen, M. P., Laszak, I., Nash, K. L., Choppin, G. R., Rogers, R. D., Uranyl Coordination Environment in Hydrophobic Ionic Liquids: An in Situ Investigation, *Inorg. Chem.* 42: 2197-2199 (2003).

- [14] Visser A.E., Rogers R.D., Room-Temperature Ionic Liquids: New Solvents for F-Element Separations and Associated Solution Chemistry, J. Solid. State. Chem. 171: 109-113 (2003).
- [15] Nakashima K., Kubota F., Maruyama T., Goto M., Feasibility of Ionic Liquids As Alternative Separation Media for Industrial Solvent Extraction Processes, Ind. Eng. Chem. Res. 44: 4368-4372 (2005).
- [16] Rout A., Venkatesan K.A., Srinivasan T.G., Vasudev Rao, P. R., Extraction of Americium(III) from Nitric Acid Medium by CMPO-TBP Extractants in Ionic Liquid Diluents, *Radiochim. Acta* 97: 719-725 (2009).
- [17] Rout V., Venkatesan K.A., Srinivasan T.G., Rao P.R.V., Extraction and Third Phase Formation behavior of Eu(III) in CMPO–TBP Extractants Present in Room Temperature Ionic Liquid, Sep. Purif. Technol. 76: 238-243 (2011).
- [18] Yaftian M.R., Burgard M., Wieser C., Dieleman C.B., Extractive Properties Towards Rare-Earth Metal Ions of Calix[4]Arenes Substituted at the Narrow Rim by Phosphoryl and Amide Groups, *Solvent Extr. Ion Exch.* 16: 1131-1149 (1998).
- [19] Zamani A.A., Yaftian M.R., Solvent Extraction of Thorium, Lanthanum and Europium Ions by Bbis(2-Ethylhexyl)Phosphoric Acid Using 2-Nitrobenzo18crown6 as Ion Size Selective Agent, Sep. Purif. Technol., 40: 115-121 (2004).
- [20] Yaftian M.R., Hassanzadeh L., Eshraghi M.E., Matt D., Solvent Extraction of Thorium(IV) and Europium(III) Ions by Diphenyl-N,Ndimethylcarbamoylmethylphosphine Oxide from Aqueous Nitrate Media, Sep. Purif. Technol., 31: 261-268 (2003).
- [21] Yaftian M.R., Eshraghi M.E., Hassanzadeh L., Extractive Properties of Tri-*n*-Octylphosphine Oxide Towards Thorium(IV) and Europium(III) Ions from Nitrate Media, *Iran. J. Chem. Chem. Eng. (IJCCE)*, 22(1): 71-76 (2003).
- [22] Yaftian M.R., Taheri R., Zamani A.A., Matt D., Thermodynamics of the Solvent Extraction of Thorium and Europium Ions by Neutral Phosphorylated Ligands, J. Radioanal. Nucl. Chem. 262: 255-259 (2004).

- [23] Yaftian M.R., Zamani A.A., Rostamnia S., Thorium (IV) Ion-Selective Transport Through a Bulk Liquid Membrane Containing 2-Thenoyltrifluoroacetone as Extractant-Carrier, Sep. Purif. Technol., 49: 71-75 (2006).
- [24] Yaftian M.R., Razipour M.R., Matt D., Thorium(IV) and Europium(III) Ions extraction by Phosphorylated Calix[4]Arene in Dichloromethane, *J. Radioanal. Nucl. Chem.*, 270: 357-361 (2006).
- [25] Arnaud-Neu, F., Browne, J. K., Byrne, D., Marrs, D. J., McKervey, M. A., O'Hagan, P., Schwing-Weill, M. J., Walker, A., Extraction and Complexation of Akali, Alkaline Earth, and F-Element Cations by Calixaryl Phosphine Oxides, *Chem. Eur. J.* 5: 175-186 (1999).
- [26] Hosseini-Monfared, H., Ghorbanloo, M., Janiak, C., Mayer, V., Intramolecular Diastereoselective Cascade Cyclization Reaction of N.N'-Bis(Salicylidene)Cyclohexanediimine with Phosphoryltrichloride to a Bis(Chlorophosphorylated)Decahydro-2,4-di(2-Hydroxyphenyl) Benzo-[d][1,3,6]Oxadiazepine, Phosphorus Sulfur, and Silicon, 189: 226-234 (2014).
- [27] Dean J.A., "Analytical Chemistry Handbook" McGraw-Hill: New York (1995).
- [28] Marczenko Z., "Spectrophotometric Determination of Elements", Wiley: New York (1976).