# EFFECT OF GRAIN BOUNDARY CHARACTER ON FRACTURE IN COLUMNAR GRAINED Ni<sub>3</sub>AI DURING COLD ROLLING<sup>\*</sup>

# K. JANGHORBAN<sup>1\*\*</sup>, F. MAHZOON<sup>1</sup>, Y. UMAKOSHI<sup>2</sup> AND T. SHIBAYANAGI<sup>3</sup>

<sup>1</sup>Dept. of Materials Science and Eng. Shiraz University, Shiraz, I. R. of Iran <sup>2</sup>Department of Materials Science and Eng. Graduate School of Engineering, Osaka University, Japan <sup>3</sup>Welding and Joining Research Institute, Osaka University, Japan

Abstract – Polycrystalline Ni<sub>3</sub>Al with a columnar grained structure was grown unidirectionally by the floating zone method at a rate of 20 mm/h. Grain boundary structure was characterized by  $\Sigma$  values determined from grain orientations of two adjacent grains using a coincidence lattice theory. Two types of specimens PD and ND, whose cold-rolling directions were parallel and perpendicular to the crystal growth direction, were prepared. Workability and fracture behavior of PD and ND specimens were examined focusing on the effect of the grain boundary character on fracture. PD specimens showed the better workability than ND specimens. Low angle and coincidence boundaries exhibited a strong resistance to grain boundary fracture, while random boundaries were harmful to crack initiation and propagation.

Keywords- Unidirectional solidification, floating zone, texture, coincidence site lattice, coincidence boundary, Svalue

## **1. INTRODUCTION**

Grain boundary embrittlement in  $Ni_3Al$  alloys is a serious problem which should be overcome before industrial application. Many attempts to improve brittle grain boundary fractures have been made by microand macro-alloying [1-6]. A small amount of boron addition has been found to be most effective in improving the tensile ductility of  $Ni_3Al$  [1, 2].

The ductility of binary Ni<sub>3</sub>Al alloys was found to be improved by controlling the grain shape: tensile elongation of cast Ni<sub>3</sub>Al alloy containing 24 at %Al increased from 1.2% to 14.1% with a change in grain shape from equiaxed to columnar grains [7]. Stoichiometric Ni<sub>3</sub>Al with a columnar grained structure and strong <111> texture, which was unidirectionally grown by using the floating zone method, showed 17% elongation at room temperature without the boron addition [8]. Furthermore, by controlling the crystal growth rate and alloy composition, the columnar grained Ni<sub>3</sub>Al alloys exhibited a large tensile elongation of over 70% at room temperature [9] and could be cold rolled to 25% reduction [10]. The nature of the grain boundary is known to be very important for controlling and improving mechanical, chemical and physical properties of polycrystalline materials [11]. Several approaches have been made to improve these properties by controlling the grain boundary character, which is evaluated using  $\Sigma$  values based on the coincidence site lattice (CSL) theory [12, 13].

The CSL can be obtained by allowing the two misoriented crystal lattices adjoining the boundary (crystal I and crystal II) to interpenetrate and translate so that lattice points of each crystal coincide [14]. The space lattice, made up of the coincident lattice is called CSL. The fraction of lattice points in one crystal in good coincidence is defined as  $1/\Sigma$ . A grain boundary can then be constructed by passing a plane through the interpenetrating crystals and placing all the lattice sites from one crystal on one side of the boundary plane and from the second crystal on the other side of the boundary plane. The reciprocal of the ratio of CSL sites to lattice sites of one of the crystals is denoted by  $\Sigma$ . In general,  $\Sigma$  is large, but for certain boundary

<sup>\*</sup>Received by the editors March 16, 2002 and in final revised form January 13, 2003

<sup>\*\*</sup>Corresponding author

misorientations it is small [15]. For example,  $\Sigma$  is seen to be 5 for the CSL of Fig.1. The broken lines in Fig.1 denote the (110) planes that terminate at the boundary; they show that the boundary can be considered as a wall of  $\frac{1}{2}(110)$  edge dislocations. The dislocation spacing is only  $\frac{1}{4}(130)$ , however, and they bear little resemblance to isolated crystal orientations. The CSL is fundamental to the understanding of the presence of order in high angle grain boundaries. A CSL will occur if each axis of coordinates is simultaneously rotated to become parallel to an original vector [u,v,w] and shares fraction  $1/\Sigma$  common lattice points with it [16]. Coincident site lattices occur at specific values of  $1/\theta$  (axis of misorientation/angle of misorientation), giving rise to a continuous set of structure sites across the boundary. A familiar example of a CSL is the case of a twin in the cubic system. Here a CSL is developed with an overall density of 1 in 3 (written as  $\Sigma=3$ ). Depending on the orientation of the boundary plane, the density of common sites may be 1 in 1 on the coherent twin plane and 1 in 3 for an incoherent segment [17].



Fig.1. (a) Schematic illustration of the atom positions on a (001) plane in two face-centered cubic crystals separated by a (310) boundary with Σ=5. The unit cells are shown in bold outline. The misorientation angle about [001] is 37° (or alternatively 53°). The projection of atoms on planes immediately above and below the diagram are omitted for clarity. (b) The two lattices of (a) superimposed to show coincident sites, marked as half-filled circles. The unit cell of the CSL is indicated by broken lines on the left, and the DSC lattice is shown on the right [15]

In this paper we describe the effect of the grain boundary character on workability and grain boundary fracture in unidirectionally grown Ni<sub>3</sub>Al polycrystals with a columnar grained structure during cold rolling.

## 2. EXPERIMENTAL PROCEDURE

A master ingot of Ni<sub>3</sub>Al with a stoichiometric composition was prepared by arc melting. Polycrystalline Ni<sub>3</sub>Al with a columnar grained structure was grown unidirectionally from the ingot by the floating zone method at a rate of 20 mm/h under a high purity argon gas flow. Two types of PD and ND specimens whose rolling planes were chosen to be parallel and perpendicular to the crystal growth direction, respectively, *W.SID.ir* 

were prepared by spark machining. The rolling directions for PD and ND specimens were chosen to be parallel and perpendicular to the growth direction, respectively. Cold rolling was carried out at room temperature by about 5% reduction for each pass.

Orientation of grains was measured using the scanning electron microscope (SEM)- electron channeling pattern (ECP) technique before cold rolling. Grain boundary structure was characterized by  $\Sigma$  values determined from the SEM-ECPs of two adjacent grains. Brandon's condition was used as the criterion for the exact coincidence orientation relationship [18]. Microstructures and cracks were examined after cold rolling using SEM. Work hardening of cold rolled specimens was monitored by micro Vicker's hardness measurement.

## **3. RESULTS AND DISCUSSION**

In unidirectionally grown Ni<sub>3</sub>Al by the floating zone method, a columnar grained structure was obtained in which grains elongated to the crystal growth direction. Figure 2 shows the schematic illustration of grains of a PD specimen before cold rolling. The columnar grains elongate to the crystal growth direction. This specimen was repeatedly cold rolled to the growth direction. Figure 3 shows a schematic illustration of a ND specimen before cold rolling. The bold line shows the  $\Sigma 1$  boundary and the numbers near the grain boundaries represent  $\Sigma$  values of the coincidence boundaries. The shade grains have the normal direction tilted less than 20° from <001>. On the cross section perpendicular to the growth direction, coincidence boundaries and random boundaries are 55.4% and 44.6% of the total number of grain boundaries, respectively. For coincidence boundaries, 42.3% and 3.6% of all the observed boundaries are  $\Sigma 1$  and  $\Sigma 3$  boundaries, respectively. Almost all grains are unidirectionally oriented to <001> direction. Similar strong <001> textured columnar grains in a Ni-24 at %AI-0.2 at %B alloy were produced by directional levitation zone melting [7], while <111> texture was reported in unidirectionally grown Ni-24 at %AI at 24mm/h [8]. Since <001> texture is known to develop in nickel base superalloys during directional solidification, preferential growth parallel to <001> may be a general tendency in Ni<sub>3</sub>AI alloy.







Fig. 3. Schematic illustration of grains of a ND specimen before cold rolling. The marks on the figure have similar meaning to those in Fig. 2

www.SID.ir

#### K. Janghorban / et al.

For a PD specimen cold rolled to the growth direction, no severe cracks were observed to a 10% reduction in thickness. As the rolling advances, a crack is initiated and propagates depending on grain boundary character as shown in Fig. 4. Random boundaries seem to be sensitive to cracking by comparison with Fig.2. Although the crack propagation may be heavy depending on grain boundary character, the whole specimen can deform to 42.3% without separating into small blocks. PD specimens show better workability in cold rolling than ND specimens. The columnar grained Ni<sub>3</sub>Al was also reported to exhibit a large tensile elongation in the crystal growth direction at room temperature, accompanied by intergranular fracture at peculiar grains [8, 9]. The workability of polycrystalline materials is known to be influenced by such factors as grain orientations, grain boundary character and rolling direction. The effect of grain boundary character in columnar grained Ni<sub>3</sub>Al was examined using an ND specimen. As shown in Fig. 5, intergranular cracks are seen in a cold rolled ND specimen depending on grain boundary character. Heavy cracks are observed at random boundaries, while small cracks are formed at  $\Sigma 1$  and  $\Sigma 3$  coincidence boundaries, but further propagation is suppressed.



Fig. 4. SEM image of a PD specimen cold rolled to 23.3% reduction



Fig. 5. Cracks and grain boundary character in an ND specimen cold rolled to 22.6% reduction. R and the numbers represent the random boundary and  $\Sigma$  value of coincidence boundary, respectively

Figure 6 shows variation in the number of cracked grain boundaries in measured 222 grain boundaries as the thickness of the specimen is reduced. The data of Figs. 6 and 7 was collected by taking several SEM micrographs similar to that of Fig. 5, and 222 grain boundaries were statistically studied. Random and  $\Sigma$ boundaries were identified, then the samples were cold rolled and cracked boundaries were recorded. At the initial stage of cold rolling, some cracks are observed in a few of the grain boundaries. The frequency of cracked grain boundaries increased with reduction in thickness accompanied by a sharp increase at over 20% reduction. Crack initiation and propagation are known to be very sensitive to grain boundary character. Figure 7 shows change in the frequency of coincidence and random boundaries in cracked grain boundaries. This figure was constructed by detecting the number of cracks and the type of grain boundary in which they occurred. Most cracks occurred in random boundaries at any tested reduction in thickness, while low angle and coincidence boundaries showed good resistance to intergranular fracture. Average micro Vickers hardness in several <001> oriented columnar grains linearly increased from 170 to 500 with cold rolling. A sharp increase in the number of cracked boundaries at above 20% reduction occurred in not only random boundaries, but in coincidence boundaries too. With a reduction of 22.5%, grains were strongly workhardened, and therefore the residual stress might exceed the strength at the coincidence grain boundary. Frequent crack initiation and propagation at low angle and coincidence boundaries at a reduction of over www.SID.ir 22.5% resulted in the fracture of the ND specimen.



Most recently it was found that grain boundaries in Ni<sub>3</sub>Al are not intrinsically brittle, but that brittleness is due to an extrinsic factor such as a hydrogen induced environmental effect [6, 19]. The most effective means of suppressing the grain boundary embrittlement is the addition of a small amount of boron, since the diffusion path can be interrupted by a boron dopant. In general, grain boundary diffusion is more enhanced in random boundaries than in low angle and/or coincidence boundaries. In aluminium [20], stainless steel [21] and niobium [22], low angle and some coincidence boundaries were reported to be resistant to corrosion by sulfuric acid. Low angle and some coincidence boundaries with low energy generally show high fracture strength. In Ni<sub>3</sub>Al the coincidence boundaries have been found to show less sensitivity to intergranular fractures than random boundaries [23, 24]. The shape and size of grains are known to be important factors for ductility [25]. Although the effect of rolling direction on workability of columnar grained Ni<sub>3</sub>Al was observed in the present study, there was no significant evidence of the grain size dependence on grain boundary embrittlement. The most important factor for the intergranular fracture is the grain boundary character and its spatial distribution. The development of microalloying and favorable fabrication processes to obtain high frequencies of low angle and coincidence boundaries with low  $\Sigma$  values are necessary to improve grain boundary embrittlement in Ni<sub>3</sub>Al alloys.

## 4. CONCLUSIONS

The effect of grain boundary character on intergranular fractures in columnar grained Ni<sub>3</sub>Al during cold rolling was examined and the following conclusions were reached:

- A columnar grained structure with a high frequency of low angle and coincidence grain boundaries is obtained in Ni<sub>3</sub>Al, unidirectionally grown by the floating zone method. The columnar grained Ni<sub>3</sub>Al can be cold rolled to 22.5% and 42.5% reduction in thickness in the rolling directions parallel and perpendicular to the crystal growth direction, respectively, accompanied by the intergranular fracture. The workability depends on the rolling direction; it is more improved in the rolling to the elongated direction of columnar grains.
- 2. Susceptibility to intergranular fracture depends strongly on the grain boundary character. Coincidence boundaries with low  $\Sigma$  values show good resistance to crack formation, while crack initiation and propagation dominantly occur in random boundaries from an early stage of cold rolling.

*Acknowledgment-* The authors would like to thank the Amada Foundation for Metal Work Technology for a research grant. Ms. F. Mahzoon is very grateful to the Umakoshi Laboratory personnel for their technical assistance.

#### K. Janghorban / et al.

### REFERENCES

- 1. Aoki, K. & Izumi, O. (1979). Improvement of room temperature ductility of the L12 intermetallic compound Ni<sub>3</sub>Al by boron addition. *J. Japan Inst. Metals*, *43*, 1190.
- Liu, C. T., White, C. L. & Horton, J. A. (1985). Effect of Boron on Grain-Boundaries in Ni<sub>3</sub>Al. *Acta Metall.*, 33, 213.
- Takasugi, T., Masahashi, N. & Izumi, O. (1986). Improved ductility and strength of Ni<sub>3</sub>Al compound by beryllium addition. *Scripta Metall.*, 20, 1317.
- Chiba, A., Hanada, S., Watanabe, S., Abe, T. & Obana, T. (1994). Relation between ductility and grain boundary character distribution in Ni<sub>3</sub>Al. *Acta. Metall. Mater*, 42(5), 1733.
- Chiba, A., Hanada, S. & Watanabe, S. (1992). Improvement in ductility of Ni<sub>3</sub>Al by *γ*-former doping. *Mater. Sci.* Eng., A152, 108.
- George, E. P., Liu, C. T. & Pope, D. P. (1996). Mechanical behavior of Ni<sub>3</sub>Al: Effect of environment, strain rate, temperature and boron doping. *Acta Mater.*, 44,1757.
- 7. Liu, C. T. (1988). High temperature ordered intermetallic alloys III, MRS symp. Proc. MRS Symp. Proc., 122, 429.
- Hirano, T. (1990). Improvement of room-temperature ductility of stoichiometric Ni<sub>3</sub>Al by unidirectional solidification. *Acta Metall. Mater.*, 38, 2667.
- 9. Mawari, T. & Hirano, T. (1995). Effects of unidirectional solidification conditions on the microstructure and tensile properties of Ni<sub>3</sub>Al. *Intermetallics*, *3*, 23.
- Hirano, T. & Mawari, T. (1992). Ductility improvement of Al-rich Ni<sub>3</sub>Al by unidirectional solidification. *Scripta Metall. Mater.*, 26, 597.
- 11. Watanabe, T. (1993). Grain boundary design for advanced materials on the basis of the relationship between texture and grain boundary character distribution (GBCD). *Textures and Microstructures*, 20, 195.
- 12. Randle, V., Ralph, B. & Dingeley, D. (1988). The relationship between microtexture and grain boundary parameters. *Acta Metall.*, *36*, 267.
- 13. Watanabe, T. (1988). Interfacial structure, properties and design. ed. M.H.Yoo, W.A.T. Clark and C.L. Briant, MRS Proc., 122, 443.
- 14. ASM (1979). Grain boundary structure and kinetics. American Society for Metals, Seminar, Ohio.
- 15. Hull, D. & Bacan, D. J. (1984). Introduction to dislocations. 3rd Edition, Pergamon Press, 196-200.
- 16. Warrington, D. H. (1979). Formal geometrical aspects of grain boundary structure. *1979 ASM Materials Science Seminar*, Milwaukee, Wisconsin.
- 17. Ralph, B. (1979). Grain boundaries in engineering materials presented at the 1979 ASM seminar, in Grain boundary structure and kinetics American society for metals. *ASM Seminar*.
- 18. Brandon, D. G. (1966). The structure of high angle grain boundaries. Acta Metall., 14, 1479.
- Liu, C. T. & Oliver, B. F. (1989). Effect of grain shape on environmental embrittlement in Ni<sub>3</sub>Al tested at elevated temperatures. J. Mater. Res., 4, 294.
- Liu, C. T. (1992). Environmental embrittlement and grain boundary fracture in Ni<sub>3</sub>Al. *Scripta Metall. Mater.*, 27, 25.
- 21. Boos, J. Y. & Goux, C. (1974). Localized corrosion. NACE-3, 556.
- 22. Matsumoto, K., Shibayanagi, T. & Umakoshi, Y. (1996). Grain growth process in Al-0.3 mass%Mg alloy proc. 2<sup>nd</sup>. *Inter. Conf. On grain growth in polycrystalline materials*. 473.
- Qian, X. R. & Chou, Y. T. (1982). Correlation between grain boundary corrosion and grain boundary energy in Niobium bicrystals. *Phil. Mag.*, *A45*, 1075.
- 24. Hanada, S., Ogawa, T., Watanabe, S., Izumi, O. & Masumoto, T. (1986). Application of the selected area channeling pattern method to the study of intergranular fracture in Ni<sub>3</sub>Al. *Acta Metall.*, *34*, 13.
- Liu, C. T. & Pope, D. P. (1993). The influence of grain boundary geometry on intergranular crack propagation in Ni<sub>3</sub>Al. *Acta Metall. Mater.*, 41, 553.