Investigation of ammonia removal from polluted waters by Clinoptilolite zeolite

^{1*}A. R. Rahmani, ²A. H. Mahvi, ²A. R. Mesdaghinia and ²S. Nasseri

¹Department of Environmental Health, School of Public Health, Hamadan University of Medical Sciences, Hamadan, Iran

²Department of Environmental Health Engineering, School of Public Health and Institute of Health Research Center, Tehran University of Medical Sciences, Tehran, Iran

Abstract

Ammonia nitrogen compounds in the wastewaters and effluents have harmful effects on water resources. Ion exchange with zeolites is a separation process for ammonia removal from effluents. The objective of this research was to study the efficiency of an ammonia removal and the factor affecting to this process. The Clinoptilolite was obtained from Semnan mines at the north part of Iran. The samples were grounded and sieved based on the U.S. standard mesh number 20, 30, 40 and conditioned by ammonia sulfate and sodium chloride solutions. The characteristics of samples for ammonia removal and the selectivity sequence for adsorbing interfering cations were then determined. Results shown that the average ion exchange capacity of zeolite in batch and continuous systems were 6.65-16 and 16.31-19.5 mg NH_4^+ , Na^+ , Ca^{2+} and Mg^{2+} respectively. In study on the zeolite for selective cations showed the ranking of K^+ , NH_4^+ , Na^+ , Ca^{2+} and Mg^{2+} respectively. Results indicated that high level of regeneration (95-98%) might be achieved with NaCl solution. Based on the results, Clinoptilolite may be effective applied in wastewater treatment, both from technical and economical aspects.

Key words: *Clinoptilolite, zeolite, wastewater treatment, ammonia, ion exchange* **Corresponding Author, E-mail: <u>rahmani@umsha.ac.ir</u>*

Introduction

discharges from Ammonia nitrogen industrial and agricultural municipal, wastewater sites, which subsequently mixes into water resources. Some of deleterious effects include accelerated eutrophication of lake, dissolved oxygen depletion in receiving waters and fish toxicity (EPA, 1975). The maximum limit of ammonia set by the European Association for drinking water is approximately 0.5 mg l^{-1} and also a guide level is given as 0.05 mg l^{-1} (AWWA, 1990 and Gaspard, et al., 1983). The raw water with high ammonia concentration must therefore be treated before it reaches the consumer and also the wastewater discharge into the receiving water. The most widely used methods for removing ammonia from wastewater are air stripping, ion exchange, breakpoint chlorination and biological nitrificationdenitrification (Metcalf and Eddy, 2003). Ion exchange has been demonstrated to be competitive with other methods both in terms of performance and cost (Mercer, et al., 1970 and Culp, et al., 1978). Clinoptilolite is one of the natural zeolites used to remove the cations

and ammonia ions from aqueous solutions (Mercer, et al., 1970; Koon and Kaufman, 1975 and Schoman, 1986). In addition to have a greater affinity for ammonia ions than other exchange media, it is relatively inexpensive synthetic when compared to sorbents employed. Several authors have investigated ammonia removal form polluted water by natural zeolite. Ames (1967) and Mercer (1970) suggested that the use of Clinoptilolite for removal of NH₄⁺ from wastewater. In these studies sedimentation effluent with 10 to 19 mg/l NH₄⁺ treated and efficiency of process was obtained 93 to 98%. Koon and Kaufman (1975) were concerned with ammonia removal from municipal wastewater by Clinoptilolite. The pilot study by Liberti (1981) on ammonia removal by Clinoptilolite showed that the ion selectivity by zeolite for ammonia. Gaspard, et al., (1983) examined the ammonia removal characteristics from drinking water by Clinoptilolite. Ershov (1984) studied the ammonia removal in laboratory and semi industrial scale. In these studies the 10% NaCl solution was used for regeneration. Schoeman

(1986) evaluated NH₃-N removal from an underground mine water by South African Clinoptilolite and compared it with Hector Clinoptilolite from the USA. Haralambous, *et al.*, (1992) compared natural and synthetic zeolites for ammonia removal from aqueous solution.

In the aqueous solution, ammonia may exist in either the nonionized form (NH₃) and/or ionized form (NH_4^+) depending on the pH and temperature. The ion-exchange process can remove only the ionized one. The equilibriumexchange capacity remains constantly up to pH 7. The pH of the aqueous solution must be at/or below 7 for optimum ion-exchange operation. During the ion-exchange process, the Na^+ ion is replaced by the NH_4^+ ion, and hence the Na⁺ ion concentration increases in the liquid phase during the ion-exchange processes. When the ion-exchanger reaches breakthrough, the up flow or down flow regeneration method is applied. Gaspard, et al., (1983) reported that the up flow regeneration is more attractive than down flow regeneration. Thus the first is ion exchange and as soon as Clinoptilolite containing a large amount of ammonia ions is in contact with salt solution and ion exchange takes place according to equation 1:

$$Z-NH_4^+ + Na^+ \longleftrightarrow Z-Na^+ + NH_4^+$$
(1)

The ammonia ion-exchange capacity varies depending on the presence of another cations in the aqueous phase and initial ammonia concentration (Gaspard, *et al.*, 1983 and Singh and Prasad, 1997).

The present work considers ammonia removal by a natural ion-exchange resin. This investigation concentrates on defining various operational parameters necessary to remove ammonia through ion exchange by using the Clinoptilolite, zeolite.

The main objective of this paper is to evaluate the characteristics of Semnan Clinoptilolite for removing ammonia ions from aqueous solutions under varying conditions.

Materials and Methods

In this study the Clinoptilolite in rock form was supplied from Semnan mines in the north part of Iran during 2000-2001. The experiments were conducted in two phases with investigations batch sorption and column studies. The chemical properties of Semnan Clinoptilolite used in this study were studied by Kazemian (1993), are given in Table 1.

Constituent	% By weight		
SiO ₂	69.53		
CaO	3.67		
K ₂ O	2.77		
Al_2O_3	7.75		
Na ₂ O	0.63		
Fe_2O_3	1.41		
TiO ₂	0.19		
LOI	12.94		
Total	99.37		

Table 1: Chemical analysis of Semnan Clinoptilolite based on XRD*

* X Ray Diffraction

All analysis was made according to the Standard Methods (1992). Ammonia was then determined by the Nessler method. Ammonia chloride stoke solution was prepared by dissolving 1g NH_4Cl in 1 liter of demonized water. For preparation of synthetic samples the appropriate amounts of ammonia chloride stoke were added to distilled water to give the desired ammonia concentration.

The collected Clinoptilolite samples were grounded and sieved and the fractions between U.S. standard mesh numbers 20, 30 and 40 (0.84, 0.589 and 0.42 mm) were used for the study. The zeolite samples after being washed for removal of fine, conditioned by 0.25-M ammonia sulfate and 1 M sodium chloride respectively. The samples were then rinsed and stored dry. The characteristics of the zeolite for ammonia exchange were determined in two batch and continuous systems.

Batch studies

1) In the first phase of runs, 500 ml of ammonia chloride solution with 1000 mg/l strength were conducted in separate stages with different weights and sizes of conditioned zeolite samples. After mixing for 48 hours ammonia remained in solution was measured with Nessler method. The cation exchange capacities for ammonia were determined by dividing the amount of ammonia removal by the mass of zeolite in the flask.

2) In the second phase of runs, batch sorption isotherms for the removal of ammonia

were investigated. In 1000 ml conical flasks at 20° C. Weighed amounts (30 g with mesh 30) of Clinoptilolite were introduced into 12 conical flasks, in which 500 ml of ammonia solution concentrations of 50 to 1400 mg/l were added. The flasks were then shaken and mixed until equilibrium was reached in each flask. Samples were taken periodically each 30 minutes for measurement of aqueous-phase ammonia concentration. The amount of ammonia accumulated on the Clinoptilolite was calculated by the following equation as the difference between the amounts present in the initial ammonia solution and that remained in solution after equilibrium with the Clinoptilolite:

$$Q = \frac{(C_0 - C_e)V}{M} \tag{2}$$

Where:

- Q (mg/g) is the amount of ammonia adsorbed
- $C_0 \,(\text{mg/l})$ represents initial ammonia concentration
- C_e (mg/l) represents equilibrium ammonia concentration
- V (1) is the volume of solution
- M (g) is the mass of zeolite

After the runs, the equilibrium point for each concentration will be selected. The equilibrium removal of the ammonia ion considered can be mathematically expressed in terms of adsorption isotherms. At equilibrium, the distribution of ammonia between the resin phase and solution phase can be described by the Freundlich or the Langmuir isotherm (Weber, 1972):

$$Q = K_f C_e^{1/n}$$
(3)
or

$$Q = \frac{K_L C_e}{1 + aC_e} \tag{4}$$

Respectively, where:

 (K_f) , and (l/n) are indicative isotherm parameters of sorption capacity and intensity, respectively (K_L) and (a) are Langmuir model parameters. These models are rearranged to the linear form by taking logarithms on both sides:

$$\log Q = \log K_f + n \log C_e \tag{5}$$

$$\frac{C_e}{Q} = \frac{1}{K_L} + \left(\frac{a}{K_L}\right)C_e \tag{6}$$

3) In the third phase of runs, the cation selectivity of zeolite for ammonia to other cations was investigated. One liter of 1M ammonia chloride solution was contacted with 1 gram of conditioned sample with mesh 30. After mixing for 24 hours ammonia in solution were measured with Nessler method and the ammonia adsorbed in solid phase in equilibrium condition was determined. Simultaneously the ammonia equilibrium concentration with addition of 1 M of Ca, Mg and K salts to sample in a separate stage was determined. Then the binary separation factor is defined as the ratio of the distribution of ion A between the solution and zeolite phases and the distribution of ion B between these two phases:

$$\alpha_B^A = \frac{q_A/C_A}{q_B/C_B} \tag{7}$$

Where q_A is the amount of ion A adsorbed to the zeolite (meq/g Clinoptilolite), C_A the concentration of ion A in solution (meq/l), q_B the amount of ion B adsorbed to zeolite (meq/g Clinoptilolite), and C_B the concentration of ion B in solution (meq/l). The separation factors between K, Ca, Mg and Na to NH₄ were determined using the method described by Clifford (1990).

Column studies

In the column studies, operational and regeneration parameters and ion-exchange capacity of Clinoptilolite were investigated.

Thus 30 grams of conditioned zeolite in three mesh sizes 20, 30 and 40 were transferred to three glass columns having 1cm internal diameter by 60cm length. A peristaltic pump was used and employed to feed the ammonia chloride solution 100 mg/l

Test	М	Mesh	Mesh 20		Mesh 30		Mesh 30 Mesh 40		h 40
No.		C _e	Q	C _e	Q	C _e	Q		
1	0	1000	-	1000	-	1000	-		
2	10	750	12.5	730	13.5	680	16		
3	20	550	11.25	500	12.5	480	13		
4	30	460	9.0	385	10.25	370	10.5		
5	40	380	7.75	320	8.5	210	9.88		
6	50	220	7.8	225	7.75	130	8.7		
7	60	160	7.0	202	6.65	105	7.46		

Table 2: Clinoptilolite capacity measurements recorded as mg of NH_4^+ per gram of dry Clinoptilolite in batch system

to the ion exchange column at the desired flow rate respectively. The ammonia concentration of the samples collected from the column exit was monitored. The breakthrough curve so obtained was used to calculate the capacity of the zeolite for ammonia exchange. The basic experimental setup is shown in Figure 1.



Figure 1: Schematic description of the process (*a- Ion Exchange phase, b- Regeneration phase*)

For determination of the effect of the velocity on the ion exchange, three columns with 30 grams conditioned zeolite and mesh sizes of 20, 30 and 40 were used. The zeolite columns were exhausted by down flow at three different superficial velocities of 5, 10 and 15-bed volume per hour (BV/h), until an ammonia breakthrough of more than 2 mg/l NH₄⁺-N was achieved. The columns were then regenerated with three different NaCl solutions (0.3, 0.5 and 1 M NaCl) and at 10 BV/h. The regeneration was passed through the column in

the up flow mode. The absence of ammonia in the effluent indicated the completion of regeneration. Another loading cycle was then carried out.

Results

Batch studies

1) The cation exchange capacity (CEC) of the Semnan Clinoptilolite was determined from the batch system. Three measurements of the zeolite capacity were made for three different mesh sizes: 20, 30 and 40 mesh. The same preconditioning treatment and the same technique for measuring capacity was used for each mesh size, and the results obtained are tabulated in Table 2.

The tests results showed that average ion exchange capacity for particles with 20, 30 and 40 mesh were between 6.65 to 16 mg NH_4^+/g zeolite weight. Furthermore the results showed that the rate of ion exchange has reverse relationship with the particle size. Thus the use of small particles increases the efficiency of processes.

2) For determination of adsorption isotherms, the results obtained by using Equation (2) are plotted vs. time and shown in Figure 2. The equilibrium points for each concentration are then selected.

The equilibrium removal of the ammonia ion considered can be mathematically expressed in terms of adsorption isotherms. Plotting the experimental data using Equations (5) and (6) in Figures 3 and 4 indicates that both models give good fit for the data.



Figure 2: Effect of initial ammonia concentration in the aqueous solution on the exchange capacity



(a+bx) r2=D. a=l2.341616 -D.D30810632 945847487 ь BD 70 60 50 CevC 10 30 20 10 п 100 200 300 500 Co

Figure 3: Linearised Freundlich isotherm for ammonia removal by zeolite

Figure 4: Linearised Langmuir isotherm for ammonia removal by zeolite

Table 3: Langmuir and Freundlich models parameters for best fit and corresponding correlation coefficients

	K _f	0.49
Freundlich model	1/n	0.475
	R^2	0.981
	K _L	0.081
Langmuir model	а	0.007
	\mathbb{R}^2	0.966

The values of K_L , a, K_f and 1/n that best

fitted the data as well as the corresponding correlation coefficients are presented in Table 3. As a consequence, the Freundlich and Langmuir isotherms for ammonia removal can be represented by the following empirical equations 8 and 9 respectively:

$$Q = 0.49C_e^{0.475}$$
 (8)
and

$$Q = \frac{0.081C_e}{1 + 0.007C_e} \tag{9}$$

The separation factors between K, Ca, Mg and Na to NH_4^+ were determined by using equation (7). The binary separation factors were then obtained:

$$\alpha_{NH_{4}}^{NH_{4}} = 1 , \ \alpha_{Ca}^{NH_{4}} = 4.71 , \ \alpha_{Mg}^{NH_{4}} = 8.17 ,$$

$$\alpha_{Na}^{NH_{4}} = 2.3 , \ \alpha_{K}^{NH_{4}} = 0.85$$
(10)

Column studies

In continuous system, total cation exchange and till breakthrough point capacity obtained 17.31 to 18.98 and 9.61 to 11.17 mg NH_4^+/g zeolite weight. The results indicated that high level of regeneration (95-98%) might be achieved with solution of NaCl (Table 4).

The concentrations of the solution for column studies were prepared synthetically at

the level of 100 mg/l of NH_4^+ . The breakthrough curves of ammonia removal by Clinoptilolite and for various velocities (5, 10, 15 BV/hr.) of the aqueous solution are shown in Figure 5 and 6 respectively. Changing the flow rate from 5 to 10 and 15 BV/h resulted has no significant decrease in ammonia adsorption capacity (Figure 6).

Regeneration

Columns were prepared by complete regeneration with 0.3, 0.5 and 1 M NaCl. Ammonia elution by regenerate solutions is shown in Figure 7. It is concluded that a volume of 3.5 liter 1 M NaCl solution is sufficient for nearly complete regeneration of the zeolite column. In lower concentration of regenerate solution for complete regeneration of column, more volumes of regenerate solution must be passed through the ion exchanger bed. The results indicated that high level of regeneration (95-98%) might be achieved with solution of NaCl.

Discussion and Conclusion

In this study, Semnan Clinoptilolite samples were tested in batch and continuous systems to evaluate their ability to adsorb ammonia from aqueous solutions. The removal of ammonia from synthetic solution was demonstrated successfully on a laboratory scale with a selective ion-exchange process.

The results from batch studies showed that the average of ion exchange capacity for samples have reverse relationship with the particle size and the use of small particles increases the efficiency of processes.

The data obtained from tests were applied to Langmuir and Freundlich isotherms. The Freundlich isotherm gives an adequate correlation coefficient value compared to the other.

Table 4: Clinoptilolite capacity measurements recorded as mg of NH₄⁺ per gram of dry Clinoptilolite in continuous system

Test No.	Zeolite weight	Particle size	NH_4^+, C_0 (mg/l.)	Breakthrough Capacity	Total capacity	Total NH_4^+ adsorbed in	Total NH ₄ ⁺ regeneration (mg)
	(g)	(Mesh)		(mg/g)	(mg/g)	column (mg)	C (C)
1	30	20	101	9.61	17.31	519.3	507.63
2	30	30	101	10.06	18.38	551.4	539.37
3	30	40	101	11.17	18.98	569.4	558.37



Figure 5: Clinoptilolite capacity measurements recorded as mg of NH₄⁺ per gram of dry Clinoptilolite in continuous system



Figure 6: Effect of the velocity on the breakthrough curve of NH₄⁺ removal at 100mg/l initial ammonia concentration



Figure 7: Ammonia elution by regenerate solutions in column system

So the results obtained from the cation selectivity of zeolite present high selectivity of the Clinoptilolite toward K^+ and NH_4^+ while much lower selectivity towards Na^+ , Ca^{2+} and Mg^{2+} . Based on the separation factors results, the following Clinoptilolite affinity order can be written:

 $K^{\scriptscriptstyle +} > N H_4^{\scriptscriptstyle +} > N a^{\scriptscriptstyle +} > C a^{2 \scriptscriptstyle +} > M g^{2 \scriptscriptstyle +}$

The results obtained from column studies showed that the total exchange capacity of the Semnan Clinoptilolite for three different mesh sizes were determined between 17.31 to 18.98 mg NH_4^+ /g of dry Clinoptilolite weight. The zeolite particles with mesh 40 gives a higher ammonia adsorption capacity than that the others. The adsorption capacities calculated by graphical integration of the area above the breakthrough curves are about 0.96, 1.02 and 1.05 meq/g NH_4^+ for particle sizes ranging between 0.42 to 0.84 mm, respectively. This indicates that the smaller particle size has a higher ion-exchange capacity due to greater available surface area. The capacity to 2 mg/l NH₄⁺ breakthrough was reached in 93, 87 and 83 BV for the samples column with velocities of 5, 10 and 15 BV/h. respectively. As the velocity of the aqueous solution decreases, the hydraulic residence time increases, resulting in more NH4⁺ being removed by the ionexchange resin. These are reasonable velocities and have no negative effect on adsorption capacity. The column regeneration phase carried out with 10 BV/h showed that in lower concentration of regenerate solution for complete regeneration of column, more volumes of regenerate solution must be passed through the ion exchanger bed. The results indicated that high level of regeneration (95-98%) might be achieved with solution of NaCl. Three loading and three regeneration cycles were carried out without loss of NH₄⁺ adsorption capacity. This shows that on regeneration of the zeolite column with NaCl solution, the Na ions have activated the zeolite column. After the 2nd and 3rd regenerations, the loading process was repeated and it was found that the ammonia adsorption capacity of the Clinoptilolite remained constant. This indicates that using NaCl solution, the regeneration of the column could be done repeatedly without loss of ammonia adsorption capacity.

Results of the experimental investigation are used to develop optimum operational conditions for Clinoptilolite exchangers. Now days, the most wastewater treatment plants in Iran are designed only for removal of organic matter and ammonia remain in effluent. The use of ion exchange with Clinoptilolite can be lead to an economical removal of NH_4^+ from wastewater effluent.

Acknowledgments

The authors would like to express their appreciation and thanks to the Department of Environmental Engineering, School of Public Health and Institute of Health Research Center, Tehran University of Medical Sciences for the valuable financial support. The great thanks also forwarded to Mr. H. Ehsani for his close Cooperation during the study.

References

- Ames, L. L., zeolite removal of ammonium ions from agriculture wastewater. Proc. 13^{th.} Pacific North West Indus. Waste Conf., Washington University, 52-135, 1967
- AWWA, Water quality and treatment. Mc Graw Hill Co., New York, 1990
- Clifford D. A., Ion exchange and inorganic adsorption, in water quality and treatment. McGraw-Hill, AWWA, Washington D.C., 1990
- Culp, H. L., G. M. Wesner, and G. L. Culp, Handbook of advanced wastewater treatment. 2^{nd.} Ed., Van Nostrand Reinhold Co., New York, 1978
- EPA, Process design manual for nitrogen control. U.S.EPA, Technology Transfer, 1975
- Ershov A. V., Use of transcarpathin clinoptilotic rock to remove ammonium nitrogen from municipal sewage. Khim Technol, Vody, (6): 71-75, 1984
- Gaspard, M., A. Neveu and G. Martin, Clinoptilolite in drinking water treatment for NH₄⁺ removal. Water Res., **17** (3): 279-288, 1983
- Haralambous A., E. Maliou and M., Malamis, The use of zeolite for ammonium uptake. Water Sci. Technol., 25 (1): 139-145, 1992
- Kazemian H., Chemical analysis, Characterization, and determination of Ion-Exchange properties of an Iranian Natural zeolite. M. S. thesis, Department of Chemistry, School of Sciences, University of Isfahan, Iran, 1993

- Koon J. H., and W. J. Kaufman, Ammonium removal from municipal wastewaters by ion exchange. J. WPCF 47 (3): 448-465, 1975
- Liberti L., Nutrient removal and recovery by ion exchange. J. Water Res. 15: 337-342, 1981
- Mercer, B. W., L. L. Ames, J. C. Touhill, W. J. Van Slyke and R. B. Dean, Ammonium removal from secondary effluents by selective ion-exchange. J. WPCF. 42 (2): R95-R107, 1970
- Metcalf and Eddy, Wastewater Engineering: Treatment and Reuse. 4^{th.} Ed., Mc Graw Hill Co., New York, 2003
- Schoeman J. J., Evaluation of a South African Clinoptilolite for ammonium-nitrogen removal

from an underground mine water. Water SA., **12** (2): 73-82, 1986

- Singh G. and B. Prasad, Removal of ammonium from coke plant wastewater by using synthetic zeolite. Water Environ. Res., 69 (2): 157-161, 1997
- Standard Methods for the Examination of Water and Wastewater 18^{th.} Ed., American Public Health Association, NW. DC., 1992
- Weber W. J., Physicochemical processes for water quality control. Wiley Interscience, 9: 261-304, 1972