

## Development of $^{153}\text{Sm}$ -DTPA-SPION as a theranostic dual contrast agents in SPECT/MRI

Amir Gholami <sup>1</sup>, Seyyed Hossein Mousavie Anijdan <sup>2, 1\*</sup>

<sup>1</sup>Department of Nuclear Medicine, Shahid Beheshti Hospital, Babol University of Medical Sciences, Babol, Iran

<sup>2</sup>Department of Radiation Technology, Allied Medicine Faculty, Babol University of Medical Sciences, Babol, Iran

### ARTICLE INFO

#### Article type:

Original article

#### Article history:

Received: Sep 20, 2015

Accepted: Dec 24, 2015

#### Keywords:

Biodistribution  
Liver  
Multi-modality imaging  
Super paramagnetic iron -  
oxide nanoparticles  
Theranostic  
 $^{153}\text{Sm}$

### ABSTRACT

**Objective(s):** This study describes the preparation, biodistribution of  $^{153}\text{Sm}$ -DTPA-SPION after intravenous injection in rats.

**Materials and Methods:** The chelator DTPA dianhydride was conjugated to SPION using a small modification of the well-known cyclic anhydride method. Conjugation was done at a 1: 4 (SPION: ccDTPA) molar ratio. Conjugation reaction was purified with magnetic assorting column (MACs) using high gradient magnetic field following incubation, the radio labeled conjugate was checked using RTLC method for labeling and purity checked.

**Results:** The RTLC showed that labeling yield was above 99% after purification and the compound have good *in vitro* stabilities until 48 hr post injection in the presence of human serum. The biodistribution of  $^{153}\text{Sm}$ -DTPA-SPION in rats showed dramatic uptake in the reticuloendothelial system (RES) and their clearance is so fast in other organs especially in the blood. Biodistribution results show that after 30 min post injection more than 84% of injected activities were taken up by the liver and spleen (about 64% and 20%, respectively).

**Conclusion:** Due to magnificent uptakes of this radiotracer in the liver and spleen and their fast clearance from other tissues, especially in blood, it is suggested that this radiotracer would be a potential candidate for RES theranostic purposes.

#### ► Please cite this article as:

Gholami A, Mousavie Anijdan SH. Development of  $^{153}\text{Sm}$ -DTPA-SPION as a theranostic dual contrast agents in SPECT/MRI. Iran J Basic Med Sci 2016; 19:1056-1062.

### Introduction

Super paramagnetic iron oxide nanoparticles (SPION) with a cross-linked dextran coating are used as negative contrast agents in MRI and have flexible uses in different medical fields such as imaging (1, 2), drug delivery (3), cell tracking (3, 4), therapy(5, 6) and lymph node detection (7). Previous studies confirmed that dextran coated NPs with the hydrodynamic size of 60-80 nm had a great tendency to take up via reticuloendothelial system (RES) after intravenously injection (5, 8, 9). Dextran coated NPs maintained in the liver up to several days post injection and they are suitable carriers with high potential for liver and spleen therapies (9, 10). In our prior study we radiolabeled dextran coated SPION with  $^{99\text{m}}\text{Tc}$  and due to their magnificent uptakes in RES (55% in Liver and 20% in spleen) and their fast clearance from other tissues we suggested that these labeled nanoparticles (NPs) (with beta emitter radioisotopes) could be suitable to be used as treatment agents for spleen and liver malignancies (5).

Samarium-153 shows promising radiation characteristics, medium-energy beta particle emissions


( $E_{\text{max}} = 808.20$  keV) which is appropriate for treatment, medium energy gamma photon (103.18 keV) which is also suitable for imaging, and short half-life (46.28 hr). Samarium -153 decays 17 beta ( $\beta$ ) particles which the most frequent beta are 705.02 keV, 635.35 keV and 808.20 keV with the intensities of 49.6%, 32.2% and 17.5%, respectively (11).  $^{153}\text{Sm}$  also decays 80 gamma and X rays, the dominating gamma rays have energies of 103.18 keV (30%) and 69.67 keV (4.85%), respectively. This radionuclide is the most widely used pain palliation radiopharmaceutical in the United States in form of EDTMP complex (Lexidronam) (12).

In this study, we try to develop a  $^{153}\text{Sm}$ -DTPA-SPION as a theranostic radiotracer, which can be applied as dual contrast agents in single photon emission computer tomography (SPECT), and MRI.

### Materials and Methods

Nanomag®-CLD-SPION NPs were provided from Micromod (Micromod Partikeltechnologie GmbH) with lot number Product No. 77-01-201. These nanoparticles were cross linked dextran-coated iron

\*Corresponding author: Sayyed Hossein Mousavie Anijdan. Department of Medical Physics, Babol University of Medical Sciences, Babol, Iran. Fax: +98-11-32234367; email: shmosavia@mubabol.ac.ir



**Figure 1.** Schematic scheme of labeling procedure of Dextran coated iron oxide NPs with amine group conjugated with ccDTPA and labeled with  $^{153}\text{Sm}$  finally

oxide particles with  $\text{NH}_2$  functional group on their surface. The mean core diameter of  $8.86 \pm 1.61$  nm with the Fe concentration of the nanoparticles 2.4 mg/ml. Production of  $^{153}\text{Sm}$  was performed at the Tehran research reactor using  $^{152}\text{Sm}$  (n, gamma)  $^{153}\text{Sm}$  nuclear reaction.  $^{152}\text{Sm}$  with purity of >98% was obtained from ISOTEC Inc., USA. Radiochromatography was performed by counting of Whatman no. 2 (GE, England) using a thin layer chromatography scanner, Bioscan AR2000 (Paris, France). All other chemical reagents were purchased from Sigma-Aldrich Chemical Co UK Whatman No 2 paper was obtained from Whatman (Maidstone, UK). Radiochromatography was performed by Whatman paper using a thin layer chromatography scanner, Bioscan AR2000, Paris, France. A high-purity germanium (HPGe) detector, coupled with a Canberra™ multichannel analyzer (model GC1020-7500SL, canberra Industries Inc, CT, USA) and a dose calibrator ISOMED 1010 (Elimpex-Medizintechnik, Austria) was used for measuring the distributed activity in rat organs. Calculations were based on the 103.18 keV peak for  $^{153}\text{Sm}$ . All values were expressed as mean  $\pm$  standard deviation (Mean  $\pm$  SD). Animal studies were performed in accordance with the United Kingdom Biological Council's Guidelines on the Use of Living Animals in Scientific Investigations, second edition (13).

### Particles characterizations

The particle core size and structure of the SPIONs were checked with a TEM (transmission electron microscope, Philips, CM 30) (14). Photon correlation spectroscopy (PCS) was used to determine the hydrodynamic particle diameter of the particle samples. The PCS measurements were performed with a Malvern Zetasizer Nano ZS-90 (Malvern Instruments Ltd, Worcestershire, UK) (3). Iron concentration of suspensions was acquired with inductively coupled plasma atomic emission spectroscopy (ICP-AES, Varian-

Liberty, 150 AX Turbo, USA) of digested samples with boiling  $\text{HNO}_3$  (7).

### Radiolabeling of SPION with $^{153}\text{Sm}$

#### Conjugation of cyclic DTPA di-anhydride with SPION


The chelator diethylenetriamine penta-acetic acid dianhydride was conjugated to SPIONs using a small modification of the well-known cyclic anhydride method (15, 16). Conjugation was performed at a 1:4 (SPION:ccDTPA) molar ratio. Concisely, NPs (1 mg,  $4.3 \mu\text{M}$ ) and DTPA anhydride (2.10 mg,  $13.76 \mu\text{M}$ ) were mixed in 0.3 ml of 0.1M phosphate buffer solution (pH = 9.0) and 0.3 ml of normal saline and stirred at room temperature (RT) under  $\text{N}_2$  for 30 min.

#### Radiolabelling of the conjugated SPIONs

The SPIONs were labeled with  $^{153}\text{Sm}$  using an optimization protocol according to the literature (17). Typically, 102-105 MBq of  $^{153}\text{Sm}$ -chloride (in 0.2 M HCl) was added to a conical vial and dried under a flow of nitrogen. The conjugated fraction was added to the  $^{153}\text{Sm}$  containing vial, in 1 ml of phosphate buffer (0.1M, pH 8) and mixed gently for 2 min. The resulting solution was incubated at RT for 45 min. Following incubation, the radio-labeled conjugate was checked using RTLC method for labeling and purity checked. The complex reaction was purified with magnetic assorting column (MACs) using high gradient magnetic field (8, 18).

#### Purification of $^{153}\text{Sm}$ -DTPA-SPIONs

In order to purify the final solution the final solution were run through a strong stationary magnetic field using a magnetic-assorting cell separation columns (MACS®), in order to trap the iron oxide NPs in the magnetic column. All the magnetic materials (included labeled and non labeled SPIONs) were trapped via an LS-MACS column (Miltenyi Biotec). The LS-MACS column washed 3 times with PBS, while the column attached



**Figure 2.** RTLC of free <sup>153</sup>Sm (a) and (b) <sup>153</sup>Sm-DTPA-SPIONs after passing through the MACs column in presence of 10 mM DTPA solution as mobile phase and Whatman paper as stationary phase


to high gradient magnet (MACS® Separation Unit, Miltenyi Biotec Inc, Germany), and after separating the column the trapped NPs were washed with the 1 ml of PBS (5).

**Quality control of <sup>153</sup>Sm-DTPA-SPIONs**

Radiochemical purity and radiolabeling yield were tested with a 1 µl sample of the <sup>153</sup>Sm-DTPA-SPION complex that spotted on a chromatography paper (Whatman No 2), and developed in a 10 mM DTPA as the mobile phase. The R<sub>f</sub> values of free <sup>153</sup>Sm and <sup>153</sup>Sm-DTPA-SPION complex were 0.9 and 0.0, respectively.

**Labeling efficiency and stability study**

The labeling efficiency of <sup>153</sup>Sm to SPION NPs by ascending RTLC using Whatman sheets (Whatman, NJ, USA). The RTLC was performed using a 5 µl sample of the final fraction (after passing the MACs column) was spotted on a chromatography sheet paper, and developed in a 10 mM DTPA solution as the mobile phase. Labeling efficiency was calculated using the following equation 1 (16):



**Figure 3.** RTLC of <sup>153</sup>Sm-DTPA-SPION at different time points, in presence of human serum and RT in 10 mM DTPA as mobile phase and Whatman paper as stationary phase

$$\text{Labeling efficiency \%} = \frac{\text{Total counts} - \text{count of free } ^{153}\text{Sm}}{\text{Total counts}} * 100$$

Equation (1)

**Stability testing of the radio-labeled compound in presence of human serum**

For serum stability studies, 7 ml of blood is centrifuged at 3500 rpm for 5 min and then 1 ml of serum is withdrawn. 100 µl of the <sup>153</sup>Sm-DTPA-SPIONs was added to 1 ml of serum and incubated at 37 °C up to 24 hr (16). Aliquots of the reaction mixture were diluted 1:10 with PBS (pH 7.4) and analyzed by RTLC like the procedure described above at 1, 2, 6 and 24 hr. The labeling efficiency and radiochemical purity were determined (Figure 3).

**Biodistribution of <sup>153</sup>Sm-DTPA-SPION NPs in normal rats**

To determine its biodistribution, NPs was administered to normal rats (NMRI) purchased from Razi Institute (Karaj, Iran). A volume (50 µl) of the final <sup>153</sup>Sm-DTPA-SPION solution containing an activity of 4.4-5.2 MBq was injected intravenously to rats through their tail veins. Five rats were sacrificed at specific time intervals (1, 5, 15, 30, 60 min and 2, 6 and 24 hr and 2 and 4 days post injections.), and the specific activity was calculated for various organs as a percentage of the injected dose per gram tissue (ID/g %) (Based on the area under the 103.18 keV peak obtained by an HPGC detector)(19).

**Measurement of activity**

The activity in the syringes was measured before and after administration of the radiopharmaceutical with well-type ionization chamber (CRC-15R, Capintec, USA N.J.). All samples were background subtracted, the decay correction was not performed, and then similar samples were averaged together (20).

For each of these measurements, three samples (from each organ) were weighed and then counted

by HPGe to determine the percentage of injected dose per gram (which was equivalent to the percentage of injected activity per gram %IA/g≡%ID/g) (21); all the organ activity measurements were normalized to injected activity. Uncertainties in the determinations were minimal, because each assay collected at least 10,000 counts, which results the standard deviation (SD) of less than 1%. In all the measurements, we try to keep same geometry and same volume in order to prevent overestimation and underestimation in dose measurements (22). All samples were background subtracted and decay correction was not considered for all measurements, and the similar samples were averaged together (5, 22).

The HPGe detector give us count therefore we had used the below formula to convert the counts into the activity (22, 23):

$$A(Bq)_{Tissue} = \frac{Area}{t * Eff * Br} \quad \text{Equation (2)}$$

Where *t* is the time of counts and *Eff* is the efficiency of the detector for the selected energy and *Br* is the decay yield of selected energy (103.18 keV) for the <sup>153</sup>Sm.

The <sup>153</sup>Sm activity concentration at time *t*, %ID/g (*t*), was then calculated as the percentage of injected activity per gram of tissue (%IA/g):

$$\%ID/g = \frac{A_{Tissue} / M_{Tissue}}{A_{Total}} * 100 \quad \text{Equation (3)}$$

Where *A<sub>tissue</sub>* is the <sup>153</sup>Sm activity in the sample, *M<sub>tissue</sub>* is the mass of the sample and *A<sub>total</sub>* is the total activity of <sup>153</sup>Sm injected into the rat (24, 25).

**Statistical analysis**

Data have been represented as the mean of four individual observations with standard error of mean. Significance has been calculated using Student's *t*-test.

**Results**

Figure 4 shows size information of the prepared SPIONs. As demonstrated in Figure 4, the core size distribution of the NPs is narrow.

The PCS histogram of SPIONs indicating their hydrodynamic magnitudes of about 69.98 nm. The radionuclide purity of <sup>153</sup>Sm-DTPA-SPION was about 81% post labeling but after passing through the MACs column, it increased to 99%. The accumulation of <sup>153</sup>Sm-DTPA-SPION in the various organs are shown in Table 1. The results showed that most of the activity was accumulated in the reticuloendothelial system (liver and spleen). Nearly all excretion of activity occurred by the renal system, and hepatobiliary excretion was insignificant.

**Discussion**


Development of new contrast agents as an theranostic agents with the potential of using in multimodalities such as single photon emission computer tomography SPECT and MRI and positron emission tomography (PET) is now emerging (26, 27). The labeling process of SPION-DTPA is took about 1 hr (include the purification). Although

**Table 1.** Biodistribution of <sup>153</sup>Sm-DTPA-SPION in various time points (represented as injected dose per gram)

Tissues	Time								
	1	5	15	30	60	360	1440	2880	5760
Blood	46.5±1.4	13.1±1.4	3.5±0.8	0.9±0.1	0.2±0.0	0.1±0.0	0.0±0.0	0.0±0.0	0.0±0.0
Intestine	0.1±0.0	0.2±0.0	0.3±0.1	0.2±0.1	0.2±0.0	0.1±0.0	0.0±0.0	0.0±0.0	0.0±0.0
Stomach	0.1±0.0	0.4±0.1	0.5±0.2	0.2±0.1	0.2±0.1	0.1±0.0	0.0±0.0	0.0±0.0	0.0±0.0
Brain	0.0±0.0	0.0±0.0	0.0±0.0	0.0±0.0	0.0±0.0	0.0±0.0	0.0±0.0	0.0±0.0	0.0±0.0
Muscle	0.1±0.0	0.2±0.0	0.1±0.0	0.1±0.0	0.1±0.0	0.0±0.0	0.0±0.0	0.0±0.0	0.0±0.0
Liver	22.5±2.6	45.4±3.4	57.9±2.7	63.9±3.7	61.5±2.9	50.6±2.2	34.6±1.9	20.2±1.2	12.9±0.8
Spleen	3.9±0.4	15.8±1.2	16.8±1.1	19.6±1.3	16.9±1.4	8.0±0.7	3.1±0.4	1.0±0.2	0.3±0.0
Bone	0.4±0.0	0.3±0.0	0.3±0.1	0.3±0.0	0.3±0.0	0.1±0.0	0.1±0.0	0.0±0.0	0.0±0.0
Heart	2.4±0.2	1.3±0.1	0.9±0.1	0.3±0.0	0.1±0.0	0.1±0.0	0.0±0.0	0.0±0.0	0.0±0.0
Kidney	3.7±0.6	4.6±0.9	3.3±0.4	1.9±0.2	1.2±0.1	0.7±0.1	0.2±0.0	0.0±0.0	0.0±0.0
Pancreas	1.1±0.1	0.4±0.1	0.4±0.0	0.3±0.0	0.2±0.0	0.1±0.0	0.0±0.0	0.0±0.0	0.0±0.0
Lung	5.2±0.3	2.6±0.3	1.7±0.1	1.3±0.1	1.2±0.3	0.4±0.0	0.0±0.0	0.0±0.0	0.0±0.0
Skin	0.2±0.0	0.1±0.0	0.1±0.0	0.3±0.0	0.1±0.0	0.1±0.0	0.1±0.0	0.0±0.0	0.0±0.0
Feces	0.0±0.0	0.1±0.0	0.2±0.0	0.3±0.0	0.4±0.0	1.1±0.1	2.1±0.3	2.3±0.2	1.6±0.1
Cascade	3.0±0.2	1.9±0.1	1.1±0.1	0.7±0.1	0.3±0.0	0.2±0.0	0.2±0.0	0.1±0.0	0.03±0.0
urine	0.0±0.0	0.1±0.0	1.8±0.1	2.1±0.3	3.6±0.2	2.9±0.2	1.9±0.1	1.1±0.1	0.3±0.0

Data are presented as (mean±SD) and the mean values as the percentage of administered activity per gram (decay corrected)





**Figure 4.** right) TEM of a SPIONs shows that the crystal core size of the particles is about  $10.4 \pm 1.98$  nm similar to our previous study (21) and left) The PCS histogram of SPIONs indicating their hydrodynamic magnitudes of about 69.98 nm

Nosrati *et al* shows that 1 hr is the optimum and best time for conjugation of DTPA with SPIONs but due to some limitation, we incubate the DTPA with SPIONs for 30 min (28). As demonstrated in Figure 2 the labeling yield after purification was increased from 81% into %100. The main reason of high purity is that the MACs column trapped all magnetic materials and therefore the free radioisotopes were washed from the column. The final product had a good stability as shown in Fig 3 after 24 hr post labeling the labeling purity in the RT and human plasma were more than 90 and 74%, respectively. The hydrodynamic size examination of the NPs shows that the size was not significantly change after labeling. The size and the kinetic of the labeled NPs were in accordance to our previous studies (5, 9). As represented in Table 1 after 30 min post injection more than 84% of injected activities were taken up by the liver and spleen (about 64% and 20%, respectively). This unique characteristic of these NPs is due to their size and their coating. Previous studies confirmed that dextran coated particles with the size range between 60 to 80 nm were rapidly cleared from the blood and accumulated in the RES (29-31). We can deliver high quantities of dose to the targeted organs (liver and spleen) with this brilliant spectacular phenomenon and since the tracer cleared so fast from blood the other organs (except RES) uptakes were negligible.

Shanehsazzadeh *et al* radiolabeled the Dextran coated nanoparticles with the range of 40nm to 80nm via  $^{99m}\text{Tc}$ ,  $^{67}\text{Ga}$  and  $^{166}\text{Ho}$ . They got similar results in terms of short blood half-life and high RES uptakes and suggested that using theranostic radioisotopes such as  $^{177}\text{Lu}$  or  $^{153}\text{Sm}$  would be better for RES detection and therapeutic purposes (28, 32). Dr. Weissleder *et al* in 1988 used the (AMI-25) which was SPION with 80 nm mean size and they reported that after 1 hrr post *i.v.* injection in rats more than 82% and 6% of injected dose were accumulated in

liver and spleen, respectively (33). While in our study, more than 64% and 20% of administrated dose were taken up by the liver and spleen, respectively. In agreement to Dr Weissleder *et al* the uptake of SPIONs was negligible in brain which shows that the NPs cannot pass through the blood brain barrier (BBB) (31, 33).

Due to splendid amount of cumulative activity in liver and spleen the effective absorbed dose in these two organs were so high compare to normal human diagnostic nuclear medicine studies. As exposed in Table 1 if we simply divided the spleen/blood and liver/blood uptakes we see that these ratios would be radically raised by the time increased this trend shows that the amount of spleen/blood and liver/blood uptakes ratios after 30 min post injection would be more than 22 and 71, respectively. These ratios were rise dramatically after 6 hr post injection into 80 and 506, correspondingly. Although the results of this study was promising in terms of liver and spleen uptakes but further studies still needed to calculate the internal dose and safety of this radiotracer (32, 34, 35).

This research evaluated the feasibility of SPIONs labeled with  $^{153}\text{Sm}$  as potential theranostic dual contrast agents in nuclear medicine and MRI. We showed that the magnetic NPs based tracers are mostly accumulated in the liver and spleen, which are the major organs of accumulation throughout the study. Due to splendid uptakes of  $^{153}\text{Sm}$ -DTPA-SPION in the liver and magnificent uptakes of this radiotracer in the liver and spleen and their fast clearance from other tissues especially in blood, it is suggested that this radiotracer would be a potential candidate for theranostic purposes.

### Acknowledgment

This work was supported by Babol University of Medical Sciences.

## References

- Shanehsazzadeh S, Lahooti A, Hajipour MJ, Ghavami M, Azhdarzadeh M. External magnetic fields affect the biological impacts of superparamagnetic iron nanoparticles. *Colloid Surface B* 2015; 136:1107-1112.
- Amanlou M, Siadat SD, Ebrahimi SES, Alavi A, Aghasadeghi MR, Ardestani MS, *et al.* Gd<sup>3+</sup>-DTPA-DG: novel nanosized dual anticancer and molecular imaging agent. *Int J Nanomed* 2011;6:747-763.
- Jahanbakhsh R, Atyabi F, Shanehsazzadeh S, Sobhani Z, Adeli M, Dinarvand R. Modified Gadonanotubes as a promising novel MRI contrasting agent. *Daru* 2013;21:53-62.
- Oghabian MA, Gharehaghaji N, Masoudi A, Shanehsazzadeh S, Ahmadi R, Majidi RF, *et al.* Effect of coating materials on lymph nodes detection using magnetite nanoparticles. *Adv Sci Eng Med* 2013;5:37-45.
- Lahooti A, Shanehsazzadeh S, Jalilian AR, Tavakoli MB. Assessment of effective absorbed dose of <sup>111</sup>In-DTPA-Buserelin in human on the basis of biodistribution rat data. *Radiat Prot Dosim* 2013; 154: 1-8.
- Hajesmaeelzadeh F, Shanehsazzadeh S, Grüttner C, Daha FJ, Oghabian MA. Effect of coating thickness of iron oxide nanoparticles on their relaxivity in the MRI. *Iran J Basic Med Sci* 2016; 19: 166-171.
- Shanehsazzadeh S, Oghabian M, Allen B, Amanlou M, Masoudi A, Daha F. Evaluating the effect of ultrasmall superparamagnetic iron oxide nanoparticles for a long-term magnetic cell labeling. *J Med Phys* 2013;38:34-40.
- Shanehsazzadeh S, Gruettner C, Lahooti A, Mahmoudi M, Allen BJ, Ghavami M, *et al.* Monoclonal antibody conjugated magnetic nanoparticles could target MUC-1-positive cells in vitro but not *in vivo*. *Contrast Media Mol Imaging* 2015;10:225-236.
- Shanehsazzadeh S, Lahooti A. Biodistribution of 80 nm iron oxide nanoparticles labeled with <sup>99m</sup>Tc in Balb/c mice. *Nucl Med Biol* 2014; 41:625.
- Weissleder R, Stark D, Engelstad B, Bacon B, Compton C, White D, *et al.* Superparamagnetic iron oxide: pharmacokinetics and toxicity. *AJR Am J Roentgenol* 1989;152:167-173.
- Firestone RB, Shirley VS. *Table of Isotopes*, 2 Volume Set, by Richard B. Firestone, Virginia S. Shirley (Editor), pp. 3168. ISBN 0-471-33056-6. Wiley-VCH, December 1998; 1998:3168.
- Resche I, Chatal JF, Pecking A, Ell P, Duchesne G, Rubens R, *et al.* A dose-controlled study of <sup>153</sup>Sm-ethylenediaminetetramethylenephosphonate (EDTMP) in the treatment of patients with painful bone metastase. *Eur J Cancer* 1997;33:1583-1591.
- Council B. *Guidelines on the use of living animals in scientific investigations: Biological Council*; 1987.
- Omid H, Oghabian MA, Ahmadi R, Shahbazi N, Hosseini HRM, Shanehsazzadeh S, *et al.* Synthesizing and staining manganese oxide nanoparticles for cytotoxicity and cellular uptake investigation. *BBA-Gen Subj* 2014;1840:428-433.
- Shanehsazzadeh S, Jalilian AR, Sadeghi HR, Allahverdi M. Determination of human absorbed dose of <sup>67</sup>Ga-DTPA-ACTH based on distribution data in rats. *Radiat Prot Dosim* 2009; 134:79-86.
- Jalilian A, Shanehsazzadeh S, Akhlaghi M, Garoosi J, Rajabifar S, Tavakoli M. Preparation and evaluation of [<sup>67</sup>Ga]-DTPA-β-1-24-corticotrophin in normal rats. *Radiochim Acta* 2008; 96:435-439.
- Jalilian AR, Shanehsazzadeh S, Akhlaghi M, Garousi J, Rajabifar S, Tavakoli MB. Preparation and biodistribution of [Ga-<sup>67</sup>]-DTPA-gonadorelin in normal rats. *J Radioanal Nucl Ch* 2008;278:123-129.
- Shanehsazzadeh S, Oghabian MA, Lahooti A, Allen BJ, editors. *Development of ultra small super paramagnetic iron oxide nanoparticles labeled with Gallium 67 as a dual modality probe.* *J Label Compd Rad* 2013: WILEY-BLACKWELL 111 RIVER ST, HOBOKEN 07030-5774, NJ USA.
- Shanehsazzadeh S, Grüttner C, Yousefnia H, Lahooti A, Gholami A, Nosrati S, *et al.* Development of <sup>177</sup>Lu-DTPA-SPIO conjugates for potential use as a dual contrast SPECT/MRI imaging agent. *Radiochim Acta* 2016; 104: 337-344.
- Shanehsazzadeh S, Lahooti A, Sadeghi HR, Jalilian AR. Estimation of human effective absorbed dose of <sup>67</sup>Ga-cDTPA-gonadorelin based on biodistribution rat data. *Nucl Med Commun* 2011;32:37-43.
- Najafian N, Shanehsazzadeh S, Hajesmaeelzadeh F, Lahooti A, Gruettner C, Oghabian MA. Effect of Functional Group and Surface Charge of PEG and Dextran-Coated USPIO as a Contrast Agent in MRI on Relaxivity Constant. *Appl Magn Reson* 2015; 46: 685-692.
- Sadeghzadeh M, Shanehsazzadeh S, Lahooti A. Assessment of the effective absorbed dose of 4-benzyl-1-(3-[<sup>125</sup>I]-iodobenzylsulfonyl) piperidine in humans on the basis of biodistribution data of rats. *Nucl Med Commun* 2015; 36:90-94.
- Moghaddam AK, Jalilian AR, Hayati V, Shanehsazzadeh S. Determination of human absorbed dose of <sup>201</sup>Tl (III)-DTPA-HiGG based on biodistribution data in rats. *Radiat Prot Dosim* 2010;141:269-274.
- Zolghadri S, Jalilian AR, Naseri Z, Yousefnia H, Bahrami-Samani A, Ghannadi-Maragheh M, *et al.* Production, Quality Control and Biological Evaluation of <sup>166</sup>Ho-PDTMP as a Possible Bone Palliation Agent. *Iran J Basic Med Sci* 2013;16:719-725.
- Jalilian AR, Shanehsazzadeh S, Akhlaghi M, Kamali-dehghan M, Moradkhani S. Development of [<sup>111</sup>In]-DTPA-buserelin for GnRH receptor studies. *Radiochim Acta* 2010;98:113-119.
- Azhdarzadeh M, Atyabi F, Saei AA, Varnamkhasti BS, Omidi Y, Fateh M, *et al.* Theranostic MUC-1 aptamer targeted gold coated superparamagnetic iron oxide nanoparticles for magnetic resonance imaging and photothermal therapy of colon cancer. *Colloid Surface B* 2016; 143: 224-232.
- Hatamie S, Ahadian MM, Ghiass MA, Saber R, Parseh B, Oghabian MA, *et al.* Graphene/cobalt nanocarrier for hyperthermia therapy and MRI diagnosis. *Colloid Surface B* 2016; 146:271-279.
- Nosrati S, Shanehsazzadeh S, Yousefnia H, Gholami A, Grüttner C, Jalilian AR, *et al.* Biodistribution evaluation of <sup>166</sup>Ho-DTPA-SPION in

normal rats. J Radioanal Nucl Ch 2016; 307: 1559-1566.

29. Mirshafiee V, Mahmoudi M, Lou K, Cheng J, Kraft ML. Protein corona significantly reduces active targeting yield. Chem Commun 2013; 49:2557-2559.

30. Shanehsazzadeh S, Oghabian MA, Lahooti A, Allen BJ, editors. Development of ultra small super paramagnetic iron oxide nanoparticles labeled with Gallium 67 as a dual modality probe. J Label Compd Rad; 2013: WILEY-BLACKWELL 111 RIVER ST, HOBOKEN 07030-5774, NJ USA.

31. Mahmoudi M, Lynch I, Ejtehadi MR, Monopoli MP, Bombelli FB, Laurent S. Protein-Nanoparticle Interactions: Opportunities and Challenges. Chem Rev 2011;111:5610- 5637.

32. Shanehsazzadeh S, Oghabian MA, Lahooti A, Abdollahi M, Haeri SA, Amanlou M, et al. Estimated background doses of [67Ga]-DTPA-USPIO in normal

BALB/c mice as a potential therapeutic agent for liver and spleen cancers. Nucl Med Commun 2013;34:915-925.

33. Weissleder R, Stark D, Engelstad B, Bacon B, Compton C, White D, et al. Superparamagnetic iron oxide: pharmacokinetics and toxicity. Am J Roentgenol 1989;152:167-173.

34. Shanehsazzadeh S, Yousefnia H, Lahooti A, Zolghadri S, Jalilian AR, Afarideh H. Assessment of human effective absorbed dose of 67 Ga-ECC based on biodistribution rat data. Ann Nucl Med 2014;28:118-124.

35. Shanehsazzadeh S, Lahooti A, Shirmardi SP, Erfani M. Comparison of estimated human effective dose of 67Ga-and 99mTc-labeled bombesin based on distribution data in mice. J Radioanal Nucl Ch 2015;305:513-520.