

## تأثیر مواد و روش‌های حفاظتی بر روی خواص فیزیکی چوب اکالیپتوس (*Eucalyptus camaldulensis*) کاملدولنسیس

داود پارسا پژوه<sup>۳</sup>

راه علی بیات کاشکولی<sup>۲</sup>

چکیده

× ×

pH AWPA

(...)

(Email: rbayatkashkoli@yahoo.com)

// : // : -

مقدمه

E.C

( )

( )

(*Eucalyptus camaldulensis*)

-

(.)

( )

(.)

( )

Cooperative Creosote )

(Projects

(.)

( )

(.)

( )

( Plato

)

(.)

-Chromium

-Arsenic

-Darred

- Creosote

-Homan

(.)

MSTAT-C

\* \*

( )

)

(

ISO ASTM

( )

AWPA

pH

( )

روش‌های اشباع

( )

( )

( )

( / )

)

( / )

(

Ruping

Double ruping

Bethell

Floure

)

( ) ISO  
 ( )  
 \* \* ISO

جدول ۱- اولین ترکیب استاندارد مورد استفاده براساس فرمول زیر است (FCAP)(فرمول اولیه از رفرنس ۱۱ است.)

مقدار از ۱۰۰ درصد		فرمول شیمیایی	ماده شیمیایی
درصد فرمول	درصد تغییر یافته		
۲۲ درصد	۲۴ درصد	NaF دارای ۵ درصد آب	فلوئورید سدیم
۳۷ درصد	۳۵ درصد	CrO <sub>۳</sub> شش ظرفیتی	اکسید کرم
۲۵ درصد	۲۴ درصد	AS <sub>۲</sub> O <sub>۵</sub> دارای ۷۵ درصد آب	آرسنیک پنتاکسید
۱۶ درصد	۱۷ درصد	(NO <sub>۲</sub> ) <sub>۲</sub> C <sub>۶</sub> H <sub>۳</sub> (OH) و ۲ دارای ۵ درصد آب	۲-۶ دی نیتروفلن

pH=۵/۷۶۸ نهایی

pH = ۵/۵ - ۷/۸ استاندارد

pH=۳/۶۶۹ اولیه

جدول ۲- دومین ترکیب استاندارد مورد استفاده براساس فرمول زیر است (CCA نوع A) (فرمول اولیه از رفرنس ۱۱ است.)

مقدار از ۱۰۰ درصد		فرمول شیمیایی	ماده شیمیایی
درصد فرمول	درصد تغییر یافته		
۲۳/۸ درصد		K <sub>۲</sub> Cr <sub>۲</sub> O <sub>۷</sub> دارای ۶۹ درصد آب	بی کرومات پتاسیم
۱۲/۵ درصد		H <sub>۲</sub> O	آب
۲۸/۷ درصد		CrO <sub>۳</sub>	اکسید کرم
۱۸/۳ درصد	۱۷ درصد	H <sub>۳</sub> ASO <sub>۴</sub> دارای ۷۵ درصد آب	اسید آرسنیک
۱۶/۷ درصد	۱۸ درصد	CuCO <sub>۳</sub> دارای ۵۵ درصد آب	کربنات مس

pH = ۲/۷۵۳ نهایی

pH = ۱/۶-۳/۲ استاندارد

pH = ۱/ اولیه

( )

هم کشیدگی کلی:

( )

:

( )

( )



)  
) ( ( )  
( ) ( )  
( )  
OH :

) ( )  
( )  
( )  
(... )

( )  
( )  
( )  
( )

( )  
( )  
( )

( )

Archive of SID

( )

( ) )

( ) )

)

( ) )

(

( )

وزن مخصوص

( ) )

SEM

( ) )

SEM

( )  
( )

pH

( )  
( )  
(...)

( )

( )

( )

( )

(OH)

pH

( )


بلوک ۴..... بلوک ۳..... بلوک ۲..... بلوک ۱



میانگین همکشیدگی کلی	وزن مخصوص پایه	وزن مخصوص خشک	وزن مخصوص نسبی	وزن مخصوص تر	تیمارها
/	/	/	/	/	
/	/	/	/	/	
/	/	/	/	/	
/	/	/	/	/	
/	/	/	/	/	
/	/	/	/	/	
/	/	/	/	/	
/	/	/	/	/	
/	/	/	/	/	
/	/	/	/	/	

Archive of SID

( )

/	/	/	/	/	
/	/	/	/	/	
/	/	/	/	/	

حروف مشابه بیانگر عدم معنی دار بودن میانگین ها می باشد

Archive of SID

( - )

درجات آزادی	مجموع مربعات	میانگین مربعات	میزان F	احتمال	منابع تغییر هم‌کشیدگی کلی
۳	۵/۸۶۸	۱/۹۵۶	۱/۸۳۹	۰/۲۴۱	تکرار
۲	۰/۰۶۳	۰/۰۳۱	۰/۰۲۹	-	فاکتور A
۶	۶/۳۸	۱/۰۶۳	-	-	اشتباه
۳	۲۷/۲۸۸	۹/۰۹۶	۹/۷۴۸	۰/۰۰۰	فاکتور B
۶	۲/۹۶۱	۰/۴۹۳	۰/۵۲۹	-	AB
۲۷	۲۵/۱۹۳	۰/۹۳۳	-	-	اشتباه
۴۷	۶۷/۷۵۲	جمع			ضریب تغییرات ۸/۱۶
درجات آزادی	مجموع مربعات	میانگین مربعات	میزان F	احتمال	منابع تغییر وزن مخصوص پایه
۳	۰/۰۹۴	۰/۰۳۱	۵/۰۸۶	۰/۰۴۴	تکرار
۲	۰/۰۰۸	۰/۰۰۴	۰/۶۵۸	-	فاکتور A
۶	۰/۰۳۷	۰/۰۰۶	-	-	اشتباه
۳	۰/۱۳۴	۰/۰۴۵	۱۵/۶۰۹	۰/۰۰۰	فاکتور B
۶	۰/۰۱۷	۰/۰۰۳	۰/۹۸۴	-	AB
۲۷	۰/۰۷۷	۰/۰۰۳	-	-	اشتباه
۴۷	۰/۳۶۷	جمع	۷/۴۱		ضریب تغییرات
درجات آزادی	مجموع مربعات	میانگین مربعات	میزان F	احتمال	منابع تغییر وزن مخصوص خشک
۳	۰/۱۲۵	۰/۰۴۲	۴۱/۶۲۹	۰/۰۰۰	تکرار
۲	۰/۰۲	۰/۰۱	۱۰/۰۲۷	۰/۰۱۲۲	فاکتور A
۶	۰/۰۰۶	۰/۰۰۱	-	-	اشتباه
۳	۰/۰۹۹	۰/۰۳۳	۱۲/۳۹۳	۰/۰۰۰	فاکتور B
۶	۰/۰۲۶	۰/۰۰۴	۱/۶۲۱	۰/۱۷۹	AB
۲۷	۰/۰۷۲	۰/۰۰۳	-	-	اشتباه
۴۷	۰/۳۴۷	جمع	۶/۲۴		ضریب تغییرات
درجات آزادی	مجموع مربعات	میانگین مربعات	میزان F	احتمال	منابع تغییر وزن مخصوص نسبی
۳	۰/۱۰۱	۰/۰۳۴	۴۹/۴۲۳	۰/۰۰۰	تکرار
۲	۰/۰۲۶	۰/۰۱۳	۱۸/۸۸۵	۰/۰۰۳	فاکتور A
۶	۰/۰۰۴	۰/۰۰۱	-	-	اشتباه
۳	۰/۱۰۵	۰/۰۳۵	۱۷/۵۳۴	۰/۰۰۰	فاکتور B
۶	۰/۰۳۱	۰/۰۰۵	۲/۵۹۲	۰/۰۴۱	AB
۲۷	۰/۰۵۴	۰/۰۰۲	-	-	اشتباه
۴۷	۰/۳۲۰	جمع کل		۵/۷۸	ضریب تغییرات
درجات آزادی	مجموع مربعات	میانگین مربعات	میزان F	احتمال	میانگین تغییر وزن مخصوص نر
۳	۰/۱۴۳	۰/۰۴۸	۱۲۶/۰۹۹	۰/۰۰۰	تکرار
۲	۰/۰۱۸	۰/۰۰۹	۲۳/۵۱۳	۰/۰۰۱	فاکتور A
۶	۰/۰۰۲	۰/۰۰۰	-	-	اشتباه
۳	۰/۰۷۲	۰/۰۲۴	۸/۷۳۷	۰/۰۰۰	فاکتور B
۶	۰/۰۱۵	۰/۰۰۳	۰/۹۲	-	AB
۲۷	۰/۰۲۴	۰/۰۰۳	-	-	اشتباه
۴۷	۰/۳۲۴	جمع کل		۶/۰۱	ضریب تغییرات

Archive of SID

- ۱- ابراهیمی، قنبر، ۱۳۷۹. رابطه آب و چوب، انتشارات دانشگاه تهران.
- ۲- بیات کشکولی، راه علی، ۱۳۷۴. روش‌های مطالعه چوب بوسیله الکترومیکروسکوپی، سمینار کارشناسی ارشد.
- ۳- پارسا پژوه، داود، ۱۳۶۳. تکنولوژی چوب، دانشگاه تهران.
- ۴- جوانشیر، کریم و احمد مصدق، ۱۳۵۱. اکالیپتوس، انتشارات دانشگاه تهران.
- ۵- جهرمی، سید مرتضی، ۱۳۶۸. بررسی سازگاری مختلف اکالیپتوس در مناطق شرق استان فارس، پایان‌نامه کارشناسی ارشد.
- ۶- علی اکبری، جاسم، ۱۳۵۷. بررسی اثر مواد و روش‌های حفاظتی بر روی خواص فیزیکی و مکانیکی چوب راش، پایان‌نامه کارشناسی ارشد.

7- American Society for Testing Materials, 1994. A.S.T.M. Philadelphia.

8- Barry.R. A., 1993. Wood Preservation Second Edition, Chapman and hall.

9- Cartwright, K. ST. G., M.t. (oxon.), W.P.K. Findlay and D. Se. (lond), 1958. Decay of Timber and it's Prevention Her Majesty's Stationery Office, Forest Products Research Laboratory.

- 10-Darred.N. D., 1973. Wood Deterioration and its Prevention by Preservation Treatments, Sgracuse University Press. Syracuse. Newyork.
- 11-Eaton, R. Aand M. D.C. Halisted. 1993. Wood; Decay, Pests, and Protection, Chapman and Hall.
- 12-Homan,W, Tjeerdsma.B, Beckers.E, Jorissen.A., 2003. Structural and Other Properties of Modified Wood, SHR Timber Research, Wageningen,USA.
- 13-International Organization for Standardization, ISO, 1975.
- 14-Kessel. F.G. and etal., 1976. Seanning Electron Microscopy in Biology part 11 (Wood), Berlin Heidelberg Newyork.
- 15-Midyley, S.J. and . K.G. Eldridge and J. Doran, 1980. Genetic Resources of *E. Camaldulensis*, CSIR Division of Forestry and Forest Product Canberra Act, Australia.
- 16-Nobuo.S and H. Kajito and M. Norimoto, 1993. Recent Research on Wood and Wood- Based Materials the Society of Materials Science, Japan Current Japancese Material Research Vol.,11.

Archive of SID

## The Effects of Preservative Materials and Impregnation Processes on Physical Properties of : *Eucalyptus camaldulensis*

R. Bayat Kashkooli<sup>1</sup>

D. Parsapajouh<sup>2</sup>

### Abstract

Wood logs were supplied from Mamasani, Fars Province, from a population of planted eucalyptus trees. They were cut into 7×7×100 cm samples, and dried to below 20% moisture content. A split plot design was used for the experiment. Three impregnation methods namely Bethel, Ruppung and Double ruppung along with three preservatives as against control samples were employed. A creosote and two other water soluble preservatives were prepared with proper pH using AWPA standard. Results are indicative of reactions of wood as well as internal wood elements to impregnation.

A decrease was observed in the overall shrinkage in the treated samples. This was more pronounced in the Bethel creosote method. This indicates the stabilization of wood dimensions as a result of impregnation. Some reasons for this phenomenon could be cited as trans attachment of wood elements, subsequent drying in double drying process, and irreversible swelling. The specific gravity is less in treated samples as compared to control, this being more pronounced in the case of double ruppung, and treated samples with preservatives; chromium, flourine and arsenic. This could be due to minor cracks on wood, microscopic cracks (inner layer fracture, cell wall ruptures, etc), increase in dimensions (of irreversible nature), inflation of wood elements, double drying stresses and unexpectable leaching. Milder treatment methods such as ruppung and use of less volatile elements of chromium, copper and arsenic (CCA) are preferred over others.

**Keyword:** Wood physical properties, Preservatives and preservation methods, Redrying, Specific gravity, Shrinkage, *Eucalyptus camaldulensis*.

---

<sup>1</sup> -Ph. D Student of Wood and Paper Science and Technology, Faculty of Natural Resources, University of Tehran ,  
(E-mail: rbayat kashkoli@yahoo.com)

<sup>2</sup> -Professor, Faculty of Natural Resources, University of Tehran