

- ()
- (L*) (R)
- .
- (EDTA) Fe²⁺ (s) (k) (a*) (b*)


(E-mail: Abdulkhani@nrf.ut.ac.ir)

/ / : / / :

%	
^{13}C	
	pH
%	

%	%
^{13}C	
	pH
% /	EDTA

mICSF	
Kpam ² /g	
mN.m ² /g	
Nm/g	
%	(ISO)
	()





		TAPPI	
		T272om-92	
	Fe ²⁺		
	(FeSO ₄ .7H ₂ O)		
	ISO		
	CIELAB (L*, a*, b*)		
	(T16-1C) Technidyne Brightmeter		
(ISO)	T452om92	TAPPI	
()	UV		
(k/s)	nm (λ _{max})		
	IE4		
	Ni		
()	()	()	
	PC	PC	
()	()	()	
	F(K∞) = $\frac{k}{s} = \frac{(1 - R∞)^2}{2R∞}$		
	PC = 100[F(R∞) _{after} - F(R∞) _{before}]		
			:K
			:S
	(ISO)	R∞	

Accelerated aging

- Post color number

Giertz




k/s () ()



() .

()

()



k/s



.

)



()

()

()

EDTA

EDTA

()

EDTA

EDTA

EDTA

()

		Fe ⁺² +EDTA*		Fe ⁺²		%ISO
/	/	/	/	/	/	%ISO
/	/	/	/	/	/	L*
/	/	/	/	/	/	a*
/	/	/	/	/	/	b*
/	/	/	/	/	/	PC

دراصد ٥٪

		Fe ⁺² +EDTA*		Fe ⁺²		%ISO
/	/	/	/	/	/	%ISO
/	/	/	/	/	/	L*
/	/	/	/	/	/	a*
/	/	/	/	/	/	b*
/	/	/	/	/	/	PC

دراصد ٥٪

EDTA

- 1-Fernandez, N., Naranjo, M. E., Alvarez, J., Sarrantes, M., 1977. Research Experiences in Bagasse Pulp Bleaching, Progress report no. 12, Tappi Press.
- 2-Rapson, H.W., 1977. The Bleaching of Pulp, Tappi Press, pp 460,Atlanta, GA,USA.
- 3-Carter, H. A., 1996, The chemistry of Paper Preservation, Part 2: The Yellowing of Paper and Conservation Bleaching, J. of Chemical Education., 73 (11) : 1068-1073.
- 4-Svensson, E., Lennholm, H and Lversen, T., 1998. Pulp Bleaching With Dithionite, : Brightening and Darkening Reactions, J. of Pulp and Paper Science, 24(8): 254-259.
- 5-Gierer, J, 1990. Basic Principles of Bleaching, Part I, Holzforschung, 44(6): 395-400.
- 6-Ni, Y et al., 1997. Minimization of the Brightness Loss , Tappi Journal, 98(10) : 72-75.
- 7-Giertz, H.W. 1945. Svensk. Papperstian, 75-233.
- 8-Kubelka, p., 1948. New Contribution to the Optics of Intensity of Light-Scattering Material. Part I, Optical Society of America J., 38(5): 448-457.
- 9-Chirat, C. and Delachapelle V., 1999. Heat and Light Induced Brightness Reversion of Bleached Chemical Pulp, J. of Pulp and Paper Science: 25(6); 201-205.
- 10-Gellerstedt, G., Petterson, I. And Sundin, S. light. 1983. Induced and heat induced yellowing of mechanical Pulps. Svensk Papperstidn 86: R157-163.
- 11-Ghosh. A., Ni, Y., 1997. Metal Ion Complexes and Their Relationship to Pulp Brightness, J. of Pulp and Paper Science. 24(1), 26-31.

Improving Optical Properties of Soda Bagasse Pulp Utilizing Complementary Bleaching with Sodium Hydrosulfite

A. Abdulkhani¹

S.A. Mirshokraie²

Abstract

Soda bagasse pulp was bleached, using sodium hypochlorite and sodium hydrosulfite sequence or vice versa (reverse sequence). The optical behavior of the bleached pulps was investigated through optical and thermal accelerated aging of the handsheets. Some characteristics such as brightness (R_∞), lightness (L^*), yellowness (b^*) and greenness (a^*) factors as well as absorption and scattering coefficients of light before and after aging were assessed. Also, in this study, the effect of consistency (per cent) of pulp and Fe^{2+} ion and a chelating agent (EDTA) on yellowing of paper was determined. The results indicate that application of a reductive bleaching stage after oxidative treatment of the pulp will cause more brightness stability as compared to the reverse sequence.

Keywords: Soda bagasse pulp, Sodium hypochlorite, Sodium hydrosulfite, Optical properties, accelerated aging, Complementary bleaching.

1- Senior Expert of Wood and Paper Science and Technology, Faculty of Natural Resources, University of Tehran,
(E-mail:Abdulkhani@nrf.ut.ac.ir)

2. Associate Professor, Chemistry Department, Payame Noor University