

AA H

NaCl

% / NaCl AA H EIS  
EDAX SEM

AA H

## EIS study on corrosion behaviour of AA 5083-H321 Aluminum-Magnesium alloys in stagnant NaCl solution.

K. Jafarzadeh<sup>1</sup>, T. Shahrabi<sup>1</sup>, S.M.M. Hadavi<sup>2</sup> and M.G. Hosseini<sup>3</sup>

1. Materials Engineering. Department., Tarbiat Modares University  
2. Malek Ashtar University., Tehran, 3. Faculty of Chemistry, Tabriz University.

**Abstract-** In this research, EIS technique was utilized to study the corrosion behaviour of AA5083-H321 aluminum-magnesium alloy in 3.5% NaCl solution. Impedance spectra were obtained during 240 hours of exposure of the sample to the test solution. The surface and cross section of the samples were studied by scanning electron microscopy (SEM) and EDAX analysis.

The results indicated the impedance of the surface is controlled by the reactions that occur in the passive layer on top of intermetallic particles and substrate. Intensification of cathodic and anodic reactions at the first 24 hours decreases the impedance of the surface. However, accumulation of corrosion products inside the pits and subsequently suspension of cathodic reactions on top of intermetallic particles tends the impedance of the surface to decrease. Meanwhile pitting corrosion provides inhomogeneous surface, which prevents the capacitors to behave ideally. Therefore, capacitors are substituted by constant phase element.

**Keywords:** Pitting Corrosion, AA5083-H321 Aluminum-Magnesium Alloy, Electrochemical Impedance Spectroscopy, intermetallic Particle, Passive Layer

]

.[ AA H

.[ ]

Barbucci .

[ , ] NaCl

.[ ]

Mansfeld

.[ ]

Bessone Munoz

.[ ]

EIS

EIS

NaCl

.[ ]

.[ ]

.[ ]

Botana

EIS

NaCl

.[ ]

NaCl

AA

H

Archive of SID

AA H

[ ]

( )  
NaCl % /

SiC

( )

EDAX

NaCl

[ ]

pH=

Cr Mn Fe

( )

[ ]

( )

[ ] AlCl<sub>3</sub>

( )

/

(EGandG Princeton Applied

Research 273A)

Al<sup>+3</sup>


± mv

AC


ZView2

AA5083-H321


	Mg	Si	Mn	Cr	Fe	Cu	Zn	Ti	Al
	/	/	/	/	/	/	/	/	




( )



( )



( )



( )

NaCl

( ):

NaCl

( )

( )



EDAX ( )

( )

EDAX ( )

$(\Omega.cm^2)$   $=CPE_{dl}$   $(\mu F.cm^{-2})$   $=R_t$   $/$   $/$   $[ ]$   
 NaCl % /  $( )$   $:$   $( )$   
 $Al^{+3}$   $(\Omega.cm^2)$   $(\mu F.cm^{-2})$   $(\Omega.cm^2)$   $(\mu F.cm^{-2})$   
 $[ ]$   $=R_s$   $(\Omega.cm^2)$   $=R_{int}$   $=C_{int}$   $=R_{np}$   $=CPE_{np}$

**Solution**



$( )$   
 $( )$   $( )$ :  
 $( )$   $( )$



NaCl % /

AA5083-H321

R<sub>p</sub>

( )

CPE<sub>p</sub>

( )

R<sub>np</sub>

R<sub>p</sub>

( )

:

( )

$$R_p = R_{np} + R_{int}$$

( )

[ ]

T

CPE

(CPE)

:

( )

$$Z_{CPE} = 1/[T(j\omega)^n]$$

( )

:

( )

N

R<sub>np</sub>

R<sub>int</sub>

( )

F.cm<sup>-2</sup>.s<sup>n-1</sup>

C


=T

Time (hr)	$R_{int}$ (ohm.cm <sup>2</sup> )	$C_{int}$ (μF.cm <sup>-2</sup> )	$R_{np}$ (ohm.cm <sup>2</sup> )	$T_{np}$ (μF.cm <sup>-2</sup> .s <sup>n-1</sup> )	$n_{np}$
		/		/	/

Time (hr)	$R_{int}$ (ohm.cm <sup>2</sup> )	$C_{int}$ (μF.cm <sup>-2</sup> )	$R_{np}$ (ohm.cm <sup>2</sup> )	$T_{np}$ (μF.cm <sup>-2</sup> .s <sup>n-1</sup> )	$n_{np}$
		/		/	/
		/		/	/
		/			/


NaCl % /

Time (hr)	$R_p$ (ohm.cm <sup>2</sup> )	$T_p$ (μF.cm <sup>-2</sup> .s <sup>n-1</sup> )	$n_p$	$R_{ct}$ (ohm.cm <sup>2</sup> )	$T_{dl}$ (μF.cm <sup>-2</sup> .s <sup>n-1</sup> )	$n_{dl}$
		/	/		/	/
			/			/
		/	/			/
		/	/			/
		/	/			/
		/	/			/
		/	/			/
		/	/			/




$(\mu\text{F}\cdot\text{cm}^{-2})$  /  
 $=R_{ct}$   
 $(\Omega\cdot\text{cm}^2)$  / ( )  
 [ ]  
 (OH)  $C_{int}$   $R_{int}$  ( )  
 pH ( )  
 [ ]  
 $C=\epsilon \epsilon_0\cdot A\cdot d$  ( )  
 ( ) T : ( )  
 $=C$   
 $=\epsilon_0$   $=R_s$   
 $=\epsilon$   $(\Omega\cdot\text{cm}^2)$   
 $=A$   $(\mu\text{F}\cdot\text{cm}^2)$   $=CPE_p$   
 $=d$   $(\Omega\cdot\text{cm}^2)$   $=R_p$   
 $T_p$   $=CPE_{dl}$





( )



( )

( ):

NaCl% /

( )

( $R_p$ )

$T_p$

( $R_{np}$ )

$R_p$

$Al^{+3}$

( $R_p$ )

$Al^{+3}$


$R_p$

$T_p$


$R_p$

$\text{ohm.cm}^2$

$T_{dl}$  [ ] /  $T_p$  ( )  
 $(R_{ct})$  ( )



( )



( )

AA5083-H321

( ) ( ) ( ) NaCl % /

$$\theta = \text{Arctg}(-Z_{im}/Z_{re})$$

( )

(Deg) =  $\theta$

(ohm.cm<sup>2</sup>) =  $Z_{im}$

(ohm.cm<sup>2</sup>) =  $Z_{re}$

(R<sub>ct</sub>)

Al<sup>+3</sup>

( )

T<sub>dl</sub> ( )

( ) T<sub>p</sub>

C=Q/V

( )

(F.cm<sup>-2</sup>)

=C

=Q

( )

(Coulomb)

(V)

=V

( )

Archive of SID

T<sub>p</sub>

T<sub>p</sub>

( )

EIS

( )

5. Z. A. Foroulis and M. J. Thbrikar, *On the kinetics of breakdown of passivity of preanodized aluminum by chloride ions*, J. of Electrochem. Soc., 122(10)(1975)81-89.
6. F. J. Martin, *Impedance studies of the passive film on aluminum*, Corrosion Science, 47(2005)3187-3201.
7. Z. S. Smailowska, *Pitting corrosion of aluminum*, Corrosion Science, 41(1999) 1743-1767.
8. R. Jianjun and Z. Yu, *The growth mechanism of pits in NaCl solution under anodic films on aluminum*, Surface and Coating Tech., 191(2005)311-316.
9. T. D. Burleigh, *Chapter 11: Corrosion of Aluminum and its Alloys*, in the Handbook of Aluminum, Alloy Production and Materials Manufacturing, (2003)421.
10. N. Birbilis and R. C. Buchheit, *Electrochemical characteristics of intermetallic phases in aluminum alloys*, Journal of the Electrochemical Society, B,152(4)(2005)140-151.
11. M. Bethencourt and F. J. Botana, *The influence of surface distribution of Al<sub>6</sub>(Mn,Fe) intermetallics on the electrochemical response of AA5083 aluminum alloy in NaCl solutions*, Materials Science Forum, 289-292(1998) 567-574.
12. R. E. Melchers, *Influence of temperature on seawater immersion corrosion of aluminum*, British Corrosion Journal, 36(3)(2001)201-204.
13. A. Aballe, M. Bethencourt, F. J. Botana, M. J. Cano and M. Marcos, *Localized corrosion of alloy AA 5083 in natural 3.5% NaCl Solution*, Corrosion Science, 43(2001)1657-1674.
14. Ph. Gimenez, *Experimental pH-potential diagrams of aluminum for seawater*, Corrosion, 37(12)(1981)673-682.
1. C. H. Holtyn, *Corrosion protection guidelines for aluminum hulls*, Marine Technology, 22(2)(1985)155-163.
2. S. Brown, *Feasibility of replacing structural steel with aluminum alloys in shipbuilding industry*, Report published by University of Viscontin at Madison. May (1999)
3. K. Nisancioglu, *Corrosion protection of aluminum alloys in seawater*, Eurocorr (2004)
4. J. R. Davis, *Corrosion of aluminum and aluminum alloys*, ASM International, (1999)85-94.

21. A. Aballe, M. Bethencourt and F. J. Botana, *Using EIS to study the electrochemical response of alloy AA5083 in solutions of NaCl*, *Materials and Corrosion*, 52(2001)185-192.
22. SSPC Standards, systems and specifications, 2, edited by James Rex, (1995)112-213.
23. A. Spirin, *Effect of external polarization on corrosion of structural aluminum alloys in Caspian seawater*, *Material Protection*, (1967)515-517.
24. W. S. Tait, *An Introduction to Electrochemical Corrosion Testing for Practicing Engineers And Scientists*, Parldocs Pub, (1994)73-76.
25. D. C. Silverman, *Primer on the AC technique, in Electrochemical Techniques for Corrosion Engineering*, R. Baboian, ed., NACE, Houston, (1987)73.
26. S. E. Freres, M. M. Stefenel, C. Mayer and T. Chierchie, *AC-Impedance measurement on aluminum in chloride containing solutions and below the pitting potential*, *J. of Applied Electrochem*, 20(1999) 996-999.
15. A. Barbucci and G. Bruzzone, *Breakdown of passivity of Al alloys by intermetallic phases in neutral chloride solution*, *Intermetallics*, 8(2000)305-312.
16. F. Mansfeld, *Analysis and interpretation of EIS data for metals and alloys*, technical report No. 26., Univ. of California, Los Angeles, Ca, USA, (1999).
17. A. G. Muñoz, and J. B. Bessone, *pitting of aluminum in non-aqueous chloride media*, *Corrosion Science*, 43(1999) 1447-1463.
18. M. Kliskik, J. Radosevic, S. Gudic and M. Smith, *Cathodic polarization of Al-Sn alloy in sodium chloride solution*, *Electrochimica Acta*, 41(21-22)(1998) 3241-3255.
19. E. Brillas, P. L. Cabot, F. Cantellas and J. A. Garrido, *Electrochemical oxidation of high purity and homogeneous Al-Mg alloys with low Mg contents*, *Electrochimica Acta*, 43(7)(1998)799-812.
20. H. B. Shao, J. M. Wang, and Z. Zhang, *Electrochemical impedance spectroscopy analysis on the electrochemical dissolution of aluminum in alkaline solution*, *J. of Electroanalytical Chemistry*, 549 (2003)145-150.