Archive of International Conference on

15 December 2016

RESEARCH IN

MECHANICAL ENGINEE

Buckling Behavior and Compressive Failure of Composite Laminates Containing Multiple Large Delaminations Growth with Cohesive Element Method

www.**rmeconf**.com

Rahnama, Saeed

Associate Professor, Department of Mechanical Engineering, University of Birjand, Birjand, Iran <u>srahnama@birjand.ac.ir</u>

Jafari, Saman

Master student, Department of Mechanical Engineering, University of Birjand, Birjand, Iran <u>Saman.Arez@birjand.ac.ir</u>

Sarayloo, Reza

Master student, Department of Mechanical Engineering, University of Birjand, Birjand, Iran reza.sarayloo@birjand.ac.ir

Abstract

The effects of delamination and delamination growth on buckling load on compressive loading for E-glass/epoxy composite laminates using multiple large delaminations with cohesive elements have been studied. A numerical study is carried out to determine the buckling load of rectangular composite plates. For the numerical (0/90/0/90)s oriented cross-ply laminated plates with multiple large delaminations are produced by using hand lay-up technique. The results of the delamination growth of structure of plates are found by clamping from the two edges by using FEM software and then these results are compared with the results obtained by experimental results. In addition, the compressive failure loads of composite laminates containing multiple large delaminations are found by compression test fixture. It is found that the longest and near-surface delamination size influences the buckling load and compressive failure load of composite laminates.

Keywords: Buckling, delamination growth, cohesive, finite element method

Archive of International Conference on RESEARCH IN MECHANICAL ENGINEERING

Singapore

15 December 2016

Introduction

Delamination is one of the most common and dangerous failure modes in laminated composites. Some of the causes of delaminations are manufacturing defects, impact load, and edge effects. Delaminations can bring about significant reduction in the strength, stiffness and load carrying capacity of laminated composites under compressive loads. Numerous computational have been carried out to determine the effect of delamination on the buckling behavior of laminated composites. [Whitcomb and Shivakumar] studied effects of delamination on the buckling and post buckling behavior of laminated composite suffering from rectangular embedded delaminations.

www.**rmeconf**.com

Helpful Hints

Manufacturing of the composite plates

The laminated composite plates with delamination and without delamination with (0 / 90 / 0 / 90) s fiber orientation are manufactured from the unidirectional E-Glass fiber and epoxy resin. The mechanical properties of the laminated composite plate are obtained by the standard tests. The composite laminated plates is produced by hand lay-up technique for determination of the mechanical properties. Average mechanical properties of the composite materials obtained from the experimental results are listed in Table 1.

Fiber volume ratio	V.	65	0/0
Density	ρ	1.27	g/cm ³
Longitudinal modulus	E1	41250	MPa
Transverse modulus	E ₂	9240	MPa
In-plane shear modulus	G12	3380	MPa
Major Poisson's ratio	v ₁₂	0.26	-

			•. •	
Table I. Mechanical	properties o	of E-Glass/epoxy	composites [Aslan and Sahinj.

Also mechanical properties of the cohesive elements taken in Table 2.

Table 2: mechanical properties of the conesive elements [wang et al].						
Longitudinal Young's modulus	E11	115	GPa			
Transverse Young's modulus	$E_{22} = E_{33}$	8.5	GPa			
Shear modulus	$G_{12} = G_{23}$	4.5	GPa			
Shear modulus	G13	3.3	GPa			
Poisson's ratio	U 12= U 13	0.29	-			
Poisson's ratio	U 23	0.3	-			
Penalty stiffness	K _P	850	MPa			
Interlaminar tensile strength	Т	3.3	MPa			
Interlaminar shear strength	S	7	MPa			
Fracture toughness	GIC	0.33	N/mm			
Fracture toughness	GIIC= GIIIC	0.8	N/mm			

Table 2: mechanical properties of the cohesive elements [Wang et al].

Modeling

The delaminations are assumed to be through the width. The gauge length of the specimen, L, is selected as 100 mm, the width w 30 mm, and the thickness t 2.4 mm. All multiple-delamination specimens have three delaminations distributing in the middle interface. Geometry of composite plate with three delaminations is illustrated in Fig. 1.



Fig. 1: Geometric Of Composite Plate.

Finite element mode

Under pure Mode I, II or III loading, the onset of damage at the interface can be determined simply by comparing the stress components with their respective tolerance. However, under mixed mode loading, damage onset may occur before any of the stress components involved reaches their respective tolerance. Therefore, it is assumed that delamination initiation can be predicted using the quadratic failure criterion [3].

$$\sqrt{\left(\frac{\sigma_z}{T}\right)^2 + \left(\frac{\tau_{xz}}{S}\right)^2 + \left(\frac{\tau_{yz}}{S}\right)^2} = 1$$
(1)

Under mixed-mode loading, the damage growth can be predicted using the quadratic interaction between the energy release rates in the same way as the delamination initiation can be predicted using the quadratic failure criterion [3].

$$\sqrt{\left(\frac{G_I}{G_{IC}}\right)^2 + \left(\frac{G_{II}}{G_{IIC}}\right)^2 + \left(\frac{G_{III}}{G_{IIIC}}\right)^2} = 1$$
(2)

Numerical study

The length of the delamination is a. The ratios of the delaminations length to specimen gauge length, a/L, are selected as 0.3, 0.5 and 0.8 in this numerical study. The buckling numerical are done under uniaxial compressive loading. The buckling numerical are carried out under displacement control and load–displacement plots are obtained.

Results and discussion

In the first part of this study, the critical buckling load results are obtained numerically for (0/90/0/90) s fiber orientation. The numerical critical buckling loads for different a values for delamination and delamination growth are given in Fig. 2, 3.





Fig. 2: buckling loads for different for delamination.



Fig. 3: buckling loads for different for delamination growth.



To illustrate the influence of the delamination length on the compression strength, the compression strength of plates was normalized with the corresponding strength without a delamination. The results, shown in Fig. 4, 5. Indicate that the compression strength is considerably reduced by the presence of a/L delamination, and that the reduction is more severe for longer delamination.



Fig. 4: Influence delamination on Buckling Load.



Fig. 5: Influence delamination Growth on Buckling Load.

Archive of International Conference on RESEARCH IN MECHANICAL ENGINEERING 15 December 2016 Singapore www.rmeconf.com



References

Whitcomb, JD. And Shivakumar, KN. (1989). Strain-Energy Release Rate Analysis of Plates with Post buckled Delaminations. Composite Materials 23(7). PP 714-734.

Aslan, Z. and Sahin, M. (2009). Buckling behavior and compressive failure of composite laminates containing multiple large delaminations. Composite Structures 89. pp 382-390.

Wang, RG. Zhang, L. Zhang, J. Liu, WB. And He, XD. (2010). Numerical analysis of delamination buckling and growth in slender laminated composite using cohesive element method, Computational Materials Science 50. pp. 20-31.